

Rigid Foam Insulation in Precast Sandwich Panel Applications

SYSTEM OVERVIEW

General Information

Concrete is a strong and highly durable material and a good choice in both commercial and multistory residential applications. However, precast concrete panel walls can absorb moisture from rain and vapor drive. Condensation buildup can reduce the effectiveness of the insulation and may cause other problems, including mold and mildew.

In precast sandwich wall construction, DuPont™ Styrofoam™ Brand Square Edge extruded polystyrene and DuPont™ Isocast™ R polyisocyanurate insulations combine superior insulating capabilities and dew point control with the additional strength of concrete. The closed-cell, rigid plastic foam insulations manufactured exclusively by DuPont provide dependable and predictable performance, even in severe moisture environments. Both are well-suited for use in precast concrete walls.

Precast Wall Assemblies

To form precast concrete walls, concrete is poured on both sides of the foam and the finished panel is held together structurally with connectors.

Precast concrete panels provide thermal mass, which can store considerable amounts of thermal energy. Rigid foam insulation isolates the thermal mass provided by the concrete panels, minimizing building interior temperature fluctuations under outside temperature swings.

This reduces energy consumption in hot and cold climates. For example, a 7" thick slab of concrete has the same R-value* as a pane of glass (R-1.5). A 2" thick layer of Styrofoam™ Brand Square Edge insulation, R-10, increases the total thermal value of the precast sandwich panel to R-11.5, almost eight times the value without it. A 2" thick layer of Isocast™ R polyisocyanurate insulation, R-13.0, increases the total thermal value of the precast sandwich panel to R-14.5, 10 times the value without it. (See Figure 1).

Buildings that incorporate precast sandwich panels made with Styrofoam™ Brand Square Edge or Isocast™ R insulation will perform more efficiently over time because of the insulations' superior long-term thermal performance and unparalleled moisture control qualities.




Figure 1. Precast sandwich panel wall with Styrofoam™ Square Edge or Isocast™ R insulation

Why Rigid Foam Insulation from DuPont?

Precast concrete wall manufacturers recognize the need for high-performance insulation in this application. Styrofoam™ Brand Square Edge insulation is an ASTM C578 Type IV extruded polystyrene insulation with smooth, high-density skins that make it virtually moisture resistant.

It has no facings that are susceptible to corrosion or delamination. Plus, Styrofoam™ Brand Square Edge insulation offers superior economical long-term thermal performance under the harsh conditions of freeze-thaw cycling, a common phenomenon exhibited in precast concrete panels in cold climates. Isocast™ R insulation is an ASTM C1289 Type I.

*R means resistance to heat flow. The higher the R-value, the greater the insulating power

on both sides that makes it virtually moisture resistant. It has no exposed metallic facings that are susceptible to corrosion or chemical reaction with the concrete, as the aluminum facer is completely covered by a polymer layer. Plus, DuPont™ Isocast™ R insulation offers superior economical thermal performance under the harsh vapor drive conditions often exhibited in precast concrete panels in cold climates.

Boards of both DuPont™ Styrofoam™ Brand Square Edge and Isocast™ R insulation are lightweight and easy to handle, cut and install. Refer to Tables 1 and 2 for physical properties of Square Edge and Isocast™ R insulations.

TABLE 1: Physical Properties of Styrofoam™ Square Edge Extruded Polystyrene Insulation

Property and Test Method	Value
Thermal Resistance, ASTM C518 ⁽¹⁾ , C177, Aged R-value per inch, ft ² ·h·°F/Btu	
@ 75°F mean temp.	5.0
@ 40°F mean temp.	5.4
@ 25°F mean temp.	5.6
Compressive Strength ⁽²⁾ , ASTM D1621, psi (kPa), min.	25
Flexural Strength, ASTM C203, psi, min.	50
Water Absorption, ASTM C272, % by volume, max.	0.1
Water Vapor Permeance ⁽³⁾ , ASTM E96, perm., max.	1.1
Coefficient of Linear Thermal Expansion, ASTM D696, in/in·°F	3.5 x 10 ⁻⁵
Maximum Use Temperature, °F	165

⁽¹⁾ Values are consistent with the criteria of ASTM C578 and the requirements of the FTC R-value rule (16 CFR Part 460).

⁽²⁾ Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first. Since Styrofoam™ Brand extruded polystyrene insulations are visco-elastic materials, adequate design safety factors should be used to prevent long-term creep and fatigue deformation.

⁽³⁾ Based on 1" thickness.

TABLE 2: Physical Properties of Isocast™ R Polyisocyanurate Insulation

Property and Test Method	Value
Thermal Resistance, ASTM C518 ⁽¹⁾ , C177, Aged R-value per inch, ft ² ·h·°F/Btu	
@ 75°F mean temp.	6.5
Compressive Strength ⁽²⁾ , ASTM D1621, psi (kPa), min.	25
Water Absorption, ASTM C272, % by volume, max.	0.05
Flexural Strength, ASTM C203, psi, min.	40
Water Vapor Permeance ⁽³⁾ , ASTM E96, perm., max.	<0.03
Dimensional Stability, 158°F, 97% RH, percent linear change, length, max.	1.0
Maximum Use Temperature, °F	190

⁽¹⁾ In accordance with ASTM C518.

⁽²⁾ Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first.



**For more information visit
building.dupont.com
or call 1-866-583-2583**

NOTICE: No freedom from any patent owned by DuPont or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries or regions. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DUPONT. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. The buyer assumes all risks as to the use of the material. Buyer's exclusive remedy or any claim (including without limitations, negligence, strict liability, or tort) shall be limited to the refund of the purchase price of the material. Failure to strictly adhere to any recommended procedures shall release DuPont Specialty Products USA, LLC or its affiliates, of all liability with respect to the materials or the use thereof. The information herein is not intended for use by non-professional designers, applicators or other persons who do not purchase or utilize this product in the normal course of their business.

CAUTION: When cured, these products are combustible and will burn if exposed to open flame or sparks from high-energy sources. Do not expose to temperatures above 240°F (116°C). For more information call the DuPont Contact Center at 866-583-2583 or contact your local building inspector. For emergencies contact Chemtrec 800-424-9300, CCN (Contract Number) 7442. The blowing agent contained within this product can exhibit vapor flame limits under the right conditions. If specific operating conditions are such that concentrations of the blowing agent above the lower flammable limit can accumulate in areas with high relative humidity and in the presence of high-energy electrical discharges or other ignition sources, additional measures such as increased ventilation or coded electrical equipment (class one, division two) may be warranted. DO NOT SMOKE DURING USE. DO NOT USE NEAR ANY OPEN FLAME OR ELECTRICAL SOURCE. OUTDOOR USE ONLY. INDOOR USE INCREASES LIKELIHOOD OF IGNITABLE CONDITIONS. Read the label and (Material) Safety Data Sheet ((M)SDS) carefully before use. Wear gloves, and goggles or safety glasses. Provide adequate ventilation or wear proper respiratory protection. Contents under pressure. For outside use only.

Building and/or construction practices unrelated to insulation could greatly affect moisture and the potential for mold formation. No material supplier including DuPont can give assurance that mold will not develop in any specific system.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2023 DuPont.