

PROPERTIES	METHOD	DuPont™ Tyvek® AtticWrap™ weather resistive barrier
Air Penetration	Gurley Hill (TAPPI T-460) (sec/100cc)	1100
Water Vapor Transmission	ASTM E-96 Method B (g/m ² -24 hrs) (US perms)	185 27
Water Penetration Resistance	AATCC-127 (cm)	200
Breaking Strength	ASTM D-882 MD/CD (lbs/in)	26/29
Tear Resistance (Elmendorf)	ASTM-1922 MD/CD (grams)	4100/4800
Surface Burning Characteristics	ASTM E-84 Flame Spread	5 Class A
	Indexed Smoke Developed Value	40 Class A

Data listed above was measured by an accredited independent laboratory. Individual roll results may differ due to normal manufacturing variations.

WARNING: DuPont™ Tyvek® is combustible and should be protected from a flame and other high heat sources. If the temperature of DuPont™ Tyvek® reaches 750°F (400°C), it will burn and the fire may spread and fall away from the point of ignition.

For more information:

1-800-44-TYVEK
www.tyvek.com

DuPont™
Tyvek®
AtticWrap™



The miracles of science™