



ITW QUICKSET – TECHNICAL BULLETIN #1033B HIGH STRENGTH, RAPID-SETTING, MULTI-PURPOSE EPOXY

Revised: 05/2018

BULLETIN DESCRIPTION

ITW QUICKSET is a two-component high strength, fast-setting, multi-purpose epoxy with a convenient mixing ratio of 1:1 by volume.

USE & BENEFITS

ITW QUICKSET can be used as a liquid shim, an anchoring adhesive or as a structural gap filler. It is recommended for applications requiring rapid turnaround of equipment but not for equipment requiring precise alignment (i.e. less than 0.005" or 0.127 mm movement over the life of the equipment).

ITW QUICKSET can be quickly mixed and applied under concrete blocks, between steel plates or between concrete and steel. ITW QUICKSET was designed to fill a void within 15 minutes then harden to 78 shore D in 30 minutes and 84 Shore D in 4 hours at a concrete / steel temperature of 70° F (21° C). ITW QUICKSET will reach a minimum compressive strength of 14,500 psi (101.5 MPa) in about 6 hours at 70° F (21° C).

DESIGN CONSIDERATIONS

Because ITW QUICKSET was designed to be installed

within 15 minutes after mixing, the void area it fills must be of a size that can be completely filled within that time based on the application method chosen. ITW QUICKSET is a hot curing epoxy so the temperature of the epoxy, the temperature of the concrete or steel and the ambient temperature must be taken into consideration when installing it. A maximum thickness of 18mm (3/4 inch) recommended at 21° C (70° F) but ITW QUICKSET can be applied at ambient temperatures between 40° F and 85° F (5° C and 29° C). For applications outside either of these ranges contact the Engineering Services Department at ITW Performance Polymers.

APPLICATION INSTRUCTIONS



ITW QUICKSET comes in gallon cans, 5 gallon buckets or 55 gallon drums. It can be mixed and applied by either mixing it with a Jiffy Mixing blade for 3 minutes then pouring it in place or by using a manual or automated mixing and dispensing system.

An automated mixing and dispensing system is recommended when it is necessary to apply a large volume of the epoxy in a short period of time. An automated dispensing system consists of metering pumps, hoses and a manually operated dispensing gun with a static mixing nozzle.

Depending on the temperature of the concrete or steel,

the thickness of the gap to be filled and the importance of a fast cure rate, ITW QUICKSET epoxy resin and hardener may need to be individually pre-mixed prior to dispensing. It should also be preconditioned for 24 hours while still in the drum to 65°F to 75°F (18°C to 24°C) prior to dispensing.

Please consult ITW Performance Polymers for additional information.



PHYSICAL PROPERTIES

COMPRESSIVE STRENGTH	14,500 psi (101.49 MPa)	ASTM D-695
COMPRESSIVE MODULUS OF ELASTICITY	347,000 psi (2392.5 MPa)	ASTM D-695
LINEAR SHRINKAGE	< 0.5%	ASTM D-2566
FLEXURAL STRENGTH	15,400 psi (106.18 MPa)	ASTM C-580
FLEXURAL MODULUS OF ELASTICITY	191,000 psi (1316.9 MPa)	ASTM C-580
TENSILE STRENGTH	8,800 psi (60.67 MPa)	ASTM D-638
TENSILE MODULUS:	191,000 psi (1316.9 MPa)	ASTM D-638
TENSILE LAP SHEAR STRENGTH	908 psi (6.26 MPa) after 30 min. >1,300 psi (9 MPa) after 7 days	ASTM D-1002
% ELONGATION AT BREAK	5.9%	
SPECIFIC GRAVITY OF RESIN	1.17	
VISCOSITY OF RESIN	48,800 cps @ 10 RPM using Viscosity Brookfield Viscometer Spindle #3	
SPECIFIC GRAVITY OF HARDENER	1.66	
VISCOSITY OF HARDENER	8,800 cps @ 20 RPM using Viscosity Brookfield Viscometer Spindle #3	
MIXED VISCOSITY	27,000 cps @ 20 RPM using Viscosity Brookfield Viscometer Spindle #3	
GEL TIME @ 75° F (24°C)	15 min 100 gram mass	
SHORE D HARDNESS	70 @ 30 Minutes @ 70°F 78 @ 1 Hour 82 @ 4 Hours 84 @ 1 Day	
FIRE RESISTANCE	Self Extinguishing	ASTM D 635

ITW PERFORMANCE POLYMERS

130 Commerce Drive | Montgomeryville | PA 18936 | USA | T: 215-855-8450 | E-mail: customerservice.na@itwpp.com | www.itwperformancepolymers.com

PRODUCT INFORMATION

UNIT COVERAGE	2 gal Unit: 435 in. ³ (7.1 L) 10 gal Unit: 2,282 in. ³ (37.4 L) 110 gal unit: 21,131 in. ³ (346.3 L)
APPLICATION TEMPERATURE	41°F (5°C) to 95°F (35°C)
PACKAGING PER UNIT	2 gal Unit: Resin – 9.3 lbs. (4.2 kg), Hardener – 12.86 lbs. (5.8 kg) in two (2) 1 gal cans 10 gal Unit: Resin – 48.5 lbs. (22 kg), Hardener – 68 lbs. (30.8 kg)) in two (2) 5 gal cans 110 gal unit: Resin – 441 lbs. (200 kg), Hardener – 641 lbs. (291 kg) in two (2) 55 gal drums
CURE TIME (APPROXIMATE)	6 hours @ 21° C (70° F)
POT LIFE	15 min. @ 21° C (70° F)
SHELF LIFE	2 years
CLEAN UP	IXT-59 or similar epoxy solvent

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support. **Warranty:** ITW Performance Polymers, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment. **Warranty Claims:** If any product fails to meet the above, ITW Performance Polymers will, at its option, either replace the product or refund the purchase price. ITW Performance Polymers will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered. **Disclaimer:** ITW Performance Polymers makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose. Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Performance Polymers' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Performance Polymers' election. Under no circumstances shall ITW Performance Polymers be liable for any indirect, incidental or consequential damages. **Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Performance Polymers. No term of any purchase order shall serve to modify any provision of this document. **Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Performance Polymers may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.

ITW PERFORMANCE POLYMERS

130 Commerce Drive | Montgomeryville | PA 18936 | USA | T: 215-855-8450 | E-mail: customerservice.na@itwpp.com | www.itwperformancepolymers.com