



# CHEMSTOP WB REGULAR, HEAVY DUTY

## WATER-BASED, SILANE/SILOXANE PENETRATING WATER REPELLENT

### PACKAGING

CHEMSTOP WB HD

5 gal (18.9 L) pail

Code: TL1912505 (HD)

Code: TL1912505 (Regular)

55 gal (208 L) drum

Code: TL1912555 (HD)

Code: TL1912555 (Regular)

1 gal (3.8 L) jugs, 6 per case

Code: TL1912501 (HD)

Code: TL1910501 (Regular)

### APPROXIMATE COVERAGE

CHEMSTOP WB REGULAR

1 coat, dense surface:

80 to 150 ft<sup>2</sup>/gal (2.0 to 3.7 m<sup>2</sup>/L)

CHEMSTOP WB HD

1st coat, porous surface:

40 to 60 ft<sup>2</sup>/gal (1.0 to 1.5 m<sup>2</sup>/L)

2nd coat, porous surface:

60 to 100 ft<sup>2</sup>/gal (1.5 to 2.4 m<sup>2</sup>/L)

Coverage rates are approximate and for estimating purposes only.

### CLEAN UP

Clean drips, runs, and overspray residue while still wet, using detergent and water. CHEMSTOP WB will not etch common glass; spills and overspray onto glass can be easily removed with a damp cloth. Dried material may require mechanical abrasion for removal. Clean application and spray equipment with detergent and water immediately following use.

### SHELF LIFE

1 year in original, unopened package

### SPECIFICATIONS AND COMPLIANCES

- Federal specification SS-W-110C
- Complies with all U.S. EPA and local VOC regulations, including OTC, LADCO, Maricopa County, and California (CARB and SCAQMD)

### DESCRIPTION

CHEMSTOP WB is a water-based, ready to use, siloxane/silane water repellent. CHEMSTOP WB REGULAR is formulated for use on dense surfaces, such as pre-cast or poured-in-place concrete. CHEMSTOP WB HEAVY DUTY is used on porous surfaces such as light weight concrete, concrete block and mortar joints.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Allows concrete/masonry repel water and salts
- Colorless & odorless
- Non-staining, non-yellowing, breathable
- Reduces efflorescence and spalling
- Will not alter texture or appearance of treated surface

#### PRIMARY APPLICATIONS

- Concrete
- Concrete block
- Lightweight concrete
- Brick
- Mortar joints
- Precast structures
- Horizontal or vertical
- Interior or exterior

#### APPEARANCE

CHEMSTOP WB is a milky white liquid in the container. CHEMSTOP WB dries clear, does not change the appearance of the substrate, and leaves no gloss on the finished surface. A small test area is strongly recommended to confirm appearance prior to beginning full application.

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Material Properties @ 75 °F (24 °C), 50% RH	Regular	Heavy Duty
Viscosity	50 cp	50 cp
Depth of Penetration (substrate dependent)	3/8" (9.5 mm)	3/8" (9.5 mm)
Active Content (by weight)	6%	10%
Reduction in Water Leakage ASTM E514	Brick: N/A Mortar Block: N/A	Brick: 100% Mortar Block: >91%
Reduction in Water Absorption SS-W-110C	90.5%	92.3%
Flash Point	> 200 °F (93 °C)	> 200 °F (93 °C)
Accelerated Weathering, 1500 hours, ASTM G154	no change	no change
Abrasion Resistance	excellent	excellent
Dirt Pick-Up	none	none
VOC Content	≤ 5 g/L	≤ 5 g/L

---

## DIRECTIONS FOR USE

**Surface Preparation:** Cure new concrete a minimum of 3 days before application. Surface should be structurally sound, clean, dry, free of dust, dirt, paint, efflorescence, laitance and other contaminants that will prevent the proper penetration of CHEMSTOP WB. A dry substrate is required for proper penetration of the sealer. Prior to application, joints or cracks must be properly sealed or filled. If acid is used for cleaning, neutralize completely before application of CHEMSTOP WB.

**Application:** Low pressure airless spray equipment is the preferred method of application, although for smaller areas, application with brush or rollers may also be acceptable. Application should be from the bottom up to ensure uniform product distribution. Apply a saturation coat with a 6 to 8 in (15 cm to 20 cm) controlled rundown. For dense surfaces, one saturation coat of CHEMSTOP WB Regular is normally required. For porous surfaces two or more saturation coats of CHEMSTOP WB Heavy Duty may be required, applied using a "wet on wet" technique.

---

## PRECAUTIONS/LIMITATIONS

- Do not dilute
- Temperature of air and surface must be at least 45 °F (7 °C) and rising.
- Application at temperatures above 90 °F (32 °C) is not recommended.
- Do not apply if rain is expected within 12 hours of application.
- Water repellency properties will develop 24 hours to 5 days after application.
- CHEMSTOP WB is not intended to seal cracks or withstand hydrostatic pressure.
- Uneven application may result in a blotchy appearance of the surface.
- Mask off/cover windows, window frames, aluminum, steel, etc. before applying CHEMSTOP WB.
- Do not apply a "fog" coat
- Do not allow to puddle. All product should penetrate the substrate with no surface build-up.
- Store between 40 to 90 °F (4 to 32 °C)
- PROTECT FROM FREEZING
- CHEMSTOP WB may exhibit minor settling upon storage. Agitation prior to use may be necessary.
- A small (6' x 6') test area is strongly recommended prior to starting full application, in order to ensure desired performance results, aesthetics, and coverage rates. Allow 5 to 7 days for product to fully react before evaluating.
- In all cases, consult the Safety Data Sheet before use.

Rev. 02.22

---

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.