

## WATER REDUCERS

Master Format #: 03 30 00 03 40 00 03 70 00

# EUCON™ WR 75

WATER REDUCING, SET RETARDING ADMIXTURE



EUCLID CHEMICAL

## PRODUCT INFORMATION

### PACKAGING

Packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums and 5 gal (18.9 L) pails

### SHELF LIFE

1 year in original, unopened container

### SPECIFICATIONS/COMPLIANCES

ASTM C494, Type A, B & D

AASHTO M194

## DESCRIPTION

EUCON WR 75 is a synthetically produced liquid, water reducing and retarding admixture for concrete that has been formulated to give optimum performance in reducing water requirements for concrete. EUCON WR 75 contains no added chlorides or chemicals known to promote the corrosion of steel.

## PRODUCT CHARACTERISTICS

### FEATURES & BENEFITS

- Improves finishability
- Improves workability
- Reduces segregation
- Extending setting time
- Increases durability
- Reduces water requirement
- Increases strength
- Reduces permeability
- Improves finished appearance
- Reduces cracking

### PRIMARY APPLICATIONS

- Flatwork Concrete
- Ready mixed concrete
- Architectural concrete
- Hot weather concrete
- Bridge Decks
- Mass concrete



## PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain EUCON WR 75 above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated. Do not agitate with air or an air lance.
- Add to mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

## TECHNICAL INFORMATION

### PERFORMANCE DATA

The following test results were achieved using typical ASTM C494 mix design requirements, 517 lb/yd<sup>3</sup> (307 kg/m<sup>3</sup>) cement content and similar ( $\pm 0.5$ )% air content. These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C494. Changes in materials and mix designs can affect the dosage response.



## DIRECTIONS FOR USE

EUCON WR 75 is typically used at dosages of 2 - 5 oz/100 lbs (130 - 325 mL/100 kg) of cementitious material. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

EUCON WR 75 has been tested per ASTM C494 at a Type A dosage of 2 oz/100 lbs (130mL/100 kg) of cementitious materials and at 5 oz/100 lbs (325 mL/100 kg) of cementitious materials for Type B and D requirements.

EUCON WR 75 should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement. Because of variations in job conditions and concrete materials, dosages other than the recommended amounts may be required. In such cases, contact your local Euclid sales representative.

Rev. 03.21

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.