

WATERPROOFING

Master Format #: 07 16 13

TAMOSEAL

CEMENT-BASED WATERPROOFING TREATMENT



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bag

Code: TR2101650501 (Gray)

Code: TR210365\$ (Colors, MTO)

50 lb (22.7 kg) pail

Code: TR2102750501 (Gray)

Code: TR210375\$ (Colors, MTO)

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

18 months in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- TAMOSEAL is NSF/ANSI/CAN 61 certified for use with potable water. Note: TAMOSEAL is NSF/ANSI/CAN 61 certified in the Gray and White colors only.

DESCRIPTION

TAMOSEAL is a cement-based, polymer-modified material designed to waterproof concrete and masonry. When mixed with AKKRO-7T or FLEX-CON acrylic admixture, it becomes suitable to seal vertical and light duty horizontal surfaces.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Waterproofs and decorates
- Tenacious bond
- Becomes an integral part of substrate
- Durable
- Breathable
- Slightly flexible to seal static cracks

PRIMARY APPLICATIONS

- Concrete and block foundations
- Water tanks
- Reservoirs
- Interior/exterior
- Balconies

APPEARANCE

TAMOSEAL is available in two standard colors: Gray and White. Special colors subjected to minimum order quantities include: Oyster, Alpine, Navajo, Pearl, Silver, and Summer.

COVERAGE

Under normal waterproofing conditions, apply the TAMOSEAL at the following coverage rates:

Base Coat	2 lbs/yd ² (1.08 kg/m ²)	225 ft ² /50 lb bag (21 m ² /22.7 kg bag)
Finish Coat	1 lbs/yd ² (0.5 kg/m ²)	450 ft ² /50 lb bag (42 m ² /22.7 kg bag)

The total thickness of the two coats will be approximately 1/16 to 1/8 inch, or 125 mils (1.6 to 3.22 mm).

Note: Coverage rates are approximate and will depend on the texture and porosity of the substrate.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	7 days 4,500 psi (31.0 MPa) 28 days 6,400 psi (44.1 MPa)
ASTM C348	Flexural Strength	7 days 350 psi (2.4 MPa) 28 days 810 psi (5.6 MPa)
ASTM C190	Tensile Strength	7 days 330 psi (2.3 MPa) 28 days 390 psi (2.7 MPa)
ASTM C67	Absorption	24 hour soak4.4% 5 hour boil3.9%
ASTM C672	Freeze/Thaw Resistance	Loss at 50 cycles 1.20%
ASTM C666	Durability Factor	After 300 cycles101.0
	Working Time	1 hour
ASTM E514	Water Permeance After coating leaking wall	Extent of damp area @ 72 hours0.0% Maximum leakage: 1 hour.none Leakage rate mL/hrnone Permeance ratingExcellent
	Salt Spray Resistance	300 hour exposure at 5% solution at 90 °F (32 °C) resulted in no adhesion loss or deterioration at completion of test.
Fed. Test 141 Method 6272	Fungus Growth Resistance	Resistant
Fed. Spec TT-C-00555	Resistance to Wind Driven Rain	Excellent
ASTM E96	Water Vapor Transmission	12 Perms
ASTM G96	Weatherometer 6000 hrs	No crazing, cracking, chipping, flaking, light chalking, or color change. No other deterioration.
Minimum # of Coats: 2	Maximum Number of Coats: 2	Induction Time: 10 minutes
Recoat Cure Time: 12 to 24 hours		Recoat Cure Temp: > 40 °F (4.4 °C)
Final Cure Time: 7 days minimum		Final Cure Temp: > 40 °F (4.4 °C)

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: New concrete and masonry must be cured 7 days before application of TAMOSEAL. The surface must be structurally sound, clean and free of dirt, oil, and other contaminants. Abrade the surface to achieve a surface profile equal to CSP 1-3 in accordance with ICRI Guideline 310.2. Repair all surface defects including cracks and voids. Allow patches and other surface preparations to cure for 24 hours. Saturate surface dry (SSD) the substrate with potable water prior to TAMOSEAL application.

Mixing: TAMOSEAL must be mechanically mixed using a slow speed motor and mixing blade to thoroughly disperse the ingredients. Do not aerate the mix.

For Vertical Applications: One 50 lb (22.7 kg) bag of TAMOSEAL requires 2 gal (7.6 L) of mixing liquid. This consists of 2 qt (1.9 L) of AKKRO-7T blended with 6 qt (5.7 L) of potable water, or 2.3 qt (2.2 L) of FLEX-CON blended with 5.7 qt (5.4 L) of potable water. **For Horizontal Applications:** One 50 lb (22.7 kg) bag of TAMOSEAL requires 2 gal (7.6 L) of mixing liquid. This consists of 1 gallon (3.8 L) of AKKRO-7T blended with 1 gal (3.8 L) of potable water or 1.15 gallon (4.4 L) of FLEX-CON blended with 0.85 gallon (3.2 L) of potable water.

Pour approximately one half of the required mixing liquid into an empty, clean container and begin slow speed mixing. Slowly add TAMOSEAL and the remainder of the mixing liquid as needed to the mixture. Stop mixing and allow the mixture to “fatten” for ten minutes. Re-mix to achieve proper consistency. Use mixed TAMOSEAL within one hour.

Application: Saturate surface dry (SSD) the substrate with potable water before starting any TAMOSEAL application.

Hand Brush: Apply TAMOSEAL using a 6 in. (15 cm) masonry brush. Load bristles with TAMOSEAL and apply a heavy coat using long, smooth horizontal strokes. Apply sufficient material to fill all voids. Final strokes should all be in one direction to produce an even texture and finish. Allow first coat to dry for 12 to 24 hours before applying a finish coat.

Push Broom: Use a 5 gal (18.9 L) pail or wide mouth tub to hold TAMOSEAL. Dip a 10 in. (25 cm) tampico-bristle push broom into the TAMOSEAL and mix just enough to load the bristles. Apply a heavy coat using long, even horizontal strokes. Apply sufficient material to fill all voids. Lift the brush at the end of each stroke. Final strokes should all be in one direction to produce an even texture and finish. Do not overbrush. Allow first coat to dry for 12 to 24 hours before applying a finish coat.

Spray: Use heavy-duty spray equipment capable of spraying cement coatings or mastics.

Horizontal Applications: Use a water-based cure and seal from Euclid Chemical on all horizontal applications for added protection and ease of cleaning.

Note: *Prior to application, it is recommended that a mock up or field sample be made containing all materials that will be coated. Obtain approval of the architect or owner for the final color, texture and coverage rate before proceeding with work. Retain approved sample until the project is completed.*

PRECAUTIONS/LIMITATIONS

- Do not apply to frozen or frost filled surfaces or when temperature is expected to fall below 40 °F (4 °C) in the 24 hour period following application.
- Do not use on moderate to heavy traffic bearing surfaces.
- When applied to the inside of open cisterns, tanks, etc., do not fill with water for at least 7 days after application.
- Some colors may chalk or show water marks after weathering.
- When using TAMOSEAL containing AKKRO-7T or FLEX-CON in enclosed tanks or reservoirs, make sure that adequate ventilation is available during the application and the total curing period.
- Not recommended for negative side waterproofing where hydrostatic pressures exceed 8 ft (2.4 m) water head.
- TAMOSEAL should not be applied to surfaces actively leaking.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.25

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.