



VERTICOAT

TWO COMPONENT, TROWEL GRADE VERTICAL & OVERHEAD CONCRETE REPAIR MORTAR

PACKAGING

54 lb (24 kg) pail

Code: 046B 96 (kit)

54 (24 kg) bag & jug

Code: 046B 50 (bag & jug separate)

APPROXIMATE YIELD

54 lb (24 kg) unit: 0.48 ft³ (0.014 m³) per unit when mixing Part A powder with Part B liquid.

MINIMUM/MAXIMUM APPLICATION THICKNESS

1/8 to 4 inches (3 to 102 mm)

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

Verticoat (powder): 2 years in original, unopened package

Verticoat Liquid: 18 months in original, unopened package

DESCRIPTION

VERTICOAT is a polymer modified cementitious mortar for vertical and overhead concrete and masonry repairs. It sets rapidly to allow quick, easy repairs of concrete surfaces both interior and exterior. VERTICOAT is a two component mortar designed for trowel applied repairs.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Fast setting for rapid repairs up to 4" (102 mm)
- High compressive strengths
- Excellent resistance to freeze-thaw cycling
- Suitable for both interior and exterior applications
- Excellent bond to sound concrete
- Compatible with galvanic anodes

PRIMARY APPLICATIONS

- Vertical and overhead repair of scaled and spalled concrete
- Repair of honeycombed surfaces
- Parking structures & bridges
- Retaining walls
- Ceilings and sloped surfaces

APPEARANCE

VERTICOAT is a free-flowing powder designed to be mixed with a white latex liquid (VERTICOAT LIQUID). After mixing and placing, the color may initially appear darker than the surrounding concrete. While this color will lighten up substantially as the VERTICOAT cures and dries out, the repair may always appear somewhat darker than the surrounding concrete.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109 2" (50 mm) cubes	Compressive Strength	1 day 4,000 psi (28 MPa) 3 days 5,000 psi (35 MPa) 7 days 6,000 psi (41 MPa) 28 days 6,500 psi (45 MPa)
ASTM C496	Split Tensile Strength	7 days 700 psi (4.8 MPa) 28 days 800 psi (5.5 MPa)
ASTM C348	Flexural Strength	7 days 1,200 psi (8.3 MPa) 28 days 1,300 psi (9.0 MPa)
ASTM C191	Set Time	Initial Set 25 minutes Final Set 40 minutes
	Working Time	Approximately 20 minutes
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . 80% relative dynamic modulus
	Volumetric Resistivity	6,730 ohm-cm

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile of at least CSP 6 - 8 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming & Bonding (Saw Cut & Chipped Out Repairs): Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of VERTICOAT to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

Priming & Bonding (Vertical & Overhead Skim Coats/Toppings): Apply EUCOWELD 2.0 to a dry substrate or a scrub coat of VERTICOAT to the saturated surface dry (SSD) concrete surface. The repair material must be placed on the scrub coat before the scrub coat dries out.

Mixing: Single units may be mixed with a drill and "jiffy" type mixer. Use a paddle type mortar mixer for large jobs. NOTE: VERTICOAT HAS A WORKING TIME OF 20 MINUTES. DO NOT MIX MORE MATERIAL THAN CAN BE USED IN THAT TIME FRAME. All materials should be in the proper temperature range of 60 to 90 °F (16 to 32 °C). Add the appropriate amount of VERTICOAT LIQUID for the batch size, and then add the dry product. Mix for 2 to 3 minutes. The mixed product should be quickly transported to the repair area and placed immediately.

Placement: Place the VERTICOAT while the scrub coat is still wet. Trowel VERTICOAT onto the prepared surface at a minimum of 1/8" (3 mm), up to a maximum of 4" (102 mm). Trowel flush with surface and allow to stiffen. Finish to match the surrounding concrete surfaces.

Finishing: Finish the repair material to the desired texture. Do not add additional water to the surface during the finishing operation. Use EUCOBAR evaporation retarder.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the repair mortar with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. (NOTE: A SOLVENT BASED CURING COMPOUND SHOULD NOT BE USED ON THIS PRODUCT.) Under hot, windy or direct sunlight situations, apply a second coat of curing compound after the first has dried. If a curing compound is not desired, wet cure for a minimum of three days.

PRECAUTIONS/LIMITATIONS

- Do not use at temperatures below 45 °F (7 °C).
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- Store material in a dry place, above freezing.
- Cool temperatures slow setting while warm temperatures speed up set times.
- Keep repair from freezing until a minimum strength of 1,000 psi (7 MPa) is reached.
- In all cases, consult the Safety Data Sheet before use.

Rev. 05.24

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.