


# Technical Information Sheet



## BASEGARD™ SA Base Sheet

| Item Description   | Item Number |
|--------------------|-------------|
| 1 Roll (2 Squares) | W71FSP70SA  |

**Meets or exceeds performance requirements of ASTM 4601**

## Description

BASEGARD SA Base Sheet consists of a Styrene-Butadiene-Styrene (SBS) rubber modified, self-adhesive asphalt blend reinforced with a 1.8 lb/100 ft<sup>2</sup> (90 g/m<sup>2</sup>) glass fiber mat and coated with a fine mineral release agent on the top surface and an opaque release film on the bottom surface. BASEGARD SA Base Sheet can be used as a base layer or as an effective vapor retarder. When used as a vapor retarder, ISO 95+™ GL / ISOGARD™ GL, RESISTA™ / ISOGARD CG or ISOGARD HD Cover Board may be adhered to the top of BASEGARD SA Base Sheet with I.S.O. Twin Pack™ Insulation Adhesive, I.S.O. Spray™ R Insulation Adhesive, I.S.O.Stick™ Insulation Adhesive, Twin Jet, or hot asphalt.

## Method of Application

1. Application of SA Primer (W70RACSAP5) is always required on concrete and existing roof surfaces. It is required on steel, insulation, and cover board substrates unless the layer above the BASEGARD SA is attached with a heat-producing method. NOTE: QuickPrime™ Plus LVOC (W563587043) or Single Ply LVOC Primer (W56358711) may be used if necessitated by VOC regulations.
2. Position the roll of BASEGARD SA Base Sheet.
3. Fold back one half (length-wise) of BASEGARD SA Base Sheet and peel off one side of the release film. Apply to the substrate at an angle to ensure a smooth application. Repeat with other side.
4. BASEGARD SA Base Sheet must be installed with 3" (76 mm) side laps and 6" (152 mm) end laps.
5. Elevate recommends that a design professional be consulted regarding the need for a vapor retarder.
6. BASEGARD SA may not be used as a temporary roof. Phasing of BASEGARD SA is unacceptable.

## Acceptable Immediate Substrates for Self-Adhered Application

- Structural Concrete (must be clean, dry, properly cured, and primed with SA primer).
- Steel Deck (must be clean, dry, and free of oils. SA Primer is required unless the subsequent layer is attached with a heat-producing method, e.g., hot asphalt, torch, or heat-producing two-part adhesive).
- Existing Smooth Surface BUR or SBS/APP Modified Bitumen (must be clean, smooth, and primed with SA primer).
- DensDeck® Prime, SECUROCK® Gypsum Fiber, STRUCTODEK® HD (SA Primer is required unless the

## Acceptable Immediate Substrates for Self-Adhered Application Continued

- subsequent layer is attached with a heat-producing method, e.g. hot asphalt, torch, or heat-producing two-part adhesive).
- Elevate ISO 95+ GL / ISOGARD GL, ISOGARD HD Composite or Cover Board, RESISTA / ISOGARD CG (SA Primer is required unless the subsequent layer is attached with a heat-producing method, e.g. hot asphalt, torch, or heat-producing two-part adhesive).

**NOTE:** Please consult the Elevate Asphalt Roofing Systems Guide for Applicators and Designers found on the Elevate website for detailed application information.

## Storage

- All material should be stored out of the weather in a clean, dry area in its original unopened packaging at a minimum of 50 °F (10 °C) and a maximum of 100 °F (38 °C) so that it will be 50 °F (10 °C) or above at the time of application. If stored correctly, the shelf life is one (1) year.
- Do not stack BASEGARD SA Base Sheet more than two (2) pallets high.
- If the material must be stored temporarily on the roof before application, it must be elevated from the roof surface on a pallet, stored on end, and covered from the weather with a light-colored opaque tarp in a neat, safe manner that does not exceed the allowable load limit of the storage area.
- Do not store or stage rolls in direct sunlight.

## Precautions

- For safety information, refer to the Safety Data Sheet (SDS) for BUR Membranes and Flashing.
- Take care when transporting and handling Elevate BUR rolls to avoid punctures and other types of physical damage.
- Isolate waste products, petroleum products, grease, oil (mineral and vegetable) and animal fats from all Elevate BUR membranes.

## LEED® Information

Post-Consumer Recycled Content: 0%  
 Post Industrial Recycled Content: 0%  
 Manufacturing Location: Beech Grove, IN

**NOTE:** LEED® is a registered trademark of the U.S. Green Building Council



| Product Data      |   |
|-------------------|---|
| Property          | Value                                       |
| Roll Width        | 3' 3" (1 m)                                 |
| Roll Length       | 65' 4" (19.9 m)                             |
| Net Coverage      | 198 ft <sup>2</sup> (18.39 m <sup>2</sup> ) |
| Roll Weight       | 87 lb (39 kg)                               |
| Pallet Size       | 48" x 39" (1.2 m x 1m)                      |
| Rolls per Pallet  | 20  |
| Weight per Pallet | 1,740 lb (789 kg)                           |

| Typical Properties                 |                               |                               |
|------------------------------------|-------------------------------|-------------------------------|
| Property                           | ASTM Standard Required Value  | Elevate Typical Performance   |
| Product Thickness                  | 40 mil (1 mm)                 | 70-mil (1.8 mm)               |
| Bottom Side Coating                | N/A                           | 20-mil (0.5 mm)               |
| Maximum Load                       | 25 lbf/in (4.4 kN/m)          | 25 lbf/in (4.4 kN/m)          |
| Elongation at Break, Bitumen       | 10%                           | 10%                           |
| Adhesion to Plywood (40 °F, 4 °C)  | 2 lbf/ft width (2.98 kgf/m)   | 2 lbf/ft width (2.98 kgf/m)   |
| Adhesion to Plywood (75 °F, 24 °C) | 12 lbf/ft width (17.86 kgf/m) | 12 lbf/ft width (17.86 kgf/m) |
| Thermal Stability, max             | 0.1 in (3 mm)                 | 0.0 in (0 mm)                 |
| Flexibility Temperature            | -20 °F, (-29 °C)              | -20 °F, (-29 °C)              |
| Tear Resistance                    | 20 lbf (89 N)                 | 20 lbf (89 N)                 |
| Sealability around Nail            | PASS                          | PASS                          |

NOTE: Meets ASTM D 4601. Tested in accordance with D5147.

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.

Firestone, the brand of premier roofing, wall, and lining systems you know and trust, will be coming to you under a new name: Elevate. During our transition, products carrying the brand name **Firestone** will change to **Elevate** on product labels and packaging, Technical Information Sheets, and elsewhere. Only the brand name is changing. Our products remain the same.

For further information on our brand transition to Elevate, scan the code below with your smartphone, or visit our website: [www.holcimelevate.com](http://www.holcimelevate.com)

