

Technical Information Sheet



Protection Mat

Item Description	Item Number
Roll 15' x 320' x 000' (4.6 mm x 97.5 m)	W563589000

Description

Protection Mat is a nominal 4.5 oz/yd² (152.6 g/m²) black synthetic, non-woven, needle-punched, Geotextile fabric. It may be used as a protection mat (under membrane), a crushed stone mat (above membrane), or as a stone protection mat in ballasted systems where allowed by Elevate Specifications and Details.

Method of Application

1. Unroll the Protection Mat overlapping side laps a minimum of 3" (76.2 mm) and end laps a minimum of 6" (152.4 mm). **NOTE:** Wetting the mat or roof membrane will facilitate handling.
2. Extend mat up penetrations and vertical surfaces past the height of gravel a minimum of 2" (50.8 mm).
3. Around penetrations where mat is cut, install an additional piece of mat overlapping a minimum of 6" (152.4 mm).
4. Once mat is positioned, install gravel ballast to protect against mat movement and sunlight.
5. Coordinate installation of the roof system so that the Protection Mat is completely covered by the end of each working day.
6. Additional ballast is necessary as a 10 lb/ft² (48.8 kg/m²) ballast rate will not offer complete coverage of the Protection Mat against U.V. degradation.

Storage

- Store in original unopened containers protected from the weather.
- Do not store near heat, flames, or strong oxidants.
- Store in cool, dry locations away from oxidizing material and UV radiation.

Precautions

- Keep away from flame or ignition source.
- Do not smoke when using.

- Do not cover deck openings, skylights, etc., with mat.
- Keep mat covered to protect from U.V. degradation.

LEED® Information

Post-Consumer Recycled Content: 0%
 Post Industrial Recycled Content: 0%
 Pre-Consumer Recycled Content: 5% by weight
 Manufacturing Location: Athens, GA or Pendergrass, GA

NOTE: LEED® is a registered trademark of the U.S. Green Building Council

Typical Properties	
Properties	Value
Color	Black
Tensile Strength (Grab), minimum	120 lb (54.4 kg), ASTM D-4632
Elongation, minimum	40% min, ASTM D-4632
Trapezoidal Tear, minimum	50 lb (22.7 kg), ASTM D-4533
Burst Strength	335 psi (2310 kPa), ASTM D-3786
Accelerated Weathering	500 hour UV exposure followed by tensile testing: Retain 70% tensile after 500 hours of UV weathering, ASTM D-4355
Permeability, min	0.047 in/second (0.12 cm/second), ASTM D-4491
CBR* Puncture Strength, minimum	310 lb (141 kg), ASTM D-6241
Packaging	
Material Width	15' -0/+1' (4.6 m -0/+0.3 m)
Material Length	320' -0/+2' (97.5 m -0/+0.6 m)
Roll Diameter	20" (508 mm)
Gross Weight	180 lb/roll (81.7 kg/roll)
Area	4,800 ft ² (445.9 m ²)
*CBR = California Bearing Ratio	

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.

Firestone, the brand of premier roofing, wall, and lining systems you know and trust, will be coming to you under a new name: Elevate. During our transition, products carrying the brand name **Firestone** will change to **Elevate** on product labels and packaging, Technical Information Sheets, and elsewhere. Only the brand name is changing. Our products remain the same.

For further information on our brand transition to Elevate, scan the code below with your smartphone, or visit our website: www.holcimelevate.com

