

# Technical Information Sheet



## Low Slope Fire Retardant (LSFR) RubberGard™

Item Description	Item Number
One Roll	Various

### Description

LSFR RubberGard EPDM is a non-reinforced, cured, single-ply roofing membrane that can be used in ballasted, fully adhered and mechanically attached systems.

### Product Preparation

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All roughened surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than ¼" (6 mm) wide shall be properly filled with an acceptable fill material.

Product Packaging				
Membrane Thickness	Widths		Length	Weight
0.045" (1.14 mm)	7.5' (2.3 m)	30' (9.14 m)	100' (30.5 m)	0.29 lb/ft <sup>2</sup> (1.4 kg/m <sup>2</sup> )
	10' (3.05 m)	40' (12.19 m)		
	16.7' (5.09 m)	50' (15.24 m)		
	20' (6.10 m)			
0.060" (1.52 mm)	7.5' (2.3 m)	30' (9.14 m)	100' (30.5 m)	0.39 lb/ft <sup>2</sup> (1.5 kg/m <sup>2</sup> )
	10' (3.05 m)	40' (12.19 m)		
	16.7' (5.09 m)	50' (15.24 m)		
	20' (6.10 m)			

## Method of Application

RubberGard Non-Reinforced LSFR EPDM Membrane must be installed in accordance with current RubberGard specifications, details, and workmanship requirements.

## Storage

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

## Precautions

- Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
- Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane.
- Refer to Safety Data Sheets (SDS) for safety information.

## LEED® Information

Post-Consumer Recycled Content: 0%  
Post Industrial Recycled Content: 0%  
Manufacturing Location: Prescott, AR

NOTE: LEED® is a registered trademark of the U.S. Green Building Council



<b>Typical Properties (Meets or exceeds ASTM D 4637, Type I)</b>			
Physical Test	ASTM Min. Value	Typ. Value 45 mil	Typ. Value 60 mil
Thickness (D412)	45 mil: 1.143 mm +0.178 mm/-0.127 mm (0.045" +0.007"/-0.005") 60 mil: 1.52 mm +0.229 mm/-0.152 mm (0.060" +0.009"/-0.006")	1.092 mm (0.043")	1.37 mm (0.054")
Tensile Strength (D412, Die C)	9.0 MPa (1305 psi) Minimum	11 MPa (1600 psi)	11 MPa (1600 psi)
Dynamic Puncture Resistance @ 5J (D5635)	Pass	Pass	Pass
Static Puncture Resistance @ 20 kg (D5602)	Pass	Pass	Pass
Elongation, Ultimate % (D412, Die C)	300% Minimum	445%	480%
Tensile set (D412, Method A, Die C)	10% Maximum	0%	Pass
Tear Resistance (D624, Die C)	26.27 kN/m (150 lbf/in) Minimum	29.60 kN/m (169 lbf/in)	29.25 kN/m (167 lbf/in)
Brittleness point (D2137)	-45 °C (-49 °F) Maximum	-45 °C (-49 °F)	Pass
Ozone resistance, no cracks D1149)	Pass	Pass	Pass
Tensile Strength after Heat Aging*	8.3 MPa (1205 psi) Minimum	9.48 MPa (1365 psi)	Pass
Elongation, Ultimate after Heat Aging*	200% Minimum	306%	Pass
Tear Resistance after Heat Aging*	21.9 kN/m 125 lbf/in Minimum	33.1 kN/m (189 lbf/in)	Pass
Linear Dimensional Change after Heat Aging*	± 1%	-1%	Pass
Water Absorption by Mass (D471)	+8%/-2%	+1%	Pass
Visual Inspection after Xenon-Arc Weather Resistance Exposure**	Pass	Pass	Pass
PRFSE, Minimum % after Xenon-Arc Weather Resistance Exposure**	30% Minimum	75%	Pass
Elongation, Ultimate, Minimum % after Xenon-Arc Weather Resistance**	200% Minimum	340%	Pass
* Heat age EPDM membrane for: 166 ± 1.66 hours at 240 ± 4°F (116 ± 2°C), followed by specified physical testing. ** Weather Resistance shall be Practices G151 and G155 Xenon-Arc as follows:			
Filter Type:	Daylight		
Irradiance:	0.35 to 0.70 W/(m <sup>2</sup> ·nm) @ 340 nm [42 to 84 W/(m <sup>2</sup> ·nm) @ 300 to 400 nm]		
Cycle:	690 minutes ± 15 minutes light, 30 minutes light plus water spray		
Un-insulated Black Panel Temp:	176° ± 4°F (80° ± 2°C)		
Relative Humidity:	50% ± 5%		
Spray Water:	De-ionized		
Specimen Rotation:	Every 315 KJ/(m <sup>2</sup> ·nm) @ 340 nm [37.8 MJ/(m <sup>2</sup> ·nm) @ 300 to 400 nm]		
Exposure:	10,080 KJ/(m <sup>2</sup> ·nm) @ 340 nm [1209.6 MJ/(m <sup>2</sup> ·nm) @ 300 to 400 nm]		

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.