

Technical Information Sheet



SKYSCAPE™ ROOT BARRIER TAPE

Item Description	Item Number
Root Barrier Tape	custom

DESCRIPTION

SkyScape Root Barrier Tape is self-adhering, waterproof tape which utilizes acrylic pressure sensitive adhesive, and is designed for sealing SkyScape Root Barrier seams, side laps, and end laps. The tape has significant temperature tolerance and can adhere to slightly damp surfaces.

METHOD OF APPLICATION

1. Center the tape carefully over the top of the seam or lap to be sealed.
2. Smooth the tape using hand pressure, ensuring that the tape is fully adhered.

STORAGE

- Deliver and store products in original packaging with Manufacturer's labels and materials list intact and signed off.
- Store Products in designated weather protected areas, elevated from ground, and protected from environmental damage.

SHELF LIFE

Indefinite

COVERAGE RATE

75' (22.9 M) PER ROLL

CLEAN-UP

- Gather and dispose all debris upon completion of work of this section.
- Clean all surfaces and inspect final assembly for approval.

LEED® INFORMATION

Post-consumer recycled content: 0%
 Post-industrial recycled content: 0%
 Manufacturing location: Murfreesboro, TN
 NOTE: LEED® is a registered trademark of the U.S. Green Building Council

TYPICAL PROPERTIES		
Property	Value	ASTM
Dimensions	4" x 75' (102 mm x 22.9 m)	---
Adhesion Properties	Polyethylene/ Propylene: 60 oz/in width (67 g/mm) Anodized Aluminum: After 7 days at 176 °F (80 °C): 70 oz/in width (78 g/mm) After 7 days in water: 65 oz/in width (73 g/mm) After Thermal Cycling: 75 oz/in width (84 g/mm) After UV Exposure: 60 oz/in width (67 g/mm)	ASTM D 3330
Permeability -Desiccant Method	0.17 perm	ASTM E-96
Nail Seal Ability as Modified per AAMA 711-07 Annex 1	Initial: Pass After Thermal Cycling: Pass	ASTM E 331
Tape Thickness	9.9 mil (0.25 mm)	---
Service Temperature Range (tested per AAMA 711-05)	40 °F to 176 °F (-40 °C to 80 °C)	---

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Amrize takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Amrize nor its representatives practice architecture. Amrize offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Amrize accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Amrize representative is authorized to vary this disclaimer.