


Technical Information Sheet



UltraPly™ TPO Platinum Membrane

Item Description	Item Number
1 Roll	Various
Meets or exceeds ASTM D 6878	

Description

Elevate UltraPly TPO Platinum membrane is a flexible, 0.080" (2.03 mm) thick, Thermoplastic Polyolefin (TPO) roofing membrane, reinforced with polyester, weft-inserted scrim. This heat weldable TPO Platinum membrane is available in 0.080" (2.0 mm) thickness and widths up to 12'4" (3.8 m). Elevate Platinum TPO is available in white, tan and gray. This reflective membrane is suitable for a variety of low-slope applications.

Method of Application

- 1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
- 2. All rough surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
- 3. All surface voids greater than 1/4" (6.4 mm) wide shall be properly filled with an acceptable fill material.
- 4. Elevate UltraPly TPO Platinum membrane is installed as continuous roofing or waterproofing layer on the roof. Rolls are overlapped (side laps and end laps) prior to the heat welding of the seam areas.
- 5. Install UltraPly TPO Platinum Roofing System in accordance with current Elevate UltraPly TPO Platinum membrane specifications, details, and workmanship requirements.

Storage

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.





Precautions

- Refer to Safety Data Sheets (SDS) for safety information.
- Exercise caution when lifting, moving, transporting, storing, or handling membrane rolls to avoid sources of punctures and possible physical damage.
- Contact a Regional Technical Coordinator at 1-800-428-4511 for specific recommendations regarding chemical or waste product compatibility with Elevate UltraPly TPO Platinum Membrane.

LEED® Information

Post-Consumer Recycled Content: 0%

Post Industrial Recycled Content: 15%

Manufacturing Location: Wellford, SC or Tuscumbia, AL NOTE: LEED[®] is a registered trademark of the U.S. Green Building Council



Typical Properties (Meets or Exceeds ASTM D 6878 Specification)

ASTM Standard				
	Performance Minimum	Typical Performance 80 mi		
D 751	0.039" (1.0 mm)	0.080" (2.03 mm) ± 10%		
D 7635	0.015" (0.381 mm)	0.033" (0.84 mm)		
D 751, Grab Method	220 lbf (979 N)	460 lbf (2,046 N)		
D 751, Grab Method	15%	25%		
D 751	55 lbf (245 N)	120 lbf (534 N)		
D 2137	-40 °F (-40 °C)	Pass		
D 1149	Pass	Pass		
Properties After Heat Aging (Retained Values) ASTM D 573-5376 h (224 days or 32 weeks) at 240 °F (116 °C)				
D 751, Grab Method	90% Minimum	> 90%		
D 751, Grab Method	90% Minimum	> 90%		
D 751	60% Minimum	> 60%		
	± 1% Maximum	< 1%		
D 1204, 6 h at 158 °F (70 °C)	± 1% Maximum	< 1%		
D 471	± 3% Maximum	< 3%		
G 155	> 60,000 kJ/m ²	> 60,000 kJ/m ²		
176 °F (80 °C) Black Panel, no cracking, crazing when wrapped around a 3" (76.2 mm) mandrel and inspected at 7X magnification				
FTM 101C, Method 2031		450 lbf (2,002 N)		
D 5635		Pass (60 J)		
	D 7635 D 751, Grab Method D 751, Grab Method D 751 D 2137 D 2137 D 1149 d Values) ASTM D 573-5376 D 751, Grab Method D 751, Grab Method D 751, Grab Method D 751 G 155 Calified of the state of the stat	D 7635 0.015" (0.381 mm) D 751, Grab Method 220 lbf (979 N) D 751, Grab Method 15% D 751, Grab Method 15% D 751 55 lbf (245 N) D 2137 -40 °F (-40 °C) D 1149 Pass d Values) ASTM D 573-5376 h (224 days or 32 weeks) at D 751, Grab Method 90% Minimum G 155 60,000 kJ/m2 at 158 °F (70 °C) ± 1% Maximum G 155 > 60,000 kJ/m2 at 200 method 30 method		

September 29, 2022

Sales: (800) 428-4442 | Technical (800) 428-4511





Typical Properties (Continued)			
Dynamic Puncture Resistance CD	D 5635		Pass (60 J)
Static Puncture Resistance	D 5602		Pass (25 kg)
Air Permeance (Material)	E 2178	< 0.004 ft ³ /ft ² (L/(s·m ²))	Pass

1. The ASTM 2178 values listed above are for the air permeance of the UltraPly TPO Membrane component only.

2. When system design includes an air barrier, please consult a Regional Technical Coordinator for additional roof system securement enhancements.

3. Consult the Designer / Architect, Code Agency or Authority having Jurisdiction (AHJ) for requirements regarding the selection and use of an appropriate air barrier material, and its installation into the building envelope.

Radiative Properties

White	Tan	Light Tan* (HR)	Gray
0.79 / 0.69	0.61 / 0.55	0.79 / 0.63**	0.34 / 0.34
0.85 / 0.83	0.81/0.84	0.90 / 0.90**	0.89 / 0.88
98/83	71 / 63	90 / 77**	37 / 36
0008	0015	TBD	0032
0608	0608	TBD	0608
Production Line	Production Line	Production Line	Production Line
White	Tan	Light Tan* (HR)	Gray
Pass (98)			
Pass (83)			
	0.79 / 0.69 0.85 / 0.83 98 / 83 0008 0608 Production Line White Pass (98)	0.79 / 0.69 0.61 / 0.55 0.85 / 0.83 0.81 / 0.84 98 / 83 71 / 63 0008 0015 0608 0608 Production Line Production Line White Tan Pass (98)	0.79 / 0.69 0.61 / 0.55 0.79 / 0.63** 0.85 / 0.83 0.81 / 0.84 0.90 / 0.90** 98 / 83 71 / 63 90 / 77** 0008 0015 TBD 0608 0608 TBD Production Line Production Line Production Line White Tan Light Tan* (HR) Pass (98)

*Light Tan data determined by testing conducted by PRI Construction Materials Technologies LLC

**Rapid Ratings Results

Product Sizes	
Membrane Thickness: 0.080" (2.03 mm)	Membrane Weight: 0.38 lb/ft² (1.9 kg/m²)
Available Sizes	Available Colors
5' x 100' (1.5 m x 30.5 m)	White, Tan, Gray
6' 2" x 100' (1.9 m x 30.5 m)	White
8' x 100' (2.4 m x 30.5 m)	White, Tan, Gray
10' x 100' (3.0 m x 30.5 m)	White, Tan, Gray
12'4" x 100' (3.8 m x 30.5 m)	White

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.

September 29, 2022

Sales: (800) 428-4442 | Technical (800) 428-4511



Firestone, the brand of premier roofing, wall, and lining systems you know and trust, will be coming to you under a new name: Elevate. During our transition, products carrying the brand name **Firestone** will change to **Elevate** on product labels and packaging, Technical Information Sheets, and elsewhere. Only the brand name is changing. Our products remain the same.

For further information on our brand transition to Elevate, scan the code below with your smartphone, or visit our website: www.holcimelevate.com

