



EPOXY ADHESIVE LV

Low-Viscosity Epoxy Adhesive

PRODUCT DESCRIPTION

Five Star® Epoxy Adhesive LV is a two component, 100% solids, moisture insensitive structural epoxy adhesive used in filling cracks and voids up to 1/4 inch (6 mm). Five Star Epoxy Adhesive LV is a low-viscosity epoxy system that can be pressure injected or gravity fed. When mixed with a dried sand, it may also be used as an epoxy patching mortar. Five Star Epoxy Adhesive LV meets ASTM C 881 Types I, II, IV and V, Grade 1, Classes B & C.

ADVANTAGES

- Low viscosity ensures deep penetration
- Moisture insensitive
- High modulus structural adhesive
- High strength
- Excellent adhesion to masonry, concrete, wood, steel and most structural material
- Meets USDA specification for use in food processing areas

USES

- Gravity feed cracks or voids in horizontal concrete and masonry
- Pressure injection of cracks in structural concrete, masonry, wood and other substrates up to 1/4 inch (6 mm) wide
- Sealing tunnels, cable vaults, tanks and basements
- Seal interior slabs and exterior above grade slabs from water and chlorides
- Gravity feed or pressure inject as void filler under equipment
- Binder for epoxy patching mortar of interior horizontal surfaces

PACKAGING AND YIELD

Five Star Epoxy Adhesive LV is available in a one-gallon (3.7 liter) unit yielding approximately 231 cubic inches of material.

SHELF LIFE

Two years in original unopened packaging when stored in dry conditions at 45°F - 90°F (5°C - 35°C). High relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)

Color	Clear / Amber
Viscosity, ASTM D 2393	300 cps
Flexural Strength, ASTM D 790	9,600 psi (62.2 MPa)
Bond Strength, ASTM C 882	
2 Day Cure	2,400 psi (16.6 MPa)
14 Day Cure	3,600 psi (24.8 MPa)
Shrinkage, ASTM D 2566	0.21%
Shear Strength, ASTM D 732	9,000 psi (62.1 MPa)
Heat Deflection Temperature, ASTM D 648	122°F (50°C)
Compressive Properties, ASTM D 695	7 Day
Compressive Strength	11,000 psi (75.8 MPa)
Compressive Modulus	2.20 x 10 ⁵ psi (1,500 MPa)
Tensile Properties, ASTM D 638	
Tensile Strength	7,000 psi (48.3 MPa)
Percent Elongation at Break	2.9
Gel Time, ASTM C 881	30-35 minutes

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

PLACEMENT GUIDELINES

- SURFACE PREPARATION:** Surface must be clean and sound. For best results surfaces should be dry. Remove dust, laitance, grease, curing compounds, impregnations and waxes. Concrete may be sandblasted or prepared by other approved mechanical means. Steel should be sandblasted to an SSPC-SP6 commercial finish. Blow out all surfaces with oil-free compressed air.
- MIXING:** Five Star® Epoxy Adhesive LV should be preconditioned to between 65°F and 85°F (18°C and 29°C) before using. Pre-mix each component thoroughly. Place two parts by volume of Component A and one part by volume of Component B into a clean pail. Mix thoroughly for three minutes with a low speed drill (400 to 600 rpm). Do not mix more material than can be placed in 30 minutes at 70°F (21°C).

To prepare an epoxy mortar, slowly add four to five parts by loose volume oven-dried aggregate to one part of the mixed Five Star Epoxy Adhesive LV and mix until aggregate is uniformly wetted.

- METHODS OF PLACEMENT:**

Gravity Fill: Pour over V-notched cracks on horizontal surfaces. Continue placement until cracks are completely filled. Prior to filling, seal underside of cracks with appropriate epoxy gel where required.

Pressure Injection: Use automated equipment. Set appropriate injection ports. Seal ports and cracks with appropriate epoxy gel. When the epoxy adhesive seal has cured, inject Five Star Epoxy Adhesive LV with steady pressure until crack is filled.

For an Epoxy Mortar: Prime prepared surface with neat Five Star Epoxy Adhesive LV. Place prepared epoxy mortar before primer becomes tack-free. Place epoxy mortar using trowel. Compact and level with steel trowel. Finish as necessary.

- CLEAN UP:** Use an appropriate solvent to clean uncured material. Cured material can only be removed mechanically.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Five Star Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CONSIDERATIONS

- Minimum application temperature of substrate is 40°F (4°C) and rising. Low temperatures adversely affect flowability and strength gain.
- Cold temperatures lengthen gel time; hot temperatures decrease gel time.
- Do not thin with solvents.
- Do not inject moving or leaking cracks.
- Minimum age of concrete must be 21 to 28 days, depending on curing and drying conditions prior to application.
- For cracks over 1/4 inch (6 mm), call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.
- Material is a vapor barrier after cure.

CAUTION

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

SKU/PRODUCT CODE	DESCRIPTION	# UNITS/PALLET	UNIT SIZE
30811	Five Star® Epoxy Adhesive LV	60	Resin (A): 6.2 lbs. (2.8 kg) Hardener (B): 2.7 lbs. (1.2 kg) 1 gallon

EXCLUSIVE WARRANTY; DISCLAIMER OF LIABILITY: FIVE STAR MARINE, INC. (FSM) WARRANTS THAT FSM PRODUCTS ARE MANUFACTURED TO (i) BE FREE OF MANUFACTURING DEFECTS AND (ii) MEET FSM'S CURRENTLY PUBLISHED SPECIFICATIONS FOR PHYSICAL PROPERTIES, PROVIDED THAT THE FSM PRODUCTS ARE APPLIED IN ACCORDANCE WITH FSM'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM INTERNATIONAL AND FSM STANDARDS. IN THE EVENT THAT A FSM PRODUCT FAILS TO SATISFY THE FOREGOING WARRANTY, FSM WILL REPLACE THE DEFECTIVE FSM PRODUCT, PROVIDED, HOWEVER, PRIOR TO PROVIDING SUCH REPLACEMENT, FSM MAY REQUIRE THE RETURN TO FSM OF ANY UNUSED, DEFECTIVE OR ALLEGEDLY DEFECTIVE FSM PRODUCT, FREIGHT PREPAID, AND FSM SHALL HAVE THE RIGHT TO INSPECT ANY PROJECT IN WHICH ALLEGEDLY DEFECTIVE FSM PRODUCT HAS BEEN APPLIED AND TO INTERVIEW PERSONNEL AND REVIEW ASSOCIATED RECORDS RELATING TO THE USE OR APPLICATION OF ALLEGEDLY DEFECTIVE FSM PRODUCTS. EXCEPT AS SET FORTH ABOVE, WITH REGARDS TO THE FSM PRODUCTS, FSM MAKES NO REPRESENTATIONS OR WARRANTIES OF ANY NATURE WHATSOEVER, EITHER EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT. FOR THE AVOIDANCE OF DOUBT, THE FOREGOING IS INTENDED AS A SOLE AND EXCLUSIVE REMEDY FOR ANY FSM PRODUCT DEFECT, AND FSM SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT ARISING FROM THE USE OF FSM PRODUCTS, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, AND WHETHER RESULTING FROM CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY (WHETHER EXPRESS OR IMPLIED) OR FROM ANY OTHER CAUSE WHATSOEVER. WITHOUT LIMITING THE FOREGOING, FSM SHALL NOT BE LIABLE IN THE EVENT THAT THE USE OF FSM PRODUCTS INFRINGES ANY PATENT OR OTHER INTELLECTUAL PROPERTY OR PROPRIETARY RIGHT OF ANY THIRD PARTY.

Five Star Products, Inc.
Corporate Headquarters
2 Enterprise Drive, Suite 303
Shelton, CT 06484 USA
Tel: +1 203-336-7900 • Fax: +1 203-336-7930
FiveStarProducts.com

Specifications Subject to Change.

For most current version of datasheet, go to FiveStarProducts.com © 2022 Five Star Products, Inc. | 10-04-2022
na12767eng Rev. E | American Owned & Operated

