



# EPOXY NOVOLAC COATING NON-SAG

Highly Chemical Resistant Epoxy Coating

Vertical Applications

## PRODUCT DESCRIPTION

Five Star® Epoxy Novolac Coating Non-Sag is a two component, 100% solids, highly chemical resistant epoxy coating for vertical applications which is highly effective on both steel and concrete.

## ADVANTAGES

- High chemical resistance
- Resistant to chipping or cracking
- USES
- Vertical applications
- Secondary containment surfaces
- Low permeability
- Low odor
- Coatings for concrete tanks
- Concrete and steel surfaces

## PACKAGING AND YIELD

Five Star® Epoxy Novolac Coating Non-Sag is a two component system consisting of premeasured containers of resin and hardener and is available as a 2.5 gallon unit yielding coverage of approximately 200 sq. feet at 20 mil thickness.

## SHELF LIFE

Two years in original unopened packaging when stored at normal ambient temperatures.

TYPICAL PROPERTIES AT 70°F (21°C)	
Color	Concrete Gray
Film Thickness	20 mils
Pot Life at 70°F (21°C)	20 minutes
Hardness, ASTM D 2240 Shore D	75
Tensile Strength, ASTM D 638	7,200 psi (49.6 MPa)
Compressive Strength, ASTM D 695	
7 Days	10,000 psi (70.0 MPa)
In-Service Time, (allow 3-5 days for maximum cure)	72 hours

Chemical Resistance Chart* at 70°F (21°C)		
Solvents	Organics Acids (Conc.)	Bases / Alkalines (Conc.)
Acetaldehyde	Acetic (1-50%)	Ammonia (1-25%)
Acetone	Acid plating solutions	Ammonium Hydroxide (1-25%)
Acetonitrile	Adipic (1-25%)	Aniline
Acrylonitrile	Azotic (1-50%)	Barium Hydroxide (1-sat.)
Butyl acetate	Battery (1-98%)	Black Pulp Liquor
Cyclohexane	Chromic (1-30%)	Butyl Amine
Ethanol	Chlorohydric (1-37%)	Cadmium Cyanide Plating
Ethyl acetate	Dibasic (1-sat.)	Calcium Hydroxide (1-25%)
Ethyl alcohol	Ethanoic (1-50%)	Chromium Trioxide (1-25%)
Formaldehyde	Ethylic (1-50%)	Copper Cyanide Plating
Isopropyl Alcohol	Engravers (1-50%)	Dimethyl Aniline
Jet Fuel	Hydrochloric (1-37%)	Hydrogen Peroxide (1-30%)
Kerosene	Hydrofluoric (1-40%)	Green Pulp Liquor
Methyl Ethyl Ketone	Mattling (1-98%)	Soap solutions
Methanol	Nitric (1-50%)	Sodium Cyanide (1-15%)
Methyl Alcohol	Oil of vitriol (1-98%)	Sodium Hypochlorite (1-9%)
Rubbing Alcohol	Oleic	Sodium Hydroxide (1-50%)
Wood Alcohol	Phosphoric (1-85%)	Triethanolamine
1,1,1 Trichloroethane	Sulfuric (1-98%)	Triethylamine
Phenol	Vitriol (1-98%)	Potassium Hydroxide (1-sat)

\* NOTE: Many factors effect chemical resistance. Application design, service and exposure temperatures, and the type and amount of impurities in the chemical or in the environment are some important considerations. These test results are reported to serve as a guide to the applicability of the Novolac systems.

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

## PLACEMENT GUIDELINES

1. **SURFACE PREPARATION:** Surfaces should be clean and sound. Remove dust, laitance, grease, curing compounds, impregnations and waxes. Concrete should be sandblasted or prepared by other acceptable mechanical means. Steel should be sandblasted to an SSPC-SP6 commercial finish.
2. **MIXING:** For optimum performance, all components should be conditioned to between 65°F and 85°F (18°C and 29°C). Premix both Component A (resin) and Component B (hardener) thoroughly before mixing. Place all of Component A and Component B into a suitable container. Component A and Component B are mixed in a 1.5:1.0 ratio by volume. Mix Component A and Component B with a slow speed mixer for no more than 3 minutes. Avoid air entrapment. Place mixed material immediately. Mix only that amount of material that can be placed within 20 minutes.
3. **METHODS OF PLACEMENT:** Five Star® Epoxy Novolac Coating Non-Sag may be applied using a squeegee, roller or brush. Apply material in even coats.
4. **POST PLACEMENT PROCEDURES:** In-service operation may begin after a 72 hour cure time.
5. **CLEAN UP:** Tools with fresh material may be cleaned with MEK, Xylene or a solution of water and strong detergent.

*NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Five Star® Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.*

## CONSIDERATIONS

- Minimum application temperature of substrate is 40°F (4°C) and rising. Low temperatures adversely affect flowability and strength gain.
- Do not thin with solvents.
- Minimum age of concrete must be 21 to 28 days, depending on curing and drying conditions prior to application. Use Five Star® Waterborne Primer in conjunction with Five Star® Epoxy Novolac Coating Non-Sag for concrete that is 3 - 5 days old.
- Cold temperatures lengthen cure time, hot temperatures decrease cure time.
- Maximum operating temperature is 200°F (93°C).

## CAUTION

FOR INDUSTRIAL USE ONLY. Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. PRIOR TO USE, REFER TO SAFETY DATA SHEET.

*For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.*

SKU/PRODUCT CODE	DESCRIPTION	#UNITS/PALLET	UNIT SIZE
34001	Five Star® Epoxy Novolac Coating Non-Sag (Grey)	48	Resin (A): 14.2 lbs. (6.44 kg.) pail Hardener (B): 9.1 lbs. (4.1 kg.) pail

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Specifications Subject to Change.

For most current version of datasheet, go to [FiveStarProducts.com](http://FiveStarProducts.com)

**Five Star Products, Inc.**  
**Corporate Headquarters**  
60 Parrott Drive  
Shelton, CT 06484 USA  
Tel: +1 203-336-7900 • Fax: +1 203-336-7930  
[FiveStarProducts.com](http://FiveStarProducts.com)



© 2018 Five Star Products | 07-18-2018  
12770 Rev. B | American Owned & Operated

