



# **FLUID GROUT 100**

High Performance Precision Non-Shrink Fluid Grout

## **PRODUCT DESCRIPTION**

**Five Star® Fluid Grout 100** is the industry's leading cement-based, nonmetallic, non-shrink, sulfate resistant fluid grout for supporting machinery and equipment. It is formulated with Air Release technology that combines high performance with the greatest reliability. When tested in accordance with ASTM C827, Five Star® Fluid Grout 100 exhibits positive expansion. Five Star® Fluid Grout 100 meets the performance requirements of ASTM C1107-02 Grades A, B and C, ASTM C1107/C1107M-20 and CRD-C 621-93 specifications for non-shrink grout over a wide temperature range, 40°F - 95°F (4°C - 35°C).

## **ADVANTAGES**

- Air release technology per ACI 351.1 R
- Placement within tight clearances down to 1/2 inch (12 mm)
- High 1, 7, 28 day strength
- Sulfate resistant
- Does not contain gas generating additives, such as aluminum powder
- Non-shrink from the time of placement
- 95% Effective Bearing Area (EBA) is typically achieved following proper grouting procedures

## **USES**

- Grouting clearances to 1/2 inch (12 mm)
- Grouting of anchors and dowels
- Grouting of machinery and equipment to maintain precision alignment
- Non-shrink grouting of structural steel and precast concrete
- Preplaced aggregate grouting
- Support of tanks and vessels

## **PACKAGING AND YIELD**

Five Star® Fluid Grout 100 is packaged in heavy-duty, polyethylene lined bags and is available in 55 lb. (25 kg) units yielding approximately 0.50 cubic feet (14.1 liters) of hardened material at maximum water content.

## **SHELF LIFE**

One year in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

### **TYPICAL PROPERTIES AT 70°F (21°C)**

|   |   |                      |
|---|---|----------------------|
| <b>Early Height Change</b> , ASTM C827  | 0.0 to 4.0%                             |                      |
| <b>Hardened Height Change</b> , ASTM C1090  | 0.00 to 0.30%                           |                      |
| <b>Effective Bearing Area</b>   | 95%                                     |                      |
| <b>Bond Strength</b> , ASTM C882  | 2,000 psi (13.8 MPa)/28 days            |                      |
| <b>Freeze Thaw Resistance</b> , ASTM C666A, 300 Cycles  | > 95% RDM                               |                      |
| <b>Sulfate Resistance</b> Wet Expansion at 1 year, ASTM C1157, 1x1x11" bars cured as per ASTM C157, conditioned as per ASTM C1012 | ≤ 0.1%                                  |                      |
| <b>Flow</b> , ASTM C1437/C1107, 5 drops/3 seconds   | Plastic Consistency; 100% - 125%        |                      |
| <b>Flow</b> , ASTM C939   | Fluid Consistency; 20 to 30 second flow |                      |
| <b>Compressive Strength</b> , ASTM C942 (C109 Restrained)   | Plastic Consistency                     | Fluid Consistency    |
| 1 Day   | 5,800 psi (40 MPa)                      | 3,500 psi (24.2 MPa) |
| 3 Days  | 7,500 psi (51.8 MPa)                    | 6,000 psi (41.4 MPa) |
| 7 Days  | 8,000 psi (55.2 MPa)                    | 6,500 psi (44.9 MPa) |
| 28 Days   | 10,000 psi (69.0 MPa)                   | 8,000 psi (55.2 MPa) |
| <b>Working Time</b> at 70°F (21°C)  | 30 minutes                              |                      |

*The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.*

## APPLICATION INFORMATION

|                                       |  |                                |  |
|---------------------------------------|--|--------------------------------|--|
| <b>Mixing Ratio</b>                   | 4½ to 5½ qts (4.25 - 5.25 L) potable water per 55 lb. (25 kg) bag; 5½ qts (5.25 L) for fluid consistency | <b>Minimum Plate Clearance</b> | ½ in (12 mm)   |
| <b>Maximum In-Service Temperature</b> | 400°F (204°C)  | <b>Placement Depth</b>         | ½ in - 6 in (12 mm - 150 mm)<br>> 6 in (150 mm), contact Five Star |

## PLACEMENT GUIDELINES

For optimum performance, install at temperatures between 40°F and 95°F (4°C and 35°C). Maintain grout and substrate above 40°F (4°C) until grout reaches 1,000 psi (6.9 MPa) compressive strength. Refer to Five Star® Technical Bulletins (TB) 101 and 102 *Cementitious Cold and Hot Weather Grouting* for extreme weather conditions.

- SURFACE PREPARATION:** Construction practices dictate a concrete foundation should achieve its design strength before grouting. All surfaces in contact with Five Star® Grout shall be clean and free of oil, grease, laitance, and other bond-inhibiting contaminants. To maximize bond, concrete surfaces should be prepared by acceptable means to coarse aggregate exposure. A minimum ½ inch (12 mm) peak to valley surface profile is recommended. Presoak concrete surfaces with potable water for a minimum of 8 hours (optimum 24 hours), continuously and consistently, via wet rags, wet burlap, ponding, or similar method to obtain a Saturated Surface Dry (SSD) condition. Any existing cracks shall be brought to the project engineer's attention prior to grout installation. Refer to Five Star® TB103 *Cementitious Grout Concrete Surface Preparation* and TB104 *Cementitious Grout Baseplate Preparation* for further details.
- FORMWORK:** Formwork should be constructed 24-hours prior to the pour. Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight, and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be sufficient to allow for a headbox to be placed between the edge of the baseplate and the form. The clearance for the remaining sides shall be 1 to 2 inches (25 - 50 mm). Formwork and areas where bond is not desired must be treated with form oil, paste wax, or similar material. Isolation/construction joints may be necessary depending on pour dimensions. Refer to Five Star® TB410 *Grout Formwork* for further details.
- MIXING:** Use of a mortar mixer (stationary barrel with moving blades) is required to completely mix the grout. A portable mixer and paddle are acceptable for single bag mixes. Start with approximately 5 quarts (4.7 L) potable water per 55 lb. (25 kg) bag. Add Five Star® Fluid Grout 100 and mix for approximately 3 minutes to a uniform consistency. To achieve desired flow, add additional potable water and mix for an additional 2 minutes. If a fluid consistency is required, typically around 5½ quarts (5.25 L) water (total) are necessary. Do not exceed the maximum recommended amount of potable mixing water as directed. Do not allow the grout to segregate. For pours over 6 inches (150 mm) refer to Five Star® TB105 *Cementitious Grout Aggregate Extension* for further guidelines. Refer to Five Star® TB108 *Cementitious Grout Mixing* for further details. For bulk mixing applications, contact Five Star Products.
- PLACEMENT:** Five Star® Fluid Grout 100 may be poured or pumped into place. Placement should always be across the shortest distance. A headbox is recommended for pouring applications. Finish as necessary. Refer to Five Star® TB412 *Grout Placement* for further details. If field testing of the grout is required, refer to Five Star® TB109 *Cementitious Grouts Proper Compressive Strength Testing*.
- POST-PLACEMENT:** Five Star® Fluid Grout 100 shall be wet cured with potable water for a minimum of 24 hours. After initial 24-hour wet cure, grout shall be coated with an approved curing compound. If a curing compound is not used, grout shall be wet cured for an additional 48 hours totaling 3 days. During the curing process, protect the grout from direct sun and wind exposure. Do not allow grout to freeze until it reaches 1,000 psi (6.9 MPa) compressive strength. In-service operation may begin immediately after the required grout compressive strength has been reached. Refer to Five Star® TB110 *Cementitious Grout Curing* and Five Star® TB413 *Grout Finishing* for further details.
- CLEAN-UP:** All tools and equipment may be cleaned with soap and water before the material hardens.

For additional Five Star® Technical Bulletins, visit [FiveStarProducts.com](http://FiveStarProducts.com). For further questions, or if additional information is required, contact your local Five Star® Technical Sales Representative at 1-800-243-2206.

## CAUTION

Contains cementitious material and crystalline silica. International Agency for Research on Cancer has determined that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

| SKU/PRODUCT CODE | DESCRIPTION     | #UNITS/PALLET | UNIT SIZE          |
|------------------|-----------------|---------------|--------------------|
| 25000            | Fluid Grout 100 | 56            | 55 lb. (25 kg) bag |

**WARRANTY:** "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Specifications Subject to Change.

For most current version of datasheet, go to [FiveStarProducts.com](http://FiveStarProducts.com)

**Five Star Products, Inc.**  
**Corporate Headquarters**  
 2 Enterprise Drive, Suite 303  
 Shelton, CT 06484 USA  
 Tel: +1 203-336-7900 • Fax: +1 203-336-7913  
[FiveStarProducts.com](http://FiveStarProducts.com)



© 2025 Five Star Products, Inc. | 07-30-2025  
 na12515eng Rev. L | American Owned & Operated

