



HIGHWAY PATCH WINTER

Fast Traffic Area Repair for Cold Weather

PRODUCT DESCRIPTION

Five Star® Highway Patch Winter is a one component, fast setting hydraulic cement material ideal for horizontal repairs of concrete in traffic areas for cold weather conditions. Five Star® Highway Patch Winter provides resistance to oil, grease, gasoline, salts and other chemicals found in the transportation environment.

ADVANTAGES

- High early strength
- One component/ease of use
- Open to traffic in three hours
- Freeze/thaw resistance
- Adjustable to working time
- Resistant to salts
- Cold weather installation
- Coarse aggregate extension

USES

- Highways and bridges
- Parking decks and ramps
- Airport runways and taxiways
- Expansion joint rebuild
- Dowel bar retrofit
- Cold weather repairs

PACKAGING AND YIELD

Five Star® Highway Patch Winter is packaged in heavy-duty polyethylene lined bags each weighing 50 lb. (22.7 kg) yielding approximately 0.40 cubic feet (11.3 liters) and approximately 0.60 cubic feet (16.9 liters) with a 70% coarse aggregate extension. Also available in 3,000 lb. (1,363 kg) bulk bags.

SHELF LIFE

One year in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)

| | |
|---|----------------------------|
| Compressive Strength, ASTM C 109 | |
| 3 Hours | 3,000 psi (20.6 MPa) |
| 1 Day | 5,000 psi (34.5 MPa) |
| 7 Days | 7,000 psi (48.3 MPa) |
| Bond Strength, ASTM C 882 | |
| 1 Day | 1,500 psi (10.4 MPa) |
| 7 Days | 2,000 psi (13.8 MPa) |
| Length Change, ASTM C 157 | |
| 28 Days Wet | + 0.03% |
| 28 Days Dry | - 0.05% |
| Freeze/Thaw Resistance, ASTM C 666A | |
| Relative Durability Factor | > 90% |
| Flexural Strength, ASTM C 78 | |
| 3 Hours | 400 psi (2.8 MPa) |
| Chloride Ion Permeability, ASTM C 1202 | |
| 28 Days | Very Low (<1,000 Coulombs) |

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

PLACEMENT GUIDELINES

- SURFACE PREPARATION:** All horizontal and vertical surfaces in contact with Five Star® Highway Patch Winter shall be free of oil, grease, laitance, and other contaminants. All horizontal and vertical concrete surfaces must be clean, sound and rough to ensure a good bond. Remove all oxidation from exposed reinforcing steel. A perimeter edge and minimum depth of one inch (25 mm) should be provided for a durable repair. Featheredging is not desirable. Soak concrete surfaces prior to application with liberal quantities of potable water, leaving the concrete saturated and free of standing water or use Five Star® Bonding Adhesive. Surfaces shall be conditioned to between 35°F and 75°F (2°C and 24°C) at time of placement.
- MIXING:** Mix Five Star® Highway Patch Winter thoroughly for approximately three to five minutes to a uniform consistency with a mortar mixer (stationary barrel with moving blades) or a drill and paddle mixer. Mix Five Star® Highway Patch Winter following water requirements on packaging. Adjust consistency if necessary, but do not exceed maximum water content stated on the package or an amount that will cause segregation. Do not mix more material than can be placed in 10 minutes. Addition of coarse aggregate, meeting ASTM C 33, should be used for pours greater than 2 inches (50 mm) in depth. Always add mixing water first to mixer followed by repair material.
- PLACEMENT PROCEDURES:** When bonding adhesive is not used, firmly work Five Star® Highway Patch Winter into substrate and place full depth from one side of the repair to the other. Where this is not practical, placement must be continuous to prevent cold joints between pours. Finish as necessary.
SPECIAL CONDITIONS: For temperatures above 60°F (16°C) use standard Five Star® Highway Patch. Protect from freezing until a compressive strength of at least 1,000 psi (6.9 MPa) is obtained. Faster strength gain will occur when the Five Star® Highway Patch Winter and mixing water have been conditioned to a higher temperature prior to placement. In warmer temperatures, chilled water or Five Star SummerSet® may be used if necessary to provide more working time.
- POST-PLACEMENT PROCEDURES:** Five Star® Highway Patch Winter shall be protected until initial set, then immediately coat with an approved curing compound meeting the water retention properties of ASTM C 309 or wet cure for a minimum of three days. In-service operation may begin immediately after the required strength has been reached.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Five Star® Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CONSIDERATIONS

- Never exceed the maximum water content as stated on the package or an amount that will cause segregation.
- Temperature of surfaces must be between 35°F and 75°F (2°C and 24°C) at time of placement. For extreme temperatures, call Five Star Products' Engineering and Technical Service Center.
- Repair material shall be protected from freezing until it reaches 1,000 psi (6.9 MPa).
- Placement shall be continuous to avoid cold joints.

CAUTION

Irritant, toxic, strong sensitizer. International Agency for Research on Cancer has determined that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

| SKU / PRODUCT CODE | DESCRIPTION | #UNITS/PALLET | UNIT SIZE |
|--------------------|---------------------------------|---------------|----------------------|
| 40010 | Five Star® Highway Patch Winter | 56 | 50 lb. (22.7 kg) Bag |

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Five Star Products, Inc.
Corporate Headquarters
2 Enterprise Drive, Suite 303
Shelton, CT 06484 USA
Tel: +1 203-336-7900 • Fax: +1 203-336-7930
FiveStarProducts.com

Specifications Subject to Change.

For most current version of datasheet, go to FiveStarProducts.com



© 2022 Five Star Products, Inc. | 10-18-2022
na12946eng Rev. C | American Owned & Operated

