



Material Performance Specification

Five Star® LC Epoxy Grout

- A. Non-shrink epoxy grout shall be 100% solids, pre-packaged system containing thermosetting epoxy resins, expansive additives, and inert fillers.
- B. The manufacturer shall be ISO 9001 certified and have a minimum of 25 years of experience in the manufacture of non-shrink epoxy grouts.
- C. The manufacturer shall provide an experienced technical representative to be present during a pre-grout meeting and during the initial mixing and placement of the materials with sufficient notice (5 working days).
- D. The grout material shall meet all the following typical performance criteria when cured at 70 °F (21 °C) ¹:

1.	Compressive Strength , ASTM C 579B at Load Rate II (0.25 inches per minute)	
	1 Day	13,000 psi (90 MPa)
	7 Days	15,000 psi (103 MPa)
	28 Days	16,000 psi (110 MPa)
	Post-cured at 140 °F (60 °C)	17,000 psi (117 MPa)
2.	Height Change , ASTM C827	Positive expansion
3.	Effective Bearing Area (EBA) , ASTM C1339/1339M-18	95%
4.	Tensile Strength , ASTM C307, 7 Days	2,500 psi (17.2 MPa)
5.	Flexural Strength , ASTM C580	5,500 psi (37.9 MPa)
6.	Bond to Concrete , ASTM C882, 7 Days	3,000 psi (20.7 MPa)
7.	Working Time	30 minutes
8.	Placement Depth	3/8 inches – 3 inches (10 mm – 75 mm)
9.	Application Temperature	55 °F – 95 °F (13 °C – 35 °C)

- E. An acceptable product which meets the above criteria is **Five Star® LC Epoxy Grout** as manufactured by Five Star Products, Inc., Shelton, CT [203-336-7900].
- F. The grout shall be installed in accordance with the grout manufacturer's installation instructions. Any deviations to the grout manufacturer's handling, mixing, and/or installation instructions that are required shall be approved in advance by the project engineer and/or the project manager.

¹ The data shown above reflect typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result in the field. Test methods are modified where applicable.

FIVE STAR® MATERIAL PERFORMANCE SPECIFICATIONS ARE PROVIDED FOR INFORMATIONAL PURPOSES ONLY AND SHOULD BE USED AS GENERAL GUIDELINES FOR CONSIDERATION BY CONTRACTORS AND ENGINEERS. WHILE EVERY REASONABLE EFFORT HAS BEEN MADE TO ENSURE THIS INFORMATION IS ACCURATE AND AUTHORITATIVE, FIVE STAR PRODUCTS DOES NOT WARRANT THE ACCURACY OR COMPLETENESS OF THIS INFORMATION, OR ITS APPROPRIATENESS FOR ANY PARTICULAR PURPOSE. THE USER OF THESE DOCUMENTS REMAINS SOLELY RESPONSIBLE FOR THE SPECIFICATION OF ALL METHODS, MATERIALS AND PRACTICES.

