



# UNDERWATER EPOXY GEL

## Epoxy Gel Adhesive

### PRODUCT DESCRIPTION

Five Star® Underwater Epoxy Gel is a multi-purpose, two component, 100% solids, moisture insensitive structural epoxy adhesive used in filling cracks up to 1/2 inch (13 mm). Ideal for steel, concrete, and masonry applications, Five Star® Underwater Epoxy Gel is a smooth, nonabrasive gel that can be pressure injected or hand applied. Five Star® Underwater Epoxy Gel meets ASTM C 881 Types I, II, IV and V, Grade 3, Classes B & C.

### USES

- Sealing Five Star® PileForm™ F Fiberglass Jacket seams
- Pressure injection of cracks in structural concrete, masonry, wood, and other substrates
- Surface repair of non-moving cracks on new or existing structures
- Anchoring of bolts, dowels, pins and special fasteners
- General purpose gel adhesive
- Re-pointing concrete block and timber drydocks

### BENEFITS

- VOC compliant
- Excellent adhesion to masonry, concrete, wood, steel and most structural materials
- High strength
- Gel consistency ideal for vertical and non-mating surfaces
- Moisture insensitive
- Convenient 1:1 mixing ratio
- Unique nonabrasive texture permits applications with automated pressure-injection equipment

### PACKAGING AND YIELD

Five Star® Underwater Epoxy Gel is available in 2 x one gallon (7.4 liters) pails yielding approximately 460 cubic inches of material or 22 oz. (600 ml) cartridges yielding 37 cu. in. (600 cu. cm).

### SHELF LIFE

Two years in original unopened packaging when stored in dry conditions at 45°F to 90°F (5°C - 35°C).

#### TYPICAL PROPERTIES AT 70°F (21°C)

<b>Color</b>	Gray
<b>Viscosity</b>	Gel
<b>Flexural Strength, ASTM D 790</b>	5,500 psi (38.0 MPa)
<b>Water Absorption, ASTM D 570</b>	0.10%
<b>Bond Strength, ASTM C 882</b>	
2 Day Cure	2,600 psi (17.9 MPa)
14 Day Cure	4,600 psi (31.7 MPa)
<b>Shrinkage, ASTM D 2566</b>	0.0007 in/in (mm/mm)
<b>Shear Strength, ASTM D 732</b>	3,500 psi (24.2 MPa)
<b>Compressive Properties, ASTM D 695</b>	
Compressive Strength	10,000 psi (68.9 MPa)
Compressive Modulus	2.80 x 10 <sup>5</sup> psi (1,930 MPa)
<b>Gel Time, ASTM C 881</b>	35 minutes

*The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.*

## PLACEMENT GUIDELINES

- SURFACE PREPARATION:** Surface must be clean and sound. For best results surfaces should be dry. Remove dust, laitance, grease, curing compounds, impregnations and waxes. Concrete may be sandblasted or prepared by other approved mechanical means. Steel should be sandblasted to an SSPC-SP6 commercial finish.
- MIXING:** Material should be preconditioned to between 70°F and 80°F (21°C and 26°C) before using. **Gallon Pails:** Pre-mix each component thoroughly. Proportion equal parts by volume of Component A and Component B into a clean pail. Mix thoroughly for three minutes with a low speed drill (400-600 rpm) to avoid air entrapment. Do not mix more material than can be placed in 40 minutes at 70°F (21°C).
- METHODS OF PLACEMENT:**

**Pressure Injection:** Use automated equipment. Set appropriate injection ports based on system used. Seal ports and cracks with Five Star® Underwater Epoxy Gel or Five Star® RS Anchor Gel. When the epoxy adhesive seal has cured, inject Five Star® Underwater Epoxy Gel with steady pressure until crack is filled.

**Structural Adhesive:** Apply Five Star® Underwater Epoxy Gel to the mating or non-mating prepared substrates. Work into the substrates for positive adhesion. Secure the bonded unit firmly into place until the adhesion has cured. Glue line should not exceed 1/8 inch (3 mm).

**Anchor bolts, dowels, pins and plates:** Annular space around bolt should not exceed 1/8 inch (3 mm); depth of embedment is typically 10-15 times the bolt diameter. Place material in hole, starting from the rear to avoid air pockets. For best results coat anchor with adhesive, insert and rotate slowly into hole.

**Trowel grade repair mortar:** Five Star® Underwater Epoxy Gel can be used as a trowel grade repair mortar when mixed with 1 to 1.5 parts by volume with oven dried silica sand. Mix Five Star® Underwater Epoxy Gel as directed then add oven dried silica sand. Mix until a uniform consistency is achieved.
- CLEAN UP:** Use an appropriate solvent to clean uncured material. Cured material can only be removed mechanically.

**NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY.** For more detailed placement procedures, refer to Five Star® Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

## CONSIDERATIONS

- Minimum application temperature of substrate is 40°F (4°C) and rising. Precondition components to 70°F-80°F (21°C-26°C) prior to use in cold weather.
- Cold temperatures lengthen gel time, hot temperatures decrease gel time.
- Do not thin with solvents.
- Do not inject moving or leaking cracks
- Minimum age of concrete must be 21 to 28 days, depending on curing and drying conditions prior to application.
- For cracks over 1/2 inch (12 mm), call the Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

## CAUTION

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

SKU / PRODUCT CODE	DESCRIPTION	# UNITS / PALLET	UNIT SIZE
30814	Five Star® Underwater Epoxy Gel (Cartridge)	720 (60 cases)	Resin (A) / Hardener (B): 22 oz. (650 ml) cartridge
32401	Five Star® Underwater Epoxy Gel (2 Gallon)	60	Resin (A): 10.25 lbs. (4.7 kg)

**WARRANTY:** "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Specifications Subject to Change.

For most current version of datasheet, go to [FiveStarProducts.com](http://FiveStarProducts.com)

**Five Star Products, Inc.**  
**Corporate Headquarters**  
60 Parrott Drive  
Shelton, CT 06484 USA  
Tel: +1 203-336-7900 • Fax: +1 203-336-7913  
[FiveStarProducts.com](http://FiveStarProducts.com)

© 2017 Five Star Products, Inc. | 11-10-2017  
12527 Rev. B | American Owned & Operated

