



# LRF

## ADHESIVE O (1 OF 2)

### Description

GAF LRF Adhesive O is a two component, VOC free, low rise, bulk packaged, polyurethane foam adhesive that contains no solvents and sets in minutes.

Application is quick and easy, resulting in significant labor savings for the contractor. LRF Adhesive O is dispensed through the PaceCart, which equally mixes Part A and Part B of the adhesive, thus providing a quality, consistent application each time. GAF LRF Adhesive O is also available as a simple-to-use cartridge with disposable mixing tip for small jobs.

### Basic Use

LRF Adhesive O is designed for use as an adhesive for bonding approved fleece-back roof membranes to a building's structural roof deck, base sheets, insulation boards, and built-up roof surfaces (adhesion test for specific BUR surface must be conducted prior to conducting work). It is dispensed in  $\frac{3}{4}$ " – 1" (19.1 mm – 25.4 mm) wide liquid beads that will quickly spread to a width of 2" to 3" (51 mm – 76 mm). LRF Adhesive O will expand and rise to fill minor surface irregularities.

### Code Approvals



### Approved Substrates

- Polyisocyanurate
- Polystyrene
- Gypsum cover boards
- Asphaltic cover boards
- Concrete
- Pre-existing asphaltic roof surface (Adhesion tests required to determine suitability. Contact your GAF territory manager to arrange testing.)

For additional information, contact your local GAF territory manager or call 1-800-766-3411.

### Advantages

- Replaces fasteners...Minimizes excessive deck penetrations
- Low rise foam...Accommodates minor surface irregularities
- Solvent free...VOC free, low odor

### Storage

Keep temperature of contents between 45°F–95°F (-13.9°C–1.7°C). Bring temperature of material to approximately 70°F (21.1°C) just before use. Do not store in direct sunlight or above 95°F (35°C). Store boxes with valve side up. **Keep from freezing.**

### Surface Preparation

All work surfaces should be clean, dry, and free of dirt, dust, debris, oils, loose and/or embedded gravel, un-adhered coatings, deteriorated membrane, and other contaminants that may result in a surface that is not sound or is uneven.

### Safety

Prior to working with this or any product, always review product label and Safety Data Sheet (SDS) for necessary health and safety precautions.

### Limitations

- Do not apply to wet or damp surfaces.
- Do not apply when ambient air temperature is below 40°F (4.4°C) or surface temperatures exceed 160°F (71.1°C).

### Application

#### 1a. If using boxes:

- A. Extend quick connect spouts in Part A and Part B box packaging.
- B. Invert boxes and place them in the tray on the PaceCart.
- C. When using the PaceCart, connect the fittings to the feed hoses. Operate pump according to manufacturer's instructions.
- D. For other equipment, follow equipment manufacturer's instructions.

#### 1b. If using cartridges:

- A. Open a cartridge and remove the existing black caps.
  - B. Attach a mixing tip to the threaded mixing head.
  - C. Place the cartridge into applicator.
2. Apply LRF Adhesive O directly to the substrate using a ribbon pattern. Space beads as required by job specification, typically 6" or 12" (152 mm or 305 mm) o.c.
  3. GAF LRF Adhesive O should be approximately 70°F (21.1°C) when being dispensed. As adhesive is applied, allow the adhesive to begin rising, then place membrane.
  4. Roll in membrane using a 150lb. (68 kg) membrane roller or equivalent.

Unused material can be applied at a later date. Properly clean dispensing wand and pump unit according to the pump manufacturer's recommendations.

### Suitable Application Equipment Systems

- OMG PaceCart or equivalent

For a complete list of approved low-pressure pump carts, or additional information, contact your local GAF Territory Manager or call 1-800-766-3411.



# LRF

## ADHESIVE O (2 OF 2)

### Coverage

Properly mixed and applied GAF LRF Adhesive O will produce the following approximate coverage rates:

Product Configuration	Standard Coverage rate 6" (152 mm) o.c.	Standard Coverage rate 12" (305 mm) o.c.
Bag In Box (A [5 gal./18.9 L]+ B [5 gal./18.9 L])	<b>9 to 11 squares</b> <b>(84 to 102 m<sup>2</sup>) per set</b>	<b>17 to 20 squares</b> <b>(158 to 186 m<sup>2</sup>) per set</b>
Cartridge (4/box) (1.5 liter per cartridge)	<b>2 to 3 squares</b> <b>(19 to 28 m<sup>2</sup>) per case</b>	<b>4 to 6 squares</b> <b>(37 to 56 m<sup>2</sup>) per case</b>
Product Configuration	Full-Coverage Spray	Bead Application
15-gallon Drum (A [15 gal./58 L]+ B [15 gal./58 L])	<b>1 square per gallon</b> <b>(2 m<sup>2</sup>/L)</b>	<b>Up to 2 squares per gallon</b> <b>(up to 5 m<sup>2</sup>/L)</b>
55-gallon Drum (A [55 gal./208 L]+ B [55 gal./208 L])	<b>1 square per gallon</b> <b>(2 m<sup>2</sup>/L)</b>	<b>Up to 2 squares per gallon</b> <b>(up to 5 m<sup>2</sup>/L)</b>

NOTE: 1 square = 100 square feet. A <sup>3</sup>/<sub>4</sub>" - 1" (19.1 mm - 25.4 mm) wide uncured adhesive bead will produce a 2" - 3" (51 mm - 76 mm) wide cured adhesive bead. Coverage rates may vary when used over irregular surfaces and will vary depending on roughness.