

RUBEROID® ENERGYCAP[™] GAF TOIChGranuleFR Membrane

ITEM CODE: 386B

106.9 ft.² (10.0 m²)

32' 6" (10.0 m)

104 lb. (47.2 kg)

160 mils (3.8 mm)

Coated Granules

2,650 lb.

State of Florida Approved

39.5" (1.0 m)

(1,202.0 kg)

Burn-Off Film

Polyester

25

Product Specifications:

Roll Size'

Roll Length

Roll Width

Roll Weight

Roll Thickness

Rolls per Pallet

Full Pallet Weight

Top Side Surfacing

Bottom Side Surfacing

* Roll size as reported represents actual

membrane dimensions and does not

calculate installation using side and

end lap recommendations.

U

Standard

Reinforcement

FM

APPROVED

ASTM D6222 Type I, Grade G

Description:

RUBEROID® EnergyCap™ Torch Granule FR membrane is an APP modified bitumen membrane with a factory-applied layer of elastomeric coating applied to extra-fine mineral granules. Its core is a strong non-woven polyester mat.

Uses:

This membrane is suitable for new roofing and re-roofing applications where long-term roof system performance is specified.

Advantages:

- Durability its polyester mat core protects against splits and tears due to its pliability and elongation characteristics. Its specially formulated modified asphalt ensures excellent performance.
- Reflectivity RUBEROID[®] EnergyCap[™] Torch Granule FR membrane is available in a highly reflective bright white surfacing.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, and limitations. See warranties and guarantees on gaf.com for complete coverage and restrictions.

Product Application:



Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

	RATED PRODUCT ID #: 0676-0025B		
		INITIAL	AGED
CRRC COLLADOF RATING COLLACIE	Solar Reflectance	0.75	0.67*
	Thermal Emittance	0.90	0.88*
	SRI	93	81*
	The ratings above are subject to CRRC rating program conditions, requirements, and limitations. Visit coolroofs. org for important information and disclaimers about CRRC rating conditions, requirements, and limitations.		

CRRC Rapid Ratings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced with the measured three-year aged values upon completion of the weathering process. Ray values calculated using Rapid Ratings may change once the aged rating replaces the interim rating.

Testing & Approvals:

- Classified by UL in accordance with ANSI/UL 790, including as a component of Class A fire resistancerated roofing assemblies. Refer to UL Product iQ for specific assemblies.
- FM Approved refer to roofnav.com for approved assemblies.
- Cool Roof Rating Council Rated Product.
- Can be used to comply with 2022 Title 24, Part 6, Cool Roof requirements of the California Code of Regulations.
- Texas Department of Insurance Report RC-49.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- UL Evaluation Report UL ER1306-02.
- Meets or exceeds ASTM D6222, Type I, Grade G.
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.

Physical Properties:

Property	Minimum Value	GAF Value
Thickness, min, mm (mils), Grade G	4.0 (160)	4.0 (160)
Peak load at 23 +/- 2° C (73.4 +/- 3.6° F) MD and CMD, before and after heat conditioning, kN/m (lbf/in.), min.	MD - 8.8 (50) CMD - 8.8 (50)	MD - 14.0 (80) CMD - 12.3 (70)
Elongation at 23 +/- 2° C (73.4 +/- 3.6° F) MD and CMD, before and after heat conditioning, at peak load, % min.	MD - 23 CMD - 23	MD - 42 CMD - 50
Peak load at -18 +/- 2° C (0 +/- 3.6° F) MD and CMD, kN/m (lbf/in.), min.	MD - 10.5 (60) CMD - 10.5 (60)	MD - 16.6 (95) CMD - 14.0 (80)
Elongation at -18 +/- 2° C (0 +/- 3.6° F) MD and CMD, at peak load, % min.	MD - 10 CMD - 10	MD - 30 CMD - 30
Ultimate elongation at 23 +/- 2° C (73.4 +/- 3.6° F), MD and CMD, % min.	MD - 30 CMD - 30	MD - 48 CMD - 55
Tear strength at 23 +/- 2° C (73.4 +/- 3.6° F) N (lbf), min.	311 (70)	467 (105)
Low-temperature flexibility, before and after heat conditioning, ° C (° F), max.	+0 (32)	-10 (14)
Dimensional stability, % change, max.	1.00	0.42
Compound stability, ° C (° F) min.	110 (230)	130 (266)
Granule embedment, max. loss, grams (Grade G Only)	2.0	0.5
Water absorption, % max.	3.2	2.8
Moisture content, % max.	1.0	<1.0
Low-temperature unrolling, ° C (° F), max.	5 (41)	-10 (14)
Net mass per unit area, min., g/m²(lb./100 fl.²)	4,150 (85)	4,185 (86)
Bottom side coating thickness, min, mm (mils)	0.76 (30)	0.78 (31)

NOTE: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.

