

GAF RUBEROID® TOICHPIUS Granule FR Membrane

ITEM CODE: 3861

Description:

RUBEROID® Torch Plus Granule FR membrane is a premium, fire-rated modified bitumen membrane manufactured to stringent GAF specifications. Its core is a strong, heavyweight, resilient non-woven polyester mat that is coated with APP polymer-modified asphalt and surfaced with mineral granules.

Uses:

RUBEROID[®] Torch Plus Granule FR membrane is designed for new roofing and re-roofing applications where long-term roof system performance is specified.

Advantages:

- Lighter weight —installed premium roof designs weigh less than 3 pounds per square foot.
- Resilience RUBEROID® Torch Plus Granule FR membrane's heavyweight polyester mat core helps resist splits and tears due to its pliability and elongation characteristics.
- Durability specially formulated modified asphalt gives RUBEROID® Torch Plus Granule FR Membrane lasting performance.
- Available with black or white granule surfacing color options.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, andlimitations. See warranties and guarantees on gaf.com for complete coverage and restrictions.

Product Application:



Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean, dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

Testing and Approvals:

- Classified by UL in accordance with ANSI/UL 790, including as a component of Class A fire resistance-rated roofing assemblies. Refer to UL Product iQ for specific assemblies.
- FM Approved refer to roofnav.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- Texas Department of Insurance Report RC-49.
- UL Evaluation Report UL ER1306-02.
- Meets or exceeds ASTM D6222 Type II, Grade G.
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.





Product Specifications:

ASTM D6222 Type II, Grade G

| Admin Dozzz Type II, Oldde O | | |
|------------------------------|-----------------------------------|--|
| Roll Size* | 106.9 ft.2 (10.0 m ²) | |
| Roll Length | 32' 6" (10.0 m) | |
| Roll Width | 39.5" (1.0 m) | |
| Roll Weight | 102 lb. (46.3 kg) | |
| Roll Thickness | 175 mils | |
| Rolls per Pallet | 25 | |
| Full Pallet Weight | 2,600 lb. (1,179.3 kg) | |
| Reinforcement | Polyester | |
| Top Side Surfacing | Granules | |
| Bottom Side Surfacing | Burn-Off Film | |

* Roll Size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.

Physical Properties:

| Property | Standard Minimum Value | GAF Value |
|---------------------------------------------------------------------------------------------------------------------------|-------------------------------------|-------------------------------------|
| Thickness, min. mm (mils), Grade G | 4.0 (160) | 4.5 (175) |
| Peak load at 23 +/- 2° C (73.4 +/- 3.6° F) MD and CMD, before and after heat conditioning, kN/m (lbf/in.), min. | MD - 8.8 (50.0) CMD - 8.8 (50.0) | MD - 17.9 (102) CMD - 15.8 (90) |
| Elongation at 23 +/- 2° C (73.4 +/- 3.6° F) MD and CMD, before and after heat conditioning, at peak load, % min. | MD - 23 CMD - 23 | MD - 45 CMD - 50 |
| Peak load at -18 +/- 2° C (0 +/- 3.6° F) MD and CMD, kN/m (lbf/in.), min. | MD - 10.5 (60) CMD - 10.5 (60) | MD - 22.8 (130) CMD - 21.0 (120) |
| Elongation at –18 +/- 2° C (0 +/- 3.6° F) MD and CMD, at peak load, % min. | MD - 10 CMD - 10 | MD - 42 CMD - 44 |
| Ultimate elongation at 23 +/- 2° C (73.4 +/- 3.6° F), MD and CMD, % min. | MD - 30 CMD - 30 | MD - 58 CMD - 60 |
| Tear strength at 23 +/- 2° C (73.4 +/- 3.6° F) N (lbf), min. | 311 (70) | 631 (142) |
| Low-temperature flexibility, before and after heat conditioning, $^\circ$ C ($^\circ$ F), max. | +0 (32) | -10 (14) |
| Dimensional stability, % change, max. | 1.00 | 0.42 |
| Compound stability, ° C (° F) min. | 110 (230) | 130 (266) |
| Granule embedment, max. loss, grams (Grade G Only) | 2.0 | 1.4 |
| Water absorption, % max. | 3.2 | 3.1 |
| Moisture content, % max. | 1.0 | <1.0 |
| Low-temperature unrolling, ° C (° F), max. | 5 (41) | -10 (14) |
| Net mass per unit area, min., g/m² (lbs./100 ft.²) | 4,150 (85) | 4,165 (85) |
| Bottom side coating thickness, min. mm (mils), | 0.76 (30) | 0.77 (30) |

Note: Values stated above are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.



Visit gaf.com