# **APP Base/Ply Sheet**







ITEM CODE: 3603

## **Description:**

RUBEROID® Torch Smooth membrane is a tough, resilient modified bitumen membrane manufactured to stringent GAF specifications. Its core is a strong, resilient, non-woven polyester mat that is coated with APP polymer-modified asphalt. The membrane is available with a smooth surface.

### **Uses:**

RUBEROID®Torch Smooth membrane is designed for new roofing and re-roofing applications as well as flashings. RUBEROID® Torch Smooth membrane is also suitable for repairs of built-up roofing membranes or other modified bitumen systems.

# **Advantages:**

- Lighter weight installed roof designs weigh less than 2 pounds per square foot.
- Resilience RUBEROID® Torch Smooth membrane's polyester mat core helps to resist splits and tears due to its pliability and elongation characteristics.
- Durability specially formulated modified asphalt gives RUBEROID® Torch Smooth membrane lasting performance.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, and limitations. See warranties and guarantees on gaf.com for complete coverage and restrictions.

# **Product Application:**



# Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean, dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

### **Testing and Approvals:**

- Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.
- FM Approved refer to roofnav.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- UL Evaluation Report UL ER1306-02.
- Texas Department of Insurance Report RC-49.
- Meets or exceeds ASTM D6222 Type I, Grade S.
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.







### **Product Specifications:**

#### ASTM D6222 Type I, Grade S

**		
Roll Size*	106.7 ft. <sup>2</sup> (10.0 m <sup>2</sup> )	
Roll Length	32' 4" (10.0 m)	
Roll Width)	39.625" (1.0 m)	
Roll Weight	85 lb. (38.6 kg)	
Roll Thickness	160 mils (4.0 mm)	
Rolls per Pallet	25	
Full Pallet Weight	2,175 lb. (986.6 kg)	
Reinforcement	Polyester	
Top Side Surfacing	Talc or Sand	
Bottom Side Surfacing	Film	
·	·	

\* Roll Size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.

Standard

# **Physical Properties:**

Property	Minimum Value	GAF Value
Thickness, min, mm (mils), Grade S	3.5 (140)	4.0 (160)
Peak load at 23 +/- $2^{\circ}$ C (73.4 +/- $3.6^{\circ}$ F) MD and CMD, before and after heat conditioning, min. kN/m (lbf/in.)	MD - 8.8 (50) CMD - 8.8 (50)	14.9 (85.3) 12.6 (72)
Elongation at 23 +/- $2^{\circ}$ C (73.4 +/- $3.6^{\circ}$ F) MD and CMD, before and after heat conditioning, min. kN/m (lbf/in.)	MD - 23.0 CMD - 23.0	45 9.5 (54)
Peak load at -18 +/- 2° C (0 +/- 3.6° F) MD and CMD, kN/m (lbf/in.), minimum	MD - 10.5 (60) CMD - 10.5 (60)	18.4 (105) 16.6 (95)
Elongation at –18 +/- $2^{\circ}$ C (0 +/- $3.6^{\circ}$ F) MD and CMD, at peak load, % minimum	MD - 10.0 CMD - 10.0	20 24
Ultimate elongation at 23 +/- 2° C (73.4 +/- 3.6° F), MD and CMD, % minimum	MD - 30.0 CMD - 30.0	50 55
Tear strength at 23 +/- 2° C (73.4 +/- 3.6° F) min. N (lbf)	311 (70)	511 (115)
Low temperature flexibility, before and after heat conditioning, max. ° C (° F)	+0 (32)	10 (14)
Dimensional stability, max. change (%)	1.0	0.4
Compound stability, ° C (° F) minimum	110 (230)	130 (266)
Water absorption, max. (%)	3.2	2.5
Moisture content, max. (%)	1.0	<1.0
Low temperature unrolling, max. ° C (° F)	5 (41)	-10 (14)
Net mass per unit area, min. g/m²(lb./100 ft.²)	3,418 (70)	3,515 (72)
Bottom side coating thickness, min, mm (mils)	0.76 (30)	0.79 (31)

NOTE: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.



