

BUR Base-Ply & Inter-Ply Sheet



Tri-Ply®
Ply4
Ply Sheet



ITEM CODE: 3193

Description:

Tri-Ply® Ply 4-ply sheet roofing felt is constructed with a strong glass fiber mat that is coated with the high-quality asphalt, and is designed to ensure a sound waterproofing membrane when installed with hot asphalt per GAF's application instructions.

Uses:

This ply felt is ideal for the construction of built-up roofs. It's designed for use in all climate zones and is appropriate for use as a base sheet, as a ply felt, and in the construction of flashing membranes.

Advantages:

- Extra strength — High-tensile strength and a high degree of dimensional stability results in a roof system with greater resistance to splitting and cracking.
- Performance — Optimum porosity of the felt provides ready escape of air while allowing proper asphalt penetration at the time of mopping.
- Durability — Asphalt coating provides high degree of moisture resistance.
- Compliance — Meets requirements for application in all climate zones.
- Versatility — Rolls out flat for easy installation.
- Limited product warranties are available. See warranties on gaf.com for complete coverage and restrictions.

Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

Testing and Approvals:

- Classified by UL in accordance with ANSI/UL 790, including as a component of Class A fire resistance rated roofing assemblies. Refer to UL Product IQ for specific assemblies.
- FM Approved — refer to roofnav.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- UL Evaluation Report UL ER1306-02.
- Texas Department of Insurance Report RC-49.
- Meets or exceeds CSA A123.17.
- Meets or exceeds ASTM D2178, Type IV
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.



Product Specifications

ASTM D2178, TYPE IV

Roll Size*	526.5 (48.9 m ²)
Roll Length	161'-8" (49.3 m)
Roll Width	39.5" (1.0 m)
Roll Weight	40 lb. (18.1 kg)
Roll Thickness	26 mils
Rolls per Pallet	25
Full Pallet Weight	1,050 lb. (476.3 kg)
Reinforcement	Glass-Fiber

* Roll Size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.

Physical Properties

PROPERTY	STANDARD MINIMUM VALUE	GAF VALUE
Ash (glass mat only)(%)	70-88	74
MD breaking strength, lbf/in (kN/m)	44 (7.7)	49 (9.9)
XMD/CD breaking strength, lbf/in (kN/m)	44 (7.7)	45 (7.9)
Pliability, 1/2-in. (13-mm) radius bend	No Failures	Pass
Net dry mass, lb/100ft ² (g/m ²) (Individual Rolls)	6.0 (293)	6.7 (327)
Moisture at time of manufacture, max. (%)	1.0	≤ 1.0
Mass of desaturated mat, min. ft. ² lb/100 ft ² (g/m ²)	1.7 (83)	1.7 (83)
Bituminous saturant, lb/100 ft ² (g/m ²)	3.0 (146)	3.1 (151)
Unrolling @50° F and 140° F (Pass/Fail)	Pass/Fail	Pass

Note: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide



Visit gaf.com

We protect what matters most™

