ELASTUFF® 101 WITH ELASTUFF® 103 QUICK SPEC

METAL (EL-1)

NOTE: The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at www.gaf.com.



METHOD REQUIREMENTS

Required:

- O Roof must be clean, dry and tight
- O No rain, dew, fog, or freezing temperatures in forecast for 24 hours
- O Adhesion test required
- O Power washing required

Recommendations:

- Refer to Technical Data Sheet for product specific application and surface temperature restrictions.
- Rust should be removed with a wire brush prior to coating, and structural repairs should be made with like-materials as needed.

Installation Overview:

1. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0

pounds per linear inch (PLI). Test patches to be applied with rates listed below.

- 2. Tighten/replace existing fasteners. Encapsulate with appropriate flashing material.
- 3. Power-wash substrate to remove contaminants that could negatively affect adhesion. Allow roof to completely dry.
- 4. Install crickets to divert water and complete other necessary sheet metal repairs.
- 5. Prime per chart below.
- 6. Treat all roof penetrations, drains, curbs, and scuppers. (Refer to Substrate Preparation section for requirements)
- Horizontal seams must be 3-coursed. Overlap and trapezoidal vertical seams must be treated with flashing grade only. Other vertical seams may forgo treatment <u>IF</u> the seal/tape is intact on the seam or if they are double locked. (Refer to Seam Treatment Guide for requirements)
- 8. Apply coating per the chart below:

CLEAN / PRIME							
	Product	Rate (Gal/Sq)					
Cleaner	UCC Cleaner (diluted)	0.5 - 0.7					
Primer	Lock-Down Primer	0.33 - 0.40					

SEAMS & DETAILS ¹								
Treatment Type	Product	Total (Gal/Sq)	DFT* (mils)					
3-Coursed Rates	Elastuff [®] 101 and Fabric	4.00	57					
Flashing Grade Only Rates	Elastuff® 101	2.00	26					

Note: For other product options, please refer to our Seam Treatment Guide.

¹Flashing rates are based on a 6" (152 mm) width.

METAL									
	Elastuff [®] 101		Elastuff [®] 103		Total		Warranties/Guarantees Available		
Coverage Term	Base Coat (Gal/Sq)	DFT* (mils)	Top Coat Gal/Sq	DFT* (mils)	Total Gal/Sq	DFT* (mils)	Emerald Pledge™	Diamond Pledge™	
10 Year	1.00	13	1.00	9	2.00	22	Yes	Yes	
15 Year	1.25	16	1.50	14	2.75	30	Yes	Yes	

* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor. Note: DFT for 3-coursed rates includes 6 mils for the fabric.