

DE NEEF® Cut Cat Fast and Extra Fast PURE Data Sheet

Product Description

DE NEEF®Cut Cat Fast and Extra Fast PURE are designed to be mixed with DE NEEF®Cut PURE to allow for faster reaction times in applications involving the cut-off of gushing water with a high to very high pressure and speed. Cut Cat Fast and Extra Fast PURE are recommended for use in cold temperatures when the use of the standard Cut Cat PURE does not result in a fast enough reaction.

DE NEEF®Cut Cat Fast and Extra Fast PURE are used at a 10% mixing ratio. Both are non-flammable, solvent free, and phthalate free. Final foam is resistant to most organic solvents, mild acids, alkaloids and microorganisms.

DE NEEF®Cut Cat Fast and Extra Fast PURE have very fast reaction times, less than 60 seconds in salt water at 27°F.

Product Advantages

- Faster reaction times for DE NEEF® Cut PURE.
- Enhanced cold weather reactivity.
- Phthalate free, unregulated for transport and storage.

Product Applications

- Sealing larger volume leaks thru concrete cracks and fissures
- Cold Weather Grouting

Installation Guidelines

Warning: Consult the Technical Data Sheets and SDS before using.

Installation Instructions: For detailed installation instructions refer to the DE NEEF®technical data sheet for Cut PURE.

1. Shake catalyst can 2-3 minutes.
2. Do not pour catalyst directly into original grout container.
3. Pour the desired amount of Cut PURE into a clean pail.
4. Measure the appropriate amount of Cut Cat Fast or Extra Fast and pour it into the grout and stir until adequately mixed.
5. Never use more than the 10% of Cut Cat Fast or Extra Fast. Excess acceleration will cause vigorous expansion that is prone to shrinkage.

During injection the grout will follow the path of least resistance.

When the material has stopped penetrating it will continue to expand against the confines of the crack/joint and compress within itself, forming a very dense, closed cell material stopping the leak.

Extreme conditions: For application procedures in extreme temperatures and specific environments or equipment recommendations call the DE NEEF® Technical Service Department.

Cleaning: Clean all tools and equipment which have been in contact with the resin with DeNeef Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

Reaction Times

10% Cut Cat Fast PRe

T	START	END	FOAM FACTOR
27°F	30"	1'40"	20V
40°F	28"	1'25"	26V
50°F	26"	1'23"	26V
60°F	23"	1'20"	28V
68°F	23"	1'20"	30V
77°F	20"	1'20"	32V

10% = 64 oz per 5 gallons of Cut PRe

Reaction Times

10% Cut Cat Extra Fast PRe

T	START	END	FOAM FACTOR
27°F	25"	1'15"	24V
40°F	23"	1'10"	28V
50°F	23"	1'10"	28V
60°F	23"	1'05"	30V
68°F	20"	1'05"	30V
77°F	18"	1'05"	32V

10% = 64 oz per 5 gallons of Cut PRe

Packaging & Handling

DE NEEF® Cut Cat Fast and Extra Fast PRe:

- 32 oz. metal cans.
- 5.0 gallon metal pail

DE NEEF® Cut Cat Fast and Extra Fast PRe are sensitive to moisture and should be stored in the original containers in a dry area. Storage temperature must be between 40 °F and 90 °F. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible.

Shelf life: 2 years.

Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations. Avoid eye and skin contact. Do not ingest. Refer to SDS. For emergencies, call CHEMTREC 1-800-424-9300.

Limitations

Please do not exceed the recommended catalyst ratio.

CAUTION: pH NOTICE. Water used to activate PRe Grouts must be in the pH range of 3-10 for optimum foam quality.

Properties

DE NEEF® CUT CAT FAST PURE		
Viscosity	20 cp at 77 °F	ASTM D2196 A
Color	Transparent Red Liquid	
Density	0.973 g/cm ³	
Flashpoint	257 °F	ASTM D93
DE NEEF® Cut Cat Extra Fast PRe		
Viscosity	20 cp at 77 °F	ASTM D2196 A
Color	Transparent Red Liquid	
Density	1.000 g/cm ³	
Flashpoint	257 °F	ASTM D93

gcpat.com | North America Customer Service: +1 (877) 423 6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DE NEEF is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-13

gcpat.com/solutions/products/de-neef-waterproofing-injection-solutions/de-neef-cut-cat-fast-and-extra-fast