

# DE NEEF® Flex LV PURE Data Sheet

---

## Product Description

DE NEEF® Flex LV PURE is a hydrophobic polyurethane designed to form a flexible gasket when injected into cracks and joints in concrete structures. DE NEEF® Flex LV PURE grout expands on contact with water and quickly cures to a tough, flexible foam that is resistant to most organic solvents, mild acids, alkali, petroleum and micro-organisms.

## Product Advantages

- Free Foam Expansion up to 18 times
- Contains no volatile solvents
- Single Component
- Controlled reaction time
- Improved low temperature performance
- Flex Cat PURE liquid to -40°F

## Product Applications

- Sealing leaking cracks in concrete 0.02” and wider
- Sealing moving and non-moving joints in concrete

## Installation Guidelines

**WARNING: DE NEEF® FLEX LV PURE MUST BE USED WITH DE NEEF® FLEX CAT PURE.**

Consult the Technical Data Sheets and SDS before using.

**INSTALLATION INSTRUCTIONS:** For detailed installation instructions refer to the DeNeef technical bulletin for your applicatio

**CATALYST:** Shake catalyst can 2-3 minutes. Pour the desired amount of Flex LV PURE into a clean dry pail. Measure the appropriate amount of Flex Cat PURE (refer to the **REACTION TIMES** section of

this data sheet for the desired set time) and pour it into the pail. Stir until adequately mixed. Exceeding the recommended amount of catalyst may adversely affect the reaction and quality of the cured foam.

- **Flush pump with DE NEEF® Washing Agent every 1 to 2 hours.**
- **Use the minimum percentage of catalyst necessary for your application.**
- **Keep grouting materials cool during storage and pumping.**
- **Only catalyze as much material as will be used in 1-2 hours. 1 hr in hot weather, 2 hrs in cold.**
- **Do not leave catalyzed material in the pump longer than 3 hours.**

**INJECTION:** During injection the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the limits of the confined space and compress within itself, forming a dense, closed cell foam.

**EXTREME CONDITIONS:** For application procedures in extreme temperatures and specific environments or equipment recommendations call the DE NEEF® Technical Service Department.

**CLEANING:** Clean all tools and equipment which have been in contact with the resin with DE NEEF® Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

## Reaction Times

T	% CAT	END REACTION	FOAM FACTOR
40°F	1	17'00"	12V
	2	8'30"	14V
	5	4'00"	16V
60°F	1	10'50"	14V
	2	7'00"	16V
	5	3'05"	16V
77°F	1	9'00"	14V
	2	5'35"	16V
	5	2'10"	17V
86°F	1	7'30"	14V
	2	4'40"	16V

	5	1'45"	17V
95°F	1	6'45"	15V
	2	4'00"	17V
	5	1'35"	18V

## Packaging & Handling

### DE NEEF® Flex LV PRe:

5 gallon metal pail  
50 gallon metal drum

### DE NEEF® Flex Cat PRe:

25 fl. oz. in 1 qt. metal cans

DE NEEF® Flex LV PRe is sealed under dry nitrogen because it is sensitive to moisture, and should be stored in original containers in a dry area. Storage temperature must be between 40°F and 90°F. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible. Shelf life: 2 years.

## Limitations

### DE NEEF® FLEX LV PURE MUST BE USED WITH DE NEEF® FLEX CAT PURE.

Low temperatures will significantly affect viscosity. Flex LV PRe is not designed for void filling and must be used in compression. If site temperatures are extremely low, heat bands or heated water baths may be used on the pails before and during installation to maintain the product's temperature. Avoid splashing water into open containers, as the material is water activated. Avoid exceeding 90°F when warming.

**CAUTION: PH NOTICE.** Water used to activate PRe Grouts must be in the pH range of 3-10 for optimum foam quality.

## Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations. Avoid eye and skin contact. Do not ingest. Refer to SDS. **FOR EMERGENCIES, CALL CHEMTREC 1-800-424-9300.**

## Properties

<b>DE NEEF® FLEX LV PURE RESIN</b>		
Solids	100%	ASTM D2369
Viscosity	550 cps at 77°F	ASTM D2196
Color	Pale yellow	
Density	1.02 g/cm <sup>3</sup>	ASTM D4659
Flashpoint	>270°F	ASTM D93
Corrosiveness	Non-corrosive	
<b>DE NEEF® FLEX CAT PURE</b>		
Viscosity	15 cps at 77°F	ASTM D2196
Color	Clear to pale grey	
Flashpoint	221°F	ASTM D93
<b>DE NEEF® FLEX LV PURE CURED</b>		
Density confined	1.00 g/cm <sup>3</sup>	ASTM D3574
Density free	about 3 PCF	ASTM D3574
Tensile strength	>174 psi	ASTM D3574
Elongation %	100	ASTM D3574

**P**hthalate free- no phthalate-based plasticizers  
**U**nregulated for transport- no hazmat shipping  
**R**eformulated TDI free-all MDI based technology.  
**e**nvironmentally friendly-NSF/ANSI 61 approved.



Flex LV PRe when combined with Flex CAT PRe is certified by  
WQA to NSF/ANSI 61 for materials safety only,  
as verified and substantiated by test data.  
Please refer to WQA website ([www.wqa.org](http://www.wqa.org))  
for use ratios and limitations.

**[gcpat.com](http://gcpat.com) | North America Customer Service: +1 (877) 423 6491**

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA  
GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as

Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2026-01-28

[gcpat.com/solutions/products/de-neef-waterproofing-injection-solutions/de-neef-flex-lv-pure-data-sheet](http://gcpat.com/solutions/products/de-neef-waterproofing-injection-solutions/de-neef-flex-lv-pure-data-sheet)