

# DARAPEL<sup>®</sup> S80

Water-repellent admixture

## Product Description

DARAPEL<sup>®</sup> S80 is a ready-to-use water-repelling admixture. It is manufactured under rigorous quality control to ensure uniform performance. The product weighs approximately 7.7 lb/gal (0.92 kg/L).

## Product Advantages

- Reduces ingress of water into the concrete
- Increases resistance to weathering
- Increases resistance to chemical attack
- Reduces potential for efflorescence
- Adds visual appeal to concrete

## Uses

Architects, engineers, contractors, and other authorities agree that even good quality concretes, mortars, etc., are inherently porous and permeable to water. DARAPEL<sup>®</sup> S80 admixture imparts water-repelling properties to the capillary pores, forming an internal barrier against water transmission in mixes used for ready mixed or precast concrete.

## How it Works

The addition of DARAPEL<sup>®</sup> S80 admixture to the concrete mixture will provide hydrophobic (water-repelling) properties to the hardened concrete. The unique silane chemistry of the product creates a permanent non-wettable lining on the walls of the concrete pores, making them water repellent. The DARAPEL<sup>®</sup> S80 “built-in” water barrier guards against damage caused by water infiltration.

## Improved Concrete Quality

Concrete shall be designed in accordance with Standard Recommended Practice for Selecting Proportions for Concrete, ACI 211. Higher quality concrete will result from the use of DARAPEL<sup>®</sup> S80 admixture. The workability of mixes will be improved. The protection of embedded steel and resistance to bacteria or fungus growth may also be increased by keeping the concrete drier.

## Addition Rates

Addition rate may be varied to achieve the desired water repellency. Typically, addition rates can vary from 2 to 5 fl oz/100 lb (130 to 325 mL/100 kg) of cementitious materials. Addition rates may vary depending on materials, job conditions and desired performance characteristics. Please consult your GCP Applied Technologies representative for information and assistance.

## Compatibility with Other Admixtures and Batch Sequencing

DARAPEL<sup>®</sup> S80 water repelling admixture is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that the product be added to the concrete mix near the end of the batch sequence for optimum performance. Please see GCP Technical Bulletin TB-0110, Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations for further recommendations. Pretesting of the concrete mix should be performed before use, and as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 airentaining agent (such as DARAVAIR<sup>®</sup> or DAREX<sup>®</sup> product lines) is recommended to provide suitable air void parameters for freezethaw resistance. Please consult your GCP Applied Technologies representative for guidance.

## Curing

Proper curing of the in-place mix is vital. Allowing the mix to prematurely dry out should be prevented because re-wetting (and continued hydration) may not be effective.

## Air management guidelines

Added by itself, DARAPEL<sup>®</sup> S80 admixture may have a slight effect on the entrained air volume. Trial mixes or field tests are recommended to evaluate its effect with actual materials at production site.

Requirements for minimum compressive strength, maximum water-cementitious ratio, and air contents listed in Building Code Requirements for Structural Concrete, ACI 318 must be strictly adhered to, being careful to select the appropriate exposure category for the structure and nominal maximum aggregate size for the concrete.

The following guidelines are recommended for concrete containing DARAPEL<sup>®</sup> S80 admixture and subject to freezing and thawing conditions. Note that minimum plastic concrete air contents represent plastic air at the point of placement.

- Minimum compressive strength at 28 days of 4,500 psi (31 MPa)
- Maximum water-cementitious materials ratio of 0.45

Maximum Aggregate Size	Minimum Plastic Concrete Air Content
3/8 in. (9.5mm)	7.5%
1/2 in. (12.5mm)	7%
3/4 in. (19mm) or greater	6%

- Minimum fresh concrete air content in accordance with the maximum aggregate size

## Packaging & Handling

DARAPEL<sup>®</sup> S80 water-repelling admixture is available in 275 gal (1040 L) totes, and in 55 gal (208 L) drums. The product will begin to freeze at approximately 14°F (-10°C). In storage and for proper dispensing, the temperature should be maintained above 32°F (0°C).

## Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

## Flammability

DARAPEL®S80 admixture has a flash point of 194 °F (90 °C). This is substantially above the upper limit of 140 °F (60 °C) for classification as a flammable material and just below the limit of 200 °F (93 °C) for classification as a combustible material by DOT requirements. This product must be treated with care and protected from excessive heat, open flame or sparks. For more information, consult the SDS.

**North America customer service: 1-877-4AD-MIX (1-877-423-6491)**

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

GCP Applied Technologies, GCP, DARAPEL, DARAVAIR and DAREX are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-28

[gcpat.com/solutions/products/darapel-water-repellent-admixture/darapel-s80](http://gcpat.com/solutions/products/darapel-water-repellent-admixture/darapel-s80)