

# ELIMINATOR<sup>®</sup> Data Sheet

Cold, Liquid, Spray Applied Bridge Deck Waterproofing

## Product Description

ELIMINATOR<sup>®</sup> is a high performance waterproofing membrane for the protection of concrete and steel bridge decks based on Stirling Lloyd, now GCP's unique ESSELAC<sup>®</sup> advanced resin technology and extensive experience in the development of coatings for specialist waterproofing. It cures rapidly to provide a tough, flexible seamless membrane impervious to water and waterborne contaminants. ELIMINATOR<sup>®</sup> has an unparalleled track record with thousands of structures waterproofed successfully throughout the world.

## Uses

ELIMINATOR<sup>®</sup> protects concrete and steel structures from the corrosive effects of water and chloride ions. Typical applications include:

- Concrete Bridge Decks
- Steel Bridge Decks
- Bridge Piers
- Bridge Service Ducts
- Culverts

ELIMINATOR<sup>®</sup> is installed in conjunction with Stirling Lloyd, now GCP Applied Technologies, proprietary primers, ensuring a high bond between substrate and membrane. For highway bridges a range of compatible tack coats promote adhesion between membrane and surfacing. The membrane can be trafficked for limited durations when required. Please discuss with GCP Technical Services if considering this application.

The system can be adapted to accommodate both high and low ambient temperatures without any detriment to the performance of the system (See table below).

## Product Advantages

- Long and effective life
- Able to withstand high humidity and cures rapidly even at low temperatures enabling all year round application
- Rapid application and re-access
- Crack-bridging across wide temperature range
- Excellent abrasion and chemical resistance
- High bond to substrate, preventing tracking of water under membrane.
- High thixotropy for application to vertical and horizontal surfaces
- Seamless, and chemically bonds to itself
- Two color-coded coats assure highest quality system minimizing defects
- Withstands 480°F pavement placement on the cured membrane

- Tough – tolerant to direct ballast loading without protection board. Conforms to AREMA Specifications Chapter 29-2-6, 2.3.10
- Quality Assured – ISO9001 certified manufacturing location
- Applied only by authorized and trained contractors

## Application

### Primer

The substrate must be primed with an appropriate GCP primer prior to application of the ELIMINATOR<sup>®</sup> membrane. A choice of primers are available depending on the type of substrate and weather conditions.

### Membrane

ELIMINATOR<sup>®</sup> is typically spray applied. The membrane is applied when the primer has cured, typically within 20 minutes. Two distinct color coats are used to aid quality assurance. ELIMINATOR<sup>®</sup> is typically applied in multiple configurations that includes, but is not limited to:

- One coat at minimum film thickness of 90 mils
- Two equal coats each at a minimum film thickness of 60 mils for a total of 120 mils
- Two coats comprising a first coat at a minimum film thickness of 80 mils followed by 40 mils with an aggregate broadcast
- Other configurations exist on a on project-by-project basis

### Tack Coat/Bond Coat

A tack coat or bond coat must be applied to ELIMINATOR<sup>®</sup> when it is being used as a waterproofing membrane on road bridges underneath asphalt paving. A range of tack coats and bond coats are available depending upon the pavement specification<sup>1</sup>.

## Cleaning

All tools and equipment should be cleaned with acetone before the material is allowed to cure.

## Precautions

ELIMINATOR<sup>®</sup> liquid resin components are classified as flammable liquid (flashpoint 52.7°F, 11.5°C) and must be handled accordingly. Workers should wear appropriate protective clothing. Adequate ventilation must be provided. Please refer to the most recent Safety Data Sheet (SDS) for recommendations.

## Safety and Handling

Read and understand the product label and Safety Data Sheet (SDS) for each system component. All users should acquaint themselves with this information prior to working with the products and follow the precautionary statements.

SDSs can be obtained by contacting your local GCP representative or office, by calling GCP toll free at 1-866-333-3SBM (3726) and in some cases from our web site atgcpat.com.

## Packaging & Storage

Primer – Refer to separate datasheets

ELIMINATOR® Membrane (Part A and Part B) – 46.7 Gallon Drum

All components of ELIMINATOR® system should be stored in cool, dry, protected conditions, out of direct sunlight and accordance with the relevant site Health & Safety regulations. Storage conditions must not exceed 77°F. Do not store near open flames or food.

Stored in unopened containers, under the correct conditions, the components have a minimum shelf life of twelve months. If your product is more than twelve months old contact GCP Technical Services before use.

<sup>1</sup> Data is also available on the tensile bond strength and the shear bond strength of ELIMINATOR® to a variety of surfacing specifications from our Customer Services Department.

## Physical Properties

PROPERTY	TEST METHOD	RESULT
Application Temperature		-10°F to 120°F (-23°C to 50°C)*
Gel Time	Internal	6-11 minutes @ 68°F (20°C)
Overcoating Time	Internal	45 minutes @ 68°F (20°C)
Water Absorption	ASTM D570-81	< 3.5%
Water Vapor Transmission	ASTM E96-00	1 gm/m <sup>2</sup> /day (≤1.0 perms)
Tensile Strength (typical)	ASTM D638-91	1,700 psi (11.8MPa)
Elongation At Break (typical)	ASTM D638-91	130%
Low Temperature Flexibility	CAN CGSB	
@ -13°F (-25°C)	37.5 M89, ¼ inch Mandrel	Pass
Resistance To Aggregate Indentation	BD 47	Recovered Thickness**
@ 104°F (40°C)		100%
@ 104°F (40°C)		100%
@ 257°F (125°C)		100%
Dynamic Ballast Impact	SNCF 181kN/2x10 <sup>6</sup> cycles	No damage or leak

Tensile Bond Strength

(minimum)

Concrete	ASTM D4541-89	100psi (0.7Mpa)
Steel	ASTM D4541-89	290 psi (2.0 MPa)
Shore Hardness	ASTM D6132	≥40D
Volume Resistivity		8.27E+14 Ohms-cm (ER295A)
Surface Resistance		2.45E+13 Ohms (ER295A)

\* Temperature extremes require additional site dosing. Please consult with GCP Technical services.

\*\* Samples subsequently tested to resistance to chloride ion penetration. Result: 0% increase in chloride ion penetration.

GCP also provides a wide range of polymer overlays, high friction surfacing, pavement marking and color demarcation systems for highways and private use. Please contact us for further information.

**gcpat.com | North America Customer Service: 1-866-333-3726**

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the end user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ELIMINATOR® is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc

GCP0083 ELIMINATOR® Data Sheet USA\_1018

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-28

[gcpat.com/solutions/products/eliminator-bridge-deck-waterproofing-solution/eliminator](http://gcpat.com/solutions/products/eliminator-bridge-deck-waterproofing-solution/eliminator)