

**RP-400® Construction Plastic  
Wet-Dry Surface Roof Cement**



**1. PRODUCT NAME:**

RP-400® construction PLASTIC WET-DRY SURFACE ROOF CEMENT

**2. MANUFACTURER:**

Geocel Products Group A Business Unit of The Sherwin-Williams Company ("Geocel Products Group") Cleveland, OH 44115  
Phone: (800) 348-7615  
Fax: (800) 348-7009  
www.GeocelUSA.com

**3. PRODUCT DESCRIPTION:**

RP-400® construction Plastic Wet-Dry Surface Roof Cement is a single-component, asbestos free, asphalt-based cement designed for many construction, roofing, manufacturing, and industrial applications.

**Product Benefits:**

- Use on wet or dry surfaces, even underwater
- Formulated to seal quickly; will not pull apart or lose its bond
- Lever-lock lids on 3-gallon and 5-gallon pails for ease of resealing container and reduced waste
- Remains soft and pliable, and resists temperature change

**Basic Uses:**

- Ideal for patching and roof maintenance, sealing and repairing shingles, flashings, and roof seams
- Shingle tab cement
- Seals vents, pipes, chimneys, and gutters
- Seals metal building seams

**Adheres to:** Asphalt, modified bitumen, and other common building substrates

**Composition and Materials:**

RP-400® construction Plastic Wet-Dry Surface Roof Cement is an asphalt-based material containing no asbestos fiber and a special wet application additive. This formula produces a product that will bond to wet and dry surfaces.

**Grade:** Gunnable, trowelable consistency

**Primer:** Not required on most surfaces.

**Packaging:** 10 fl. oz. cartridge, 1-gallon, 3-gallon lever-lock pail, 5-gallon lever-lock pail

**Colors:** Black

**Limitations:**

- Do not paint or thin
- Do not use with single-ply membranes such as EPDM, PVC, CSPE, etc.

- Product contains solvents that may craze some plastic materials
- Store at room temperature for 24 hours before use to improve ease of application

**4. INSTALLATION:**

**Surface Preparation:** For best results, remove dust and dirt with a stiff brush or broom. Remove old sealant or roof coatings. Surface to be repaired must be clean.

**Cure:** 1 to 3 days

**Service Temperature:** -40°F to 150°F (-40°C to 66°C)

**Application Temperature:** 0°F to 140°F (-18°C to 60°C)

**Application and Tooling:** Apply with standard caulking gun, trowel, or putty knife, tooling into seams and cracks. Extend RP-400 Roof Cement coverage 3" to 4" beyond problem area to ensure seal. Apply at a rate of 1/8" per coat, not exceeding 1/4" in thickness. Geocel 1200 Poly Mesh Fabric or similar material is recommended for use in areas with movement such as cracks, seams, or flashing. Allow 24 hours to cure. Inspect and re-coat if necessary. When application is to take place at temperatures below 50°F (10°C), store RP-400 Roof Cement at room temperature for 24 hours prior to use for easier application.

**Cleaning:** Remove spilled or misapplied material from tools or other surfaces with mineral spirits or paint thinner. Observe manufacturer's pre-cautions when using toxic or flammable solvents.

**Storage Life:** One year (unopened)

**Warning:** Harmful or fatal if swallowed. If swallowed, call a physician immediately. May be harmful if inhaled in an enclosed space. Use only in a well-ventilated area. Avoid prolonged skin contact. Combustible (during cure). KEEP OUT OF REACH OF CHILDREN.

**5. AVAILABILITY AND COST:** Marketed throughout the U.S., Canada, and in select foreign markets, it is available from construction material and industrial distributors. Cost and further technical data are available from your local Geocel Products Group representative or from our office.

**6. LIMITED WARRANTY:**

Geocel, LLC warrants that the product is manufactured according to their published standards. The company guarantees for 5 years from the date of manufacture that RP-400 Plastic Wet-Dry Surface Roof Cement will not crack due to normal expansion and contraction and that it will not lose its adhesion or cohesion. Geocel, LLC will, at its option, either refund the purchase price of, or provide replacement for, that portion of the RP-400 Roof Cement which fails to perform in accordance with this warranty. Such refund or replacement will constitute the limit of Geocel's liability and obligation for any such failure. Geocel, LLC will not be liable

or obligated otherwise for any loss or damage arising directly or indirectly from this product, or the use or failure thereof, whether based on breach of warranty or negligence.

#### **7. MAINTENANCE:**

No maintenance should be required. If the sealant is damaged, either remove and reseal, or apply additional RP-400 Roof Cement over the damaged area.

#### **8. TECHNICAL SERVICES:**

Geocel Products Group representatives throughout the U.S. are available to provide technical assistance. Our in-house technical staff and laboratory facilities are equipped to respond to specific requests for further information.

#### **THEORETICAL YIELD**

##### **Per 10 fl. oz. Cartridge**

Joint Size	Linear Feet
1/4" x 1/4"	24.1
1/4" x 3/8"	16.0
1/4" x 1/2"	12.0
1/2" x 3/8"	8.4
1/2" x 1/2"	6.0

##### **Per Pail**

Sealant Thickness	Square Feet
1/8" – 1/4"	10 – 15 sq. ft./gal.

For additional product information, refer to the product spec sheet located at [www.GeocelUSA.com](http://www.GeocelUSA.com) and/or application testing.