

UltraGlaze™ SSG4000

Structural Glazing Silicone Adhesive

Product Description

UltraGlaze SSG4000 silicone sealant is a one-component high-strength neutral cure elastomeric adhesive sealant tested for structurally glazed curtainwall applications. The material is supplied as a paste, which cures into durable and flexible silicone rubber upon exposure to atmospheric moisture.

Key Features and Typical Benefits

- **Primerless Adhesion** - Direct bonds to most conventional substrates and finishes including: glass, glass coatings, ceramic frits, fluropolymer and powder coated paints, conversion-coated and anodized aluminum.
- **High Tensile Strength** - Can increase safety factors in silicone structural glazing designs.
- **High Tear Strength** - Useful in Protective Glazing applications.

Potential Applications

- Structural glazing—Factory glazing of unitized curtainwall systems or in field constructed stick curtainwall systems
- Weatherseal—For applications where expected joint movement is ≤25% of installed width
- Protective glazing
- Panel stiffener

Packaging

UltraGlaze SSG4000 silicone is currently available in 10.1 fl. oz. (299 ml) plastic caulking cartridges, 20 fl. oz. (591 ml) foil sausage packs, 5 gallon plastic pails (5 gals. / 18.9 L) and 55 gallon drums (42 gals. / 158.9 L).

Colors

UltraGlaze SSG4000 structural glazing adhesive - Black

Typical Physical Properties

Typical physical property values of UltraGlaze SSG4000 structural glazing silicone adhesive as supplied and cured are set forth in the tables.

Typical Properties - Uncured

Property	Value ⁽¹⁾	Test Method
Color	Black	-
Polymer	100% Silicone	-
Consistency	Non-sag paste	-
Specific Gravity	1.52	P-15
VOC	31 g/l	EPA 24
Work Life (tooling time)	20-40 minutes	-
Tack Free Time	5-7 hours	ASTM C679
Application Rate	2 seconds	ASTM C603
Sag/Slump	0.1" max.	ASTM D2202

Typical Properties - Cured

Property	Value ⁽¹⁾	Test Method
Hardness, Durometer (Type A Indentor)	39	ASTM D2240
Ultimate Tensile Strength	342 psi (2.36 MPa)	ASTM D412
Ultimate Elongation	451%	ASTM D412
Tensile at 25% Elongation	71 psi (0.49 MPa)	ASTM C1135
Tensile at 50% Elongation	112 psi (0.77 MPa)	ASTM C1135
Ultimate Tensile Strength	163 psi (1.12 MPa)	ASTM C1135
Ultimate Elongation	124%	ASTM C1135
Tear Strength; die B	79 ppi	ASTM D624
Shear Strength (@ 1/4" thickness)	175 psi (1.21 MPa)	ASTM C961
Peel Strength (average); aluminum, glass (21-day cure @ 75°F (21°C) 50% RH)	40 pli	ASTM C794
Joint Movement Capability	±25%	ASTM C719
Service Temperature Range (after cure)	-55°F to +250°F	-
Weathering and U.V. Resistance	Excellent	20 yr. study
Cure Time (1/4" or 6 mm deep section) @ 75°F (24°C) 50% RH	2-3 days	-
Full Cure (most common bead sizes)	10-14 days	-

(1) Typical properties are average data and are not to be used as or to develop specifications.

Installation

Refer to QC & Application Guidelines- UltraGlaze Sealants for Surface Preparation requirements, design information and detailed application instructions.

Applicable Standards

UltraGlaze SSG4000 silicone meets or exceeds the requirements of the following specifications for one-part sealants.

ASTM Specifications:

C1184, Type S, Use G and O (finished aluminum)
C920; Type S, Grade NS, Class 25, Use NT, A, G, O

Canadian Specification:

CAN/CGSB-19.13-M87

Technical Services

Additional technical information, literature, laboratory testing and application engineering are available upon request from Momentive Performance Materials (MPM). Any technical advice furnished by MPM or any representative of MPM concerning any use or application of any MPM product is believed to be reliable, but MPM makes no warranty, expressed or implied, of suitability for use in any application for which such advice is furnished.

Limitations

Customers must evaluate MPM products and make their own determination as to fitness of use in their particular applications.

UltraGlaze SSG4000 structural glazing adhesive should not be considered for:

- Structural adhesion on bare metals or surfaces subject to corrosion (i.e., mill aluminum, bare steel, etc.)
- Encapsulated designs without access to moisture
- Exceedingly large structural cavities (see Sealant Application section in SSG Design and Application Guide for additional information).
- Application of product in exceedingly hot or cold conditions (see Sealant Application section in SSG Design and Application Guide for additional information).
- Underwater or in applications where the product will be in continuous contact with water.
- Contact with strong acids or bases.
- Food contact applications.

Patent Status

Nothing contained herein shall be construed to imply the non existence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.siliconesforbuilding.com or, upon request, from any MPM representative. Use of other materials in conjunction with MPM sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Customer Service Centers

North America - America, Canada	+1 800 295 2392 Toll free Email: commercial.services@momentive.com
Latin America	Brazil +55 11 5128-4222 Direct Number Email: contato@momentive.com Mexico +52 55 2169 7670 Direct Number Email: commercial.services@momentive.com
EMEIA - Europe, Middle East, Africa, and India	Europe +39 0875 758888 Direct Number Middle East, Africa and India + 91 44 71212207 Direct Number* *All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka Email: 4information.eu@momentive.com
APAC - Asia Pacific	China 800 820 0202 Toll free +86 21 3860 4928 Direct Number Japan Sales: JP.Silicones@momentive.com South Korea +82 2 3495 2141 Direct Number South East Asia, Australia & New Zealand +60 3 8309 8088 Direct Number* *South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).
MyMomentive™ Order Management Site	shop.mymomentive.com

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Before purchasing or using any Momentive products, please visit www.siliconeforbuilding.com/legaldisclaimer to view our full product and sales disclaimer.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc., or its affiliated companies.

Copyright 2025 Momentive Performance Materials Inc. All rights reserved.



Licensed Partner

siliconesforbuilding.com