



TECHNICAL PRODUCT BULLETIN Acrylitex Hand Texture

Physical Characteristics

Weight per Gallon: $12 \pm 2 \text{ lb}$ pH: 9 ± 1

% Solids by Weight: $63 \pm 5\%$ Substrate: Gypsum wallboard,

concrete

% Solids by Volume: $47 \pm 5\%$ Pre-Treatment: None

Viscosity @ 78^{\circ}F (25.5°C): 28,000 ± 6000 cps **Form:** Liquid, Ready-to-Use

Flash Point (Closed Cup): None Color: White

Spreading Rate: $750 \pm 50 \text{ ft}^2$ @ 1 wet mil **Odor:** Mild Latex

Material VOC: < 75 g/ltr (0.49 lb/gal) Carrier: Water-base

Coating VOC (minus water): < 95 g/ltr (0.8 lb/gal)

Note: a certified product data sheet detailing VOC content will be available upon request from Acrylic Technologies, Inc.

Environmental Department.

Application Specifications

Method: Product can be applied by hawk and trowel, pan and knife.

Drying Schedule: Ambient air, forced air Reduction: None

Special Notes

Effect on Freezing: DO NOT FREEZE; product will not recover

Shelf Life: 12 months - please rotate stock on a regular basis

Regulatory Status: This product is not considered a hazardous waste under current RCRA regulations. This product does not contain, nor is it manufactured using ozone-depleting substances as listed under Section 611 of the Clean Air Act.

Before using this product, please read the Material Safety Data Sheet for Acrylitex Hand Texture and follow the recommended safety instructions.