

WATERPROOFING

CCW-702



Description

CCW-702 is a quick-drying, solvent-based, high-tack adhesive specifically designed to promote maximum adhesion of CCW Membrane Waterproofing products.

Installation

Apply by medium ($\frac{3}{8}$ " for best results) nap roller or brush in an even film at 300 to 350 square feet per gallon. Caution must be taken not to apply excess contact adhesive which could cause longer drying times. Allow adhesive to dry for 20 minutes minimum at 75°F. Drying times may vary at lower temperatures. Porous substrates require additional material, reducing the coverage rates for proper adhesion. Adhesive has a satisfactory cure when surface is tacky, but will not transfer when touched. Apply only in areas to be waterproofed the same day. Reapply if area becomes dirty or wet. When used in adverse climactic conditions (i.e. humid, cool, etc.) or on a porous substrate, additional time will be required.

All fluid-applied product application rates are based on theoretical coverage relative to the percentage of solids in the material. These are minimum application rates to achieve the required dry film thickness for the system and do not account for substrate condition or porosity. A thicker application of the product may be necessary to achieve the required dry film thickness for system relative to the substrate.

Apply to any surface the same day of application of membrane.

Surface Preparation for Gypsum-Sheathing with Glass-Mat Facers:

When installing CCW sheet membranes and sheet flashings over gypsum-sheathing with glass-mat facers, coverage rates for contact adhesives and primers will depend on the porosity and texture of the sheathing and will vary substantially by gypsum-sheathing brand and manufacturer. To achieve consistent contact adhesive and/or primer coverage with adequate tack, it may be necessary to decrease the coverage rate (i.e. Increase the amount applied) of the contact adhesive and/or primer and/or the application of multiple coats. CCW Contact adhesives and primers shall be allowed to dry completely (lower temperatures will extend drying time) before additional coats are applied or membranes installed. Caution should be taken as contact adhesives and/or primers applied to gypsum-sheathings with glass-mat facers will take longer to dry than other substrates. Multiple adhesion tests should be performed randomly to verify proper application of primer and ensure a successful application.

Warnings and Hazards

Flammable liquid and vapors. Use only with adequate ventilation and avoid breathing vapors. Refer to MSDS for other important warnings and product safety information.

Storage

Store CCW-702 between 35° and 110°F (2° to 43°C).

Packaging

5-gallon pails, 45 pails per pallet, P/N 305363

Typical Properties

| Property | Results |
|----------------------|---------------|
| Weight per Gallon | 7.5 lbs |
| Solids Content | 46% by wt |
| VOC Content | 450 g/l |
| Color | Blue |
| Flash Point | -4°F (-20°C) |
| Adhesion to Concrete | 11.0 lb/in in |
| Viscosity | 200 cps |
| Storage Temp | 35°F to 110°F |

WATERPROOFING

CCW-702

Limited Warranty

Carlisle Coatings & Waterproofing Incorporated (Carlisle) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Carlisle materials prove to contain manufacturing defects that substantially affect their performance, Carlisle will, at its option, replace the materials or refund its purchase price. This limited warranty is the only warranty extended by Carlisle with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. Carlisle specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Carlisle's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Carlisle material in question.