

# WATERPROOFING

## CCW-704

### Description

Carlisle CCW-704 is a solvent-based, rubberized bitumen mastic. After evaporation of the solvent, the remaining compound is a rubber-like material that adheres tenaciously to the polyethylene facer of CCW Sheet Membranes.

CCW-704 Mastic is used as a secondary seal on the seams, T-joints, overlaps and other terminations/penetrations of CCW sheet membrane systems. It is designed for use on the top surface and edges of the CCW sheet membrane and should never be used underneath the membrane.

### Coverage Rate

A ½" bead yields approximately 100 linear feet per gallon. Estimate one 30-oz. tube for T-joint and end lap treatment for every 200 sq. ft. of membrane installed.

### Warnings and Hazards

Contains combustible solvents. Use only with adequate ventilation. Avoid contact with the skin, especially open breaks in the skin. In the event of skin contact, remove immediately and wash with hot, soapy water. Refer to MSDS before use for other warnings and product information.

### Packaging

30-oz. cartridges/12 cartridges per case, P/N 304737

5-gallon pails/45 pails per pallet, P/N 305360

### Typical Properties

Property	Method
Color	Black
Weight	10.4 lbs/gal
Viscosity (Brookfield #7 @ 10 rpm)	5000 poise
VOC	200 g/l
Flash Point	180°F

### Limited Warranty

Carlisle Coatings & Waterproofing Incorporated (Carlisle) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Carlisle materials prove to contain manufacturing defects that substantially affect their performance, Carlisle will, at its option, replace the materials or refund its purchase price. This limited warranty is the only warranty extended by Carlisle with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. Carlisle specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Carlisle's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Carlisle material in question.