

Physical Properties

Appearance Black liquid	Flexibility (Low Temperature) Pass (ASTM D-2939)	Solids By Weight >51% (ASTM D-2939-94)
Application Temperature 50° F and rising	Freezability Do not freeze	Specific Gravity @ 77° F (25°C) 1.02
Brookfield Viscosity 3500-6500 cPs 2D@ 20 rpm and 77° F	Maximum VOC 0 calculated	Water Resistance Pass (ASTM D-2939)
Color Black brown	Maximum VOS 0 calculated	Weight Per Gallon 8.44-8.46 lbs (ASTM D-2939-94)
Flash Point >212° F	pH 10-11	

Description

HE305 - DRIVEWAY ELASTOMERIC CRACK FILLER is an asphalt based material for effectively filling cracks in asphalt pavements. **HE305 - DRIVEWAY ELASTOMERIC CRACK FILLER** is a unique elastomer-modified asphalt base emulsion produced by incorporating the rubber polymer into the asphalt using extreme pressures and temperatures. It is formulated with additional adhesion promoting polymers to provide a tight, highly extensible and flexible, dried film with excellent resistance to water, weathering and elevated temperatures.

Features

- Fill cracks up to 1/2 inch wide in asphalt driveways.
- Provide a tight and flexible seal.
- Resist water, weather, and high temperatures.
- Be applied directly from the container.

Usage

This product is especially designed to be used straight from the container for filling cracks in driveways and parking lots which are up to 1/2" wide.

Coverage

HE305 - DRIVEWAY ELASTOMERIC CRACK FILLER can be used to fill cracks up to 1/2" wide.

Surface Preparation

Hose or blow off loose materials, dust, and dirt from cracks. Cracks should be damp but free of standing water. Apply when temperature is at least 50°F and when rain is not likely within 24 hours. Allow sealer to dry until firm before covering with driveway sealer.

Application

Invert container and shake for 1 to 2 minutes to obtain a uniform consistency. To use, remove cap and cut tip to 1/8" opening. Place spout in crack. Squeeze container to apply filler in crack. Fills cracks up to 3/8" wide level with the surface. For cracks between 1/8" and 1/2" wide, fill higher to allow for shrinkage. Fill deep cracks with sand until 1/4" below the top of pavement. Apply crack filler slightly below pavement surface. **Note:** Filler applied above surface can cause tracking. Sprinkle sand over filler to help prevent tracking during drying. Plug hole in filler spout when not in use.

Precautions

Avoid using when rainfall is likely within 24 hours, at temperatures below 50°F, or for cracks wider than 1/2". Let filled cracks cure at least 7 days or until firm before coating is applied or when temperature will fall below 50°F within 24 hours after application. When transporting this product, be sure the container is secured and the lid is tight. Do not allow the container to tumble as this may loosen the lid and allow leakage to occur. Do not heat container or store in temperature above 110°F.

Cleanup

Fresh coating can be removed with water. Use kerosene, paint thinner, or mineral spirits if material has started to dry. Clean hands with waterless hand cleaner. Use care in handling solvents.

Caution

CAUTION! Do not heat container or store at temperatures greater than 120° F. Close container after each use. **DO NOT TAKE INTERNALLY!** Use protective measures to avoid contact with eyes and skin. **If swallowed, CALL PHYSICIAN IMMEDIATELY!** In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. **GET MEDICAL ATTENTION.** Dispose of container and unused contents in accordance with Local, State and Federal regulations. **KEEP OUT OF REACH OF CHILDREN! DO NOT ALLOW THIS PRODUCT TO FREEZE!**

WARNING: This product contains detectable amounts of chemicals known to the State of California to cause cancer, birth defects, or other reproductive harm.

EMPLOYERS should obtain a copy of the **Material Safety Data Sheet (MSDS)** from your supplier or directly from Henry at the toll free number or website below.

Product Sizes

GALLON (8.98 lb)

Limited Warranty

We, the manufacturer, warrant only that this product is free of defects, since many factors which affect the results obtained from this product - such as weather, workmanship, equipment utilized and prior condition of the substrate - are all beyond our control. We will replace at no charge any product proved to be defective within 12 months of purchase, provided it has been applied in accordance with our written directions for uses we recommended as suitable for this product. Proof of purchase must be provided. **DISCLAIMER OF WARRANTIES AND LIMITATION OF LIABILITY: THIS LIMITED WARRANTY IS IN LIEU OF ANY OTHER WARRANTIES EXPRESS OR IMPLIED INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FOR A PARTICULAR PURPOSE. MANUFACTURER SHALL HAVE NO LIABILITY OF ANY KIND BEYOND PRODUCT REPLACEMENT, INCLUDING FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES RESULTING FROM ANY DEFECTS OR ANY DELAYS CAUSED BY REPLACEMENT OR OTHERWISE. THIS LIMITED WARRANTY PROVIDES THE PURCHASER'S EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT.**