

# P-1

## Paver Criteria



### Description

Concrete Plaza pavers shall be a high-density pressed concrete unit manufactured to  $\pm 1/8$ " tolerance and produced by subjecting the concrete mix to a minimum pressure of 1,000 pounds per square inch over the entire surface area. CCW recommends the use of pedestals and shims to elevate and adjust the pavers. The paver should meet the following minimum physical properties.

### Limited Warranty

Carlisle Coatings & Waterproofing Incorporated (Carlisle) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Carlisle materials prove to contain manufacturing defects that substantially affect their performance, Carlisle will, at its option, replace the materials or refund its purchase price. This limited warranty is the only warranty extended by Carlisle with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. Carlisle specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Carlisle's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Carlisle material in question.

Property	Results
Thickness	1 <sup>7</sup> / <sub>8</sub> "
Finish and Color	As specified by owner
Compressive Strength	7,500 psi min
Water Absorption	< 5%
Density	155 lbs/cu ft
Flexural Strength	1,100 psi
Weight	23.5 lbs/sq ft min