

Extreme Rubberized Flashing Cement

| Physical Property                 | Typical Value     | Test Method   |
|-----------------------------------|-------------------|---------------|
| Appearance                        | Black Thick Paste | -             |
| Application Temperature (Ambient) | -20° F to 140° F  | -             |
| Consistency                       | Trowel Grade      | -             |
| Flash Point                       | 105º F            | ASTM D3278    |
| Underwater Adhesion               | 100%              | ASTM D3409    |
| VOC Content (maximum)             | 275 g/l           | EPA Method 24 |
| Weight                            | 8.5-9.5 lbs./gal. | -             |

# **Approvals and Certifications**

- 100% underwater adhesion per ASTM D3409
- Meets or exceeds ASTM D4586 Standard Specification for Asphalt Roof Cement, Asbestos-Free, Type I, Class II
- Miami-Dade County Approved
- Can contribute to LEED certification credits

# Description

**Pro-Grade® 167 Extreme Rubberized Flashing Cement** is a super-premium roof flashing cement formulated with the professional roofer in mind. **Pro-Grade® 167** is modified with SEBS rubber and contains high quality solvents and UV inhibitors making it a best-in-class flashing cement for permanent repairs in any weather condition, wet or dry.

# Features

- · Contains UV inhibitors and SEBS rubber for durability
- Suitable for extreme weather conditions, apply between -20° F and 140° F
- Superior elasticity and flexibility; ideal for control joints and seams or anywhere else movement is expected

## Usage

Repairs holes, cracks and splits on composition shingles, mineral surface cap sheets, asphalt roofs, APP, SBS modified rubber roofs, cured concrete and metal roofs. Seals leaks and openings around flashings, chimneys, masonry, vents, skylights, joints in metal edging, gutters, etc.

## Application

Surface Prep: Clean dirt, loose material, and any other foreign matter from the surface. Remove embedded gravel and cut away old roof cement to ensure bond. Remove rust and scale with wire brush.

Apply: For cartridge: cut nozzle at angle, puncture inner seal, and apply with caulking gun.

Work into hole 1/8" to 1/4" thick with a trowel, putty knife or gloved hand. Press firmly and spread at least 2" beyond, feathering edges. If hole is over 1/4" wide or 2" long, reinforce with **Henry®** 181 or **Henry®** 183 Roof Repair Fabric between two layers of cement.

## Coverage

Approximately 12 sq. ft. per gallon applied at 1/8" thick.

For 3-course application, approximately 6 sq. ft. per gallon.

## Clean-up

Clean tools with kerosene, paint thinner or mineral spirits. Clean hands with waterless hand cleaner.

# Packaging

1 Gallon, 3 Gallon

# Precautions

CLOSE AIR INTAKES ON ROOF UNTIL SOLVENTS DISSIPATE! May not yield satisfactory results over some APP torch down membranes. Not for use over coal tar, gravel, rubber or PVC sheet roofing, wood shingles or under APP membrane or other products with burn-off film. To extend repair life, coat with a Henry Roof Coating after 30 days.

For more information, visit www.henry.com or for technical assistance call us at 800-486-1278. For more information on Henry's<sup>®</sup> product warranty and liability disclaimer please visit www.henry.com/warranty. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at www.henry.com or by emailing Henry<sup>®</sup> Product Support at productsupport@henry.com or by calling 800-486-1278.

® Henry and Pro-Grade are registered trademarks of Henry Company

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry<sup>®</sup> Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice