



Physical Property	Typical Value	Test Method
Appearance	Bright White, fluid	-
Application Temperature (Ambient)	35° F to 120° F (2° C to 49° C)	-
Tack-Free Time	1-2 Hours	-
Durometer Hardness	42 Shore A	ASTM D2240
Flash Point	140.9° F (60.5° C)	ASTM D93
Flame Spread	Class A	ASTM E108/UL790
Low Temperature Flexibility	-15° F (-26.1° C)	ASTM D522
Permeability	4.6 perms	ASTM E96
Solids Content by Volume	92% +/-3	ASTM D2369
Tensile Strength	320 psi	ASTM D412
Elongation at break	170%	ASTM D412
VOC Content (maximum)	10 g/l	EPA Method 24
Water Absorption	0.0005%	ASTM D471
Water Resistance (Hydrostatic Pressure)	100 psi (min 24 wet mil)	AATCC 127 (option 1)
Water Leakage Resistance	Pass (≥22 dry mils)	ASTM D7281
Weathering, Accelerated QUV 5,000 hours	No Degradation	ASTM G154
Solar Reflectance, Initial	0.88	ASTM C1549
Thermal Emittance, Initial	0.88	ASTM C1371
Solar Reflectance Index (SRI), Initial	111	ASTM E1980
Accelerated Solar Reflectance	0.83	ASTM D7897, C1549
Accelerated Aged Thermal Emittance	0.88	ASTM D7897, C1371
Accelerated Aged Solar Reflectance Index (SRI)	104	ASTM D7897, ASTM E1980

### Approvals and Certifications

- Meets or exceeds ASTM D6694 Standard Specification for Liquid-Applied Silicone Coating Used in Spray Polyurethane Foam Roofing Systems
- Meets or exceeds ASTM D7281 Standard Test Method for Determining Water Migration Resistance through Roof Membranes.
- Excellent fungi resistance in accordance with ASTM G21 Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi
- ENERGY STAR<sup>®</sup> Certified
- Meets the requirements of California Energy Commission (CEC) Title 24 Section 118(i)3
- Cool Roof Rating Council (CRRC) Rated
- Florida Approved
- FM Certified
- UL Certified
- Miami-Dade County Approved
- NSF Protocol P151 Certification of Rainwater Catchment System Components

### Description

**Pro-Grade<sup>®</sup> 988 Silicone White Roof Coating** is a 100% silicone, high solids, solvent-free, one-component, moisture-curing silicone rubber roof coating system for use on existing smooth asphaltic BUR, smooth or granulated cap sheet, single ply roof membrane, well-adhered acrylic coating, metal, concrete, sprayed-in-place polyurethane foam and various aged membrane roofing. The system provides long-term weathering protection and resists the effects of ozone, ultraviolet radiation and temperature extremes. With its high solids content and absence of hydrocarbon solvents, **Pro-Grade<sup>®</sup> 988** can be applied in excess of 50 mils in a single coat without blistering, while maintaining maximum adhesion.

### Features

- High solids

## Pro-Grade® 988 Silicone White Roof Coating

---

- Solvent-free – VOC compliant
- Permanent ponding water resistant
- Rain safe in 15 minutes
- 100% silicone moisture-cure technology
- Chemically bonds with roof substrates as it cures
- Mold and mildew resistant
- Easy application with roller, brush, or commercial spray equipment
- Wide temperature performance range: -40° F to +200° F

### Usage

---

Coating can be used on many different commercial and residential roof substrates to reflect the sun's heat and UV rays, as well as to help seal and protect the surface. It works well on low slope roofs and suitable for pitched roofs. Acceptable roof types include:

- Spray polyurethane foam (SPF) roofs
- Metal roofs
- Recoating previously coated roof.
- Aged asphalt roofs – including Built-Up Roofing (BUR) and Modified Bitumen (MB) roofs
- Aged Single Ply Membrane, including EPDM, TPO, PVC, and Hypalon® roofs
- Aged concrete

To prevent bleed-through, discoloring and staining over new or aged asphalt materials, BUR and modified bitumen membrane, **Pro-Grade® 294 Base Coat & Sealer** must be used prior to making silicone repairs. On metal roofs, remove all rust and treat with a rust-inhibiting spot primer. Not recommended over Kynar® / Hylar® coated metal roofs, or shingles of any kind.

Always perform an adhesion test patch over smooth MB/BUR, EPDM, TPO, PVC, and Hypalon® and existing coated roofs, and metal roofs. Refer to the Adhesion Test Instructions for more information. If the adhesion test result is not greater than or equal to two pounds, use **Pro-Grade® 941 Primer** and repeat test.

### Application

---

**Clean:** Using a minimum 2,000 psi pressure washer wash the roof with a non-filming detergent, such as TSP or TSP substitute. Caution should be used to not inject water into the roof substrate during washing. In areas with stubborn dirt, grease, or other contaminants, use a stiff bristle brush or broom to scrub the areas clean with additional water and non-filming detergent. Treat mildew or mold. Give the roof a final rinse to ensure it is free of all detergent or anything else that could affect adhesion. Allow roof to dry completely before application. Apply a test area of coating over the existing membrane to verify proper adhesion to membrane prior to start of application.

**Prep:** On metal roofs, remove all rust and treat with a rust-inhibiting spot primer. On asphaltic roofs, use **Pro-Grade 294®** for bleed blocking. If primer is required on single ply membrane or metal, apply **Pro-Grade® 941**.

After primer or base coat sealer is applied (if needed), repair defects, such as splits, cracks, blisters, deteriorated flashing, cracked metal edging, and any other defects affecting the water tightness of the roof. As a preventative measure, seal all penetrations, curbs, flashings, transition areas, areas where dissimilar materials intersect, and other areas that could leak with **Pro-Grade® 920 Silicone Roof Sealant** or **Pro-Grade® 923 Butter Grade Silicone Roof Sealer**, **Pro-Grade® 957 Silicone Fibered Roof Sealer** or a three-course patch with **Pro-Grade® 988 Silicone Roof Coating**. Ensure all drains are clean and clear and cut back any vegetation that is growing that may cause debris to fall on the roof and clog drains in the future.

**Coat:** Coating should only be applied to a clean, dry, and fully prepared roof substrate as described above. It may be applied with a 1/2" to 1" nap lint-free roller, brush, or commercial airless spray rig. If spraying, a commercial airless spray rig capable of producing a minimum of 3500 psi at the spray gun tip is required. The pump should have a minimum of 3 gallons per minute output and be fed by a 5:1 transfer pump to prevent cavitation. Always use components rated for pump pressure. Hoses should have a minimum I.D. of 3/4" and an adequate working pressure.

The spray gun should be high pressure (5000 PSI) with a reverse-a-clean spray tip, having a minimum orifice of 0.030 and a 50° fan tip. Mix well prior to and during use with a minimum ¾ horsepower air operated mixer. After opening the container, try to use it up as soon as possible. Keep containers covered and sealed at all times during use, when practical. If a skin forms in the container, simply remove the skin, mix the product and use the rest. Coating must be evenly applied and pin-hole free. Allow coating to fully cure before applying additional coats (depending on weather conditions, a full cure may take 2-6 hours). Please consult Product Support for specific questions regarding the application of this product.

## Pro-Grade<sup>®</sup> 988 Silicone White Roof Coating

---

Coating should only be applied to a clean, dry, and fully prepared roof substrate as described above. Application at temperatures lower than 50° F (10° C) and less than 35% relative humidity will typically result in slower cure times. The surface temperature must be at least six Fahrenheit degrees or three Celsius degrees above the dew point and rising.

**NOTE:** DO NOT THIN. Do not apply at temperatures below 35° F (2° C) or if rain is expected within 15 minutes of application. The surface temperature must be at least six Fahrenheit degrees or three Celsius degrees above the dew point and rising. Store product in a cool, dry, shaded location. Ensure lid is completely sealed. Not for use over plywood, walking decks, gravel, uncoated polyurethane foam, Kynar<sup>®</sup> / Hylar<sup>®</sup> coated metal roofs, shingles of any kind, or old roofs that are too dry and brittle to withstand the shrinkage stresses that occur after the application of any coating. Do not apply to wet or saturated roofs.

This product is not recommended for interior use. Building occupants should be warned of spray operations in process. Installers should exercise caution during spray processes to avoid falls caused by stepping into slippery wet coating. Installers should read and understand all technical and informational literature on this product, prior to use of the product. **Slip Warning:** Use extreme caution when walking or working on silicone coated surfaces. Surface is extremely slippery and can create a fall hazard resulting in injury or death.

### Coverage

---

Minimum coating coverage is 1.5 gallons/square. Dry film thickness (DFT) should be a minimum of 22 mils. Apply each additional coat in a perpendicular direction to the previous coat. Application rates should be adjusted to meet each particular roof's specified requirements. Coverage rates are theoretical and do not take into account for material loss due to spraying, surface texture, etc. Thicker dry film results in better performance and longer coating life.

- For Henry<sup>®</sup> Material Plus and Gold Seal Warranty, see appropriate Henry<sup>®</sup> Restoration System (HRS) Guide Specifications coating coverage rate requirements by substrate and duration.

### Clean-up

---

Clean-up of spray equipment containing uncured material may be accomplished by flushing with VM&P Naphtha or mineral spirits. Read solvent Safety Data Sheets before use. Keep cleaning solvents away from all sources of heat, sparks, flame, lighted smoking materials, or any other ignition source. This product cures by reacting with moisture and should not be left in spray guns, pump equipment, and hoses for prolonged periods unless equipment contains moisture lock hoses, fittings, and seals. Equipment without these components will transmit sufficient moisture vapor to gradually form cured material on hose walls and at unsealed connections potentially causing an increase in operating pressure and material flow restriction.

### Packaging

---

5 Gallon, 55 Gallon

### Color

---

White

### Shelf Life

---

Unopened, 24 months from date of manufacture when stored in a cool, dry, and shaded location.

### Limited Product Warranty

---

We, the manufacturer, warrant only that this product is free of defects, since many factors which affect the results obtained from this product - such as weather, workmanship, equipment utilized and prior condition of the substrate - are all beyond our control; therefore, Henry Company cannot guarantee results of the application of the coating including, but not limited to: appearance, watertightness, and suitability of the substrate. The substrate to be coated must be structurally sound and have reasonable life expectancy prior to being coated. We will replace at no charge any product proved to have a material defect during the life of the existing roof, provided it has been applied in accordance with our written directions for uses we recommended as suitable for this product. Proof of purchase must be provided. This warranty is void if the coating is coated over, patched, painted, or covered in any way with any product other than this coating or approved products. **DISCLAIMER OF WARRANTIES AND LIMITATION OF LIABILITY: THIS LIMITED WARRANTY IS IN LIEU OF ANY OTHER WARRANTIES EXPRESS OR IMPLIED INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. MANUFACTURER SHALL HAVE NO LIABILITY OF ANY KIND BEYOND PRODUCT REPLACEMENT, INCLUDING FOR CONSEQUENTIAL, EXEMPLARY OR INCIDENTAL DAMAGES RESULTING FROM ANY DEFECTS OR ANY DELAYS CAUSED BY REPLACEMENT OR OTHERWISE. IF PURCHASER DOES NOT ACCEPT THESE TERMS OF HENRY'S LIMITED WARRANTY, PURCHASER MAY RETURN WITHIN 30-DAYS OF PURCHASE ALL CONTAINERS OR PACKAGES OF PRODUCT PURCHASED FOR A FULL REFUND (PROVIDED THE CONTAINERS OR PACKAGING IS UNOPENED AND LESS SHIPPING CHARGES IF ANY). RETENTION OF PRODUCT BEYOND 30-DAYS FROM PURCHASE, OR USE OF PRODUCT SHALL CONSTITUTE ACCEPTANCE OF HENRY'S LIMITED WARRANTY TERMS, CONDITIONS AND DISCLAIMERS. THIS LIMITED WARRANTY PROVIDES THE PURCHASER'S EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT.** To the extent that any part of this LIMITED PRODUCT WARRANTY AND LIABILITY DISCLAIMER is determined unenforceable under the law of the place of purchase of the product, that part is severed and the remainder of these terms remain in full force and effect. To the extent permitted by law, the duration of any implied warranties is limited to the duration of Henry's express warranty.

---

© Henry and Pro-Grade are registered trademarks of Henry Company  
© Hypalon is a registered trademark of DuPont Performance Elastomers LLC  
© Kynar is a registered trademark of Arkema  
© Hylar is a registered trademark of Solvay

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry® Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.