


Concrete Inserts HW-340

Malleable Iron Wedge Inserts



DRAWINGS FOR ILLUSTRATIVE PURPOSES ONLY

Material Conformances:

Hohmann & Barnard Wedge Inserts are made from malleable iron and conform to **ASTM A47/A47M** Grade 32510.

Hot-Dip Galvanized: ASTM A153/A153M-B2 (zinc coating 1.5 oz/ft²).

Performance Data:

Shear	Tension	Concrete Strength	Torque
16,650 lbs.	13,093 lbs.	4,125 p.s.i.	150 ft/lbs.

*Values listed above are ultimate capacities in pounds which should be reduced by a minimum safety factor of three to determine the allowable working loads.

*Minimum of 1 1/2" of concrete under bottom of insert.

Finish:

Plain Malleable Iron

Hot-Dip Galvanized

Accessories: Askew Head Bolt, Nut, and Washer

The beveled head of the askew head bolt engages the internal wedge shape of a concrete insert and produces an automatic tightening action when a load is placed on it.

HOHMANN & BARNARD, Inc.

30 Rasons Court | Hauppauge, NY 11788 CORPORATE HEADQUARTERS
T: 800.645.0616 F: 631.234.0683

www.h-b.com

Branch/Subsidiary Locations: ALABAMA - ILLINOIS - MARYLAND NEW YORK - PENNSYLVANIA - TEXAS CANADA © HOHMANN & BARNARD, INC. - 2012