

Control Joints / Expansion Joints Rebonded Rubber



DRAWINGS FOR ILLUSTRATIVE PURPOSES ONLY

PRODUCT TECHNICAL DATA - Physical Properties

Compression Set 5% maximum AASHTO M 153-95, ASTM D 1752-84 Type I Para 5.3 1/2" samples compressed 50%

for 22 hrs @ 70° F - 24 hr recovery

Recovery 95% (+) AASHTO M 153-95, ASTM D 1752-84 Typel Para 5,2

Compression Deflection

AASHT0 M 153-95 not less than 50 not greater than 1500 psi

Extrusion 50% compression AASHTO M 153-95, ASTM D 1752-84 Type I Para 5.4

Accelerated Aging good (7 days@158° F - Lineal shrinkage maximum 2%) 114

Water Absorption by Weight 3% ASTM D 1056-91 Type 1 (max. allowed by spec. 10%)

Density (Minimum) ASTM D 1752-84 30 PCF

Temperature Resistance

Flexibility 180 degree bend w/o cracking

HOHMANN & BARNARD, Inc.

www.h-b.com

30 Rasons Court | Hauppauge, NY 11788 CORPORATE HEADQUARTERS T: 800.645.0616 F: 631.234.0683

Branch/Subsidiary Locations: ALABAMA - ILLINOIS - MARYLAND NEW YORK - PENNSYLVANIA - TEXAS CANADA © HOHMANN & BARNARD, INC. - 2012