

HOOVER TREATED WOOD PRODUCTS, INC

TECHNICAL NOTE

FOR ADDITIONAL INFORMATION: www.frtw.com or 1-800-TEC-WOOD (832-9663)

FASTENER RECOMMENDATIONS

PYRO-GUARD[®] Interior Fire-Retardant-Treated Wood

Treatment with **PYRO-GUARD[®]** does not cause fasteners to corrode. Corrosion is caused by wetting from rainfall or other sources. **PYRO-GUARD[®]** treatment is not significantly more hygroscopic than untreated wood.

International Building Code (IBC) Section 2304.10.5.4* states - **Fasteners for fire-retardant-treated wood used in interior applications.** Fasteners, including nuts and washers, for *fire-retardant-treated wood* used in interior locations shall be in accordance with the manufacturer's recommendations. In absence of manufacturer's recommendations, Section 2304.10.5.3* shall apply.

In accordance with IBC 2304.10.5.4*, Hoover recommends the following:

- Per UL Evaluation Report UL ER7002-01 section 5.3 - Fasteners made from aluminum, carbon steel, galvanized (zinc) steel, copper or red brass are acceptable.
- When **PYRO-GUARD[®]** fire-retardant-treated wood products are used and installed in code compliant interior enclosed dry applications, not exposed to dampness or wetting, uncoated carbon steel fasteners are acceptable.
- It is suggested, but not required, that carbon steel fasteners be plated or coated.
- As stated in IBC 2304.10.5.3 stainless steel or silicon bronze fasteners are also permitted.

Plywood Fasteners Size and Spacing:

Fastener size and spacing must be as required in the applicable building code for untreated plywood of the same thickness; except that roof sheathing must be fastened with

1. Minimum 8d common or 8d deformed shank nails spaced a maximum 6 inches o.c. at edges with all nails at least 3/8 inch from panel ends and 3/8 inch from panel edges and a maximum of 12 inches o.c. at intermediate supports for panels on 24- and 32-inch spans and spaced a maximum of 6 inches o.c. on all supports for panels on a 48-inch span, or
2. Other fasteners with comparable withdrawal and lateral load capacities at the same maximum spacing.
3. For 1-1/8-inch roof sheathing panels, minimum 10d common or deformed shank nails must be used.

For unblocked roof diaphragms panel edge clips are required for roof sheathing: one midway between supports for 24-inch and 32-inch spans, and two at 1/3 points between supports for 48-inch span. Clips must be specifically manufactured for the plywood thickness used.

**Code reference sections are from 2015 edition of the IBC. Sections 2403.10.5.3 and 2403.10.5.4 are 2304.9.5.3 and 2403.9.5.4 in the 2012 and 2009 editions.*

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY HOOVER TREATED WOOD PRODUCTS, INC.: The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Hoover Treated Wood Products, Inc. ("Hoover") disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein.