

# **INLAND COATINGS** **CR-2150** Waterproof Sealer 5% Silicone

**CR-2150** is a thin liquid of high penetrating nature with active thinners that will seal and waterproof unpainted brick, stone, stucco, masonry and cement block surfaces without changing appearance of such buildings.

#### TYPE OF APPLICATIONS:

- Brick
- Stone
- Stucco
- Masonry
- Cement Blocks

#### SURFACE PREPARATION:

The surface must be free of any oils, moisture, soil or other contaminants that may interfere with good adhesion. Carefully remove any loose material from surface with a wire brush or scraper. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

#### APPLICATION TEMPERATURES:

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-100°F. For best application, the product should be at a minimum of 50°F.

#### APPLICATION METHODS:

CR-2150 can be applied by brush or roller. See Inland Application Bulletins for additional information.

#### HANDLING & STORAGE:

CR-2150 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

#### STORAGE:

Keep container tightly closed in a dry and well-ventilated location. Keep away from sources of ignition, heat, sparks and flames. KEEP OUT OF REACH OF CHILDREN

#### TECHNICAL DATA .....

Color .....	Clear
Coverage Rate .....	
Smooth Surface .....	300ft <sup>2</sup> /gal
Rough Surface .....	150ft <sup>2</sup> /gal
Flashpoint .....	105°F
Weight (lb./gal).....	7.5
Solids (% by Weight).....	5%
Viscosity @ 78° .....	1500 cps.
Drying Time at 77°F.....	12 hours
Viscosity .....	Very thin
Application Temperature .....	50°F
Service Temperature.....	-30 – 300°F

**\*The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.**