



RC 2018

Rubber Top Coat

RC 2018 Rubber Top coat provides excellent waterproofing and ultraviolet resistance. It is a one-component product that has excellent adhesion to properly prepared surfaces. It is thermally stable and resists cracking and peeling due to weather extremes. RC 2018 Rubber Top-coat can be applied over various base-coats, including RC 2012B, RC 2013M, DF 1000 and DF 1050.

TYPE OF APPLICATIONS:

- Metal Roofing
- TPO
- Hypalon
- EPDM
- Modified Bitumen
- Built-up
- Urethane Foam

SURFACE PREPARATION:

The surface must be free of any oils, moisture, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces. Oil and grease should also be removed with solvents or an appropriate detergent cleaner, such as Inland RC 300. In many cases high pressure water blast will be sufficient to prepare the surface.

APPLICATION TEMPERATURES:

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-100°F. For best spray application, the product should be at a minimum of 70°F. Lower temperatures can be utilized for brush applications.

APPLICATION METHODS:

RC 2018 can be applied by brush, spray or roller. Best results can be obtained with airless spray equipment. See Inland Application Bulletins for additional information.

Recommended Spray Equipment = Airless

- Tip size025" - .035"
- Fluid Pressure (PSI). 3000 min.
- Fluid hose size 3/8" - 1/2"

TECHNICAL DATA:

Coverage	65-100 sf/gal
Flashpoint	101°F.
Weight (lb./gal.)	8.95
Solids (% by Weight)	56%±1%
Viscosity @ 78°F	4800 cps.
Drying Time	2-4 hours
Elongation	400%
Tensile Strength	1200 PSI

HANDLING & STORAGE:

RC 2018 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

Form:#LC2018-1 Revision:02/18