



TITANIUM™ Roofing Products Information

TITANIUM™ UDL-25 PLUS Synthetic Roofing Underlayment

Code Listings

- ICC ESR 2391
- MIAMI-DADE HVHZ NOA Nr.08-0625.02
- INTERTEK WARNOCK HERSEY Report # 3107959
- CLASS A ASTM E-108 UDL 25 met ASTM E108, Intertek Report # 3114956-01
- CAN/CSA A220.1 Intertek Report # 3144563COQ-004A

Technical Data

TEST & STANDARD

Class A Fire ASTM E108
Nail Sealability ASTM D1970
Permeability ASTM E96-00
Water Transmission ASTM D4869
Tear Strength ASTM D4533-91
Tensile Strength ASTM D751-95
Burst Strength ASTM D751-95
Elongation ASTM D751-95
Weight per Square ASTM D5261
Minimum Thickness ASTM D1777
Temperature Range

TITANIUM™ UDL-25 PLUS TYPICAL VALUE

Pass
Pass
.06 perms
Pass
MD 40 lbs. (18 kg) | CD 35 lbs. (17 kg)
MD 154 lbs. (70 kg) | CD 110 lbs. (50 kg)
220 psi (1517 kPa)
MD 18% CD 18%
2.9lbs (1.3 kgs)
17 mils (0.43 mm)
-70°F (-55°C) to 212°F (100°C)

LENGTH PER ROLL: 250' / 76.2 m
WIDTH PER ROLL: 48" / 122 cm
WEIGHT PER ROLL: 31 lbs / 14 kg
ROLL SIZE: 10 sq / 93 m²
ROLLS PER PALLET: 42
PALLET WEIGHT: 1352 lbs / 613 kg

Test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications. All values \pm 10%. Dry tested conditions: in water, #30 felt will absorb +30% water and lose +50% strength when wet. This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measures. Values are typical data and not limiting specifications. All values \pm 10%



InterWrap Inc.
Customer Service
Toll Free: 1-888-713-7663

Fax: 1-604-820-5420

E-mail: info@interwrap.com

32923 Mission Way,

Mission, BC Canada, V2V 6E4

InterWrap, The InterWrap logo and TITANIUM are trademarks of InterWrap Inc. in Canada, The United States and other countries, used under license by InterWrap Corp. in the United States and IBCO SRL worldwide. © 2009

TITANIUM™
SYNTHETIC ROOFING UNDERLAYMENT

Roofers rely on it.