TITANIUM UDL SYNTHETIC ROOFING UNDERLAYMENT

PROFESSIONAL GRADE FOR USE UNDER ALL: METAL, TILE, SLATE, SHAKE & SHINGLE ROOFING

- Up to 6 months UV exposure rating
- Meets and exceeds ASTM D226 Types I & II
- ICC ES Approved
- Class A Fire ASTM E108
- CAN/CSA A220.1
- Meets Class 4 Hail Rating
- Florida Building Code Approved
- Texas Department of Insurance
- 6 times lighter & 20 times stronger than 30 lb felt
- Contributes to LEED® points, 100% Recyclable
- All temperature performance -40°F to 240°F
- Synthetic construction inert to mold growth
- Cool gray surface, doesn't expand or contract
- Dual logo custom printing available

SPECIFICATIONS

LENGTH PER ROLL:	250′ / 76.2 m
WIDTH PER ROLL:	48" / 122 cm
WEIGHT PER ROLL:	40 lbs / 18.2 kg
NET ROLL SIZE:	10 sq / 93 m ²
ROLLS PER PALLET:	30

PALLET WEIGHT: 1250 lbs / 567 kg













*See www.InterWrap.com/LifetimeWarranty for complete coverage and restrictions

TEST & STANDARD UDL

Class A Fire ASTM E108 Nail Sealability ASTM D1970

Permeability ASTM E96
Water Transmission ASTM D4

Water Transmission ASTM D4869

Tear Strength ASTM D4533

Tensile Strength ASTM D751

Burst Strength ASTM D751

Elongation ASTM D751

Weight per Square ASTM D5261

Minimum Thickness ASTM D1777

Temperature Range

UDL30 TYPICAL VALUE

Pass

Pass

0.06 perms

Pass

MD 44 lbs (20 kg) CD 40 lbs (18 kg)

MD 143 lbs (65 kg) CD 110 lbs (50 kg)

250 psi (1720 kPa)

MD 18 % CD 18 %

4.0 lbs (1.82 kg)

25 mils (0.63 mm)

-40°F to 240°F (-40°C to 115°C)

ASTM #30 FELT TYPICAL VALUE

N/A

N/A

1.75 perms

Pass

MD 4 lbs (1.8 kg) | CD 2 lbs (0.9 kg)

MD 70 lbs (32 kg) | CD 38 lbs (17 kg)

62 psi (430 kPa)

MD 2% CD 2%

27.5 lbs (12.5 kgs)

60 mils (1.5 mm)



Charleston, SC • Vancouver, BC • Mission, BC • Montréal, QC Web: www.InterWrap.com/titanium | E-mail: info@interwrap.com
Toll Free: 888 713 7663 | Tel: 778 945 2888



This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measures.

Test data is based on average taken over several production runs and should not be considered or

Test data is based on average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications. All values ± 10 %. UDL30_SS_21April2015