

TITANIUMMoofing Products Information

TITANIUM™ UDL-50 COMMERCIAL GRADE Synthetic Roofing Underlayment

Code Listings

- ICC-ES ESR-2154
- MIAMI-DADE HVHZ NOA Nr.08-0625.02
- INTERTEK WARNOCK HERSEY
- CLASS A ASTM E-108 Intertek report# 312482MID-007
- CAN/CSA A220.1 Intertek report # 3124618COQ-005F
- Florida Building Code (FBC) (PENDING)

Technical Data

TEST & STANDARD

Class A Fire ASTM E108
Nail Sealability ASTM D1970
Permeability ASTM E96-00
Water Transmission ASTM D4869
Tear Strength ASTM D226
Tensile Strength ASTM D751-95
Burst Strength ASTM D751-95
Elongation ASTM D751-95
Weight per Square ASTM D5261

Minimum Thickness ASTM D1777

Temperature Range

TITANIUM™ UDL-50 TYPICAL VALUE

Pass Pass 0.05 perms Pass

MD 55 lbs. (25 kg) | CD 55 lbs. (25 kg) MD 178 lbs. (81 kg) | CD 176 lbs. (80 kg)

300 psi (2065 kPa) MD 20% CD 20% 4.7 lbs. (2.13 kgs) 30 mils (0.75 mm)

-70°F (-55°C) to 212°F (100°C)

LENGTH PER ROLL: 250' / 76.2 m

WIDTH PER ROLL: 48" / 122 cm

WEIGHT PER ROLL: 48 lbs / 21.8 kg

ROLL SIZE: 10 sq / 93 m²

ROLLS PER PALLET: 25

PALLET WEIGHT: 1250 lbs / 567 kg

Test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications. All values \pm 10%. Dry tested conditions: in water, #30 felt will absorb \pm 30% water and lose \pm 50% strength when wet. This product is manufactured in accordance with national standards which allow for non-critical variances in

weights and measures. Values are typical data and not limiting specifications. All values ± 10%



InterWrap Inc.

Customer Service Toll Free: 1-888-713-7663

Fax: 1-604-820-5420 E-mail: info@interwrap.com 32923 Mission Way,

Mission, BC Canada, V2V 6E4

InterWrap, The InterWrap logo and TITANIUM are trademarks of InterWrap Inc. in Canada, The United States and other countries, used under license by InterWrap Corp. in the United States and IBCO SRL worldwide. © 2009

