

Features and Components

Use: JM EPDM/PVC Pourable Sealer is used as a penetration pocket filler.

Type: Two-part polyurethane sealant.

Colors: Part A: Black
Part B: Amber



Component
SE
Sealant

Type
FP
Penetration
Single Ply

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	CA	HW	HA	CA	HW	SA	MF

Do not use in Multi-Ply systems

Single Ply	TPO		PVC		EPDM		
	MF	FA	MF	FA	MF	FA	BA

Used to fill Penetration Pockets in the selected Single Ply systems above

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened FA = Fully Adhered BA = Ballasted

Energy and the Environment

Maximum VOC	Part A & B: 0 g/l
-------------	-------------------

Physical Properties

Property		JM EPDM/PVC Pourable Sealer
Percent Volatile	Part A	0%
	Part B	0%
Specific Gravity @ 77°F (25°C)	Part A	1.51
	Part B	1.24
Vapor Pressure	Part A	< 0.001 @ 68°F (20°C)
	Part B	< 1x10 ⁻⁵ mm Hg @ 77°F (25°C)

Precautions

Johns Manville EPDM/PVC Pourable Sealer is a combustible material and should be shipped and stored away from open flames, heat or sources of ignition. Keep all cans tightly sealed while in storage. It should be used only in well-ventilated areas. It may cause eye, skin and respiratory irritation, and is harmful or fatal if swallowed. Avoid contact with skin. Use impervious clothing and rubber gloves to avoid prolonged or repeated contact with skin. Read the container label and follow all safety instructions.

Installation/Application



- Apply between temperatures of: 40° to 90° Do Not Thin.
- Refer to the application instructions guidelines for proper utilization of this sealant.

Packaging and Coverage

Container Sizes	Box of three kits: Part A: 0.75 gal (2.84 l) can Part B: 0.5 pint (0.24 l) can
Weight per Can	Part A: 8.7 lb (3.95 kg) Part B: 0.57 lb (0.26 kg)
Shipping Weight (approx.)	32 lb (14.5 kg)/box
Boxes per Pallet	45
Pallet Weight (approx.)	1,500 lb (681.8 kg)
Pallets per Truck	8 (depends on order size)

Storage

Shelf Life	12 months from manufacture date
Storage Conditions	Clean, dry, indoor environment in an unopened container
Temperature Range	60°F – 75°F (16°C – 24°C) - Protect from freezing

Exposure Window

Workable pot life after mixing is approximately 30 minutes at 72°F (22°C). The material begins to cure firmly 2 hours after mixing.