

JM PVC SD PLUS — 50 MIL

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane

Meets the requirements of ASTM D 4434, Type III

Features and Components

Non-wicking Reinforced Polyester Scrim: Our fully integrated manufacturing process adds tensile strength and toughness. Edge sealant is not a requirement for cut edges.

Excellent Chemical Resistance: JM PVC is inherently resistant to oils, air conditioning coolants, fuels and grease.

Energy Savings: The white membranes provide exceptional reflectivity and emissivity for energy savings.





Single Ply

Color

White

JM Membranes are designed with a cap, core, and bottom in order to utilize recycled content. The cap, or top-side is produced with non-recycled content, and should always be install facing up. The cap is identified by the lap line and production code.

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

PI	BUR		APP		SBS			
Tulti-1	HA	CA	CA	HW	HA	CA	HW	SA
Ž	Do not use with Multi-Ply systems							

MF FA MF FA MF FA BA
Compatible with the selected Single Ply systems above

PVC

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened FA = Fully Adhered BA = Ballasted

Energy and the Environment

	Standard		Reflectivity	Emissivity	
CRRC®	White	Initial	0.86	0.86	
Unnu"		3 Yr. Aged	0.70	0.82	
CA Title 24	White	Pass	0.86	0.86	
ENERGY	White	Initial	0.86	0.86	
STAR®		3 Yr. Aged	0.70		
LEED®	White	Initial	10	08	
(SRI)		3 Yr. Aged	8	4	
Recycled	Post-consumer		0%		
Content	Post-industrial		0% - 10%		

The LEED® Solar Reflectance Index (SRI) is calculated per ASTM E1980

Peak Advantage® Guarantee Information

Product Thickness	Terms		
50 mil	5, 10 or 15 yr NDL		

Guarantee terms are for mechanically fastened and fully adhered systems. Mixed-membrane jobs $-\operatorname{JM}$ PVC SD Plus and JM PVC (KEE) $-\operatorname{will}$ not be eligible for a JM Peak Advantage Guarantee.

Codes and Approvals





Installation/Application







Fully Adhered Mechanically

nically Hot Air Weld

Refer to JM PVC application guides and detail drawings for instructions.

Packaging and Dimensions

Sizes	Coverage		
5' x 100' (1.52 m x 30.48 m)	500 ft² (46.33 m²)		
10' x 100' (3.05 m x 30.48 m)	1000 ft² (92.96 m²)		
Widths	5'	10'	
Rolls per Pallet	9	12	
Pallet Weight - lb (kg)	1485 (673.6)	4200 (1905.1)	
Pallets per Truck*	16	8	
Producing Locations	Lancaster, SC and Pawtucket, RI		

^{*}Assumes 48' flatbed truck and does not reflect pallets of accessories or impact of mixed sizes.

Mixed membrane jobs for JM PVC SD Plus and JM PVC will not be eligible for a JM Peak Advantage® Guarantee. JM PVC accessories are formulated to be compatible with JM PVC SD Plus and JM PVC.



JM PVC SD PLUS — 50 MIL

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane

Meets the requirements of ASTM D 4434, Type III

Manufactured Physical Properties

Physic	cal Properties	ASTM Test Method	ASTM Requirements	50 mil Result
Strength	Breaking Strength, min, lbf/in (N)	D 751	200 (890)	240 (1,068)
	Elongation at Break, min, %	D 751	15	15
	Tearing Strength, min, lbf (N)	D 751	45 (200)	45 (200)
	Seam Strength, min, % of breaking strength	D 751	75	80
	Static Puncture Resistance lbf (kg)	D 5602	Pass @ 33 (15)	Pass
	Dynamic Puncture Resistance J	D 5635	Pass @ 20	Pass
Longevity	Thickness, min, in.	D 751	+/- 10% from Nominal	0.050 Nominal
	Thickness Over Scrim, min, in.	D 7635	0.016	0.016
	Change in Weight After Immersion in Water, max, %	D 570 modified	3.0	3.0
	Low Temperature Bend, °F	D 2136	No cracks @ -40° F	Pass
Heat Aged Performance	Properties after Heat Aging, min	D 3045	56 days @ 176° F	
	Breaking Strength, %	D 751	90	>90
	Elongation, %	D 751	90	>90
	Linear Dimensional Change, max, % after 6 hrs @ 176° F	D 1204	0.5	<0.5
Weather Performance	Accelerated Weathering, min	G 151 & G 154	5,000 hrs	
	Cracking (@7x magnification)	G 154	No cracks	Pass
	Discoloration (by observation)	G 154	Negligible	Negligible
	Crazing (@7x Magnification)	G 154	No crazing	Pass