

JM PVC SD Plus — 60 mil MIN

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane

Meets the requirements of ASTM D 4434, Type III

Features and Components

Non-wicking Reinforced Polyester Scrim: Our fully integrated manufacturing process adds tensile strength and toughness. Edge sealant is not a requirement for cut edges.

Excellent Chemical Resistance: JM PVC is inherently resistant to oils, air conditioning coolants, fuels and grease.

Energy Savings: The white membranes provide exceptional reflectivity and emissivity for energy savings.

Patented Aramid-Reinforced Edge: Aramid fiber is woven into the fastening side of PVC membrane.





Color

White

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Ply	BUR APP			SBS				Ply	TPO			PVC			EPDM				
Lifi	HA	CA	HW	HA	CA	HW	SA	MF	igle	MF	AD	SA	IW	MF	AD	IW	MF	AD	BA
Ē	Do not use in multi-ply systems							Sin		Сотр	oatible	with the	e select	ed sing	le ply sy	stems a	above		

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

	Standard	Reflectivity Emissivity					
CRRC®	White	Initial	0.86	0.86			
CNNC ⁻		3 Yr. Aged	0.70	0.82			
CA Title 24	White	Pass	0.86	0.86			
LEED®	White	Initial	108				
(SRI)		3 Yr. Aged	8	4			
Recycled	Post-co	nsumer	0%				
Content	nt Post-industrial		0% - 10%				
The LEED® Solar Potlestones Index (SPI) is aclaulated per ASTM E1090							

The LEED® Solar Reflectance Index (SRI) is calculated per ASTM E1980.

Peak Advantage® Guarantee Information

Product Thickness	Terms
60 mil MIN	5, 10, 15 or 20 yr NDL

Guarantee terms are for mechanically fastened and fully adhered systems. Mixed-membrane jobs – JM PVC SD Plus and JM PVC (KEE) – will not be eligible for a JM Peak Advantage Guarantee. JM PVC SD Plus is not compatible with JM PVC and should not be used in JM PVC Systems.

Codes and Approvals



Installation/Application



Fastened Refer to JM PVC application guides and detail drawings for instructions.

Packaging and Dimensions

Size	10' x 100' (3.05 m x 30.48 m)				
Coverage	1000 ft ² (92.96 m ²)				
Widths	10'				
Rolls per Pallet	9				
Pallet Weight - Ib (kg)	3865 (1753.1)				
Pallets per Truck*	8				
Producing Locations	Lancaster, SC and Pawtucket, RI				

*Assumes 48' flatbed truck.

Mixed membrane jobs of JM PVC SD Plus and JM PVC will not be eligible for a JM Peak Advantage[®] Guarantee. JM PVC accessories are formulated to be compatible with JM PVC SD Plus and JM PVC.



JM PVC SD Plus — 60 mil MIN

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane

Meets the requirements of ASTM D 4434, Type III

Manufactured Physical Properties

Physic	cal Properties	ASTM Test Method	ASTM Requirements	60 mil MIN Result	
	Breaking Strength, min, lbf (N)	D 751	200 (890)	240 (1,068)	
	Elongation at Break, min, %	D 751	15	15	
Strength	Tearing Strength, min, lbf (N)	D 751	45 (200)	45 (200)	
Stre	Seam Strength, min, % of breaking strength	D 751	75	80	
	Static Puncture Resistance lbf (kg)	D 5602	Pass @ 33 (15)	Pass	
	Dynamic Puncture Resistance J	D 5635	Pass @ 20	Pass	
	Thickness, min, in.	D 751	+/- 10% from Nominal	0.060 Minimal	
Longevity	Thickness Over Scrim, min, in.	D 7635	0.016	0.025	
Long	Change in Weight After Immersion in Water, max, %	D 570 modified	3.0	3.0	
	Low Temperature Bend, °F	D 2136	No cracks @ -40° F	Pass	
	Properties after Heat Aging, min	D 3045	56 days @ 176° F		
ged ance	Breaking Strength, %	D 751	90	>90	
Heat Aged Performance	Elongation, %	D 751	90	>90	
Pel	Linear Dimensional Change, max, % after 6 hrs @ 176° F	D 1204	0.5	<0.5	
e	Accelerated Weathering, min	G 151 & G 154	5,000 hrs		
ther nanc	Cracking (@7x magnification)	G 154	No cracks	Pass	
Weather Performance	Discoloration (by observation)	G 154	Negligible	Negligible	
4	Crazing (@7x Magnification)	G 154	No crazing	Pass	

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at www.jm.com/roofing. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit www. jm.com/terms-conditions.