

JM Two-Part Urethane Insulation Adhesive

ΑD

Type

В

Cover Board

Multi-Ply

Single Ply

Features and Components

Use: For bonding insulation board products to approved roofing

substrates, and insulation to insulation.

Type: Two-part, cold application insulation adhesive.

Substrates: Compatible with the following insulations, cover boards,

and substrates: polyisocyanurate; HD wood fiber; perlite;

HD Polyiso; gypsum; concrete; treated plywood;

cementitious wood fiber plank; base sheets; gypsum; and some existing smooth-surfaced asphalt (per inspection).

Color: Pink

Features: No primers or catalysts are required for application.

May be used in single ply and bituminous systems.

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.



TPO PVC EPDM

MF AD SA IW MF AD IW MF AD BA

Used to adhere Insulation in all Single Ply systems

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

Maximum VOC	11 g/l as applied after mixing (EPA method 24)
i waxiiiluiii voc	

Physical Properties

Property		ASTM Test Method	JM Two-Part UIA	
	Weight (liquid components) Viscosity (liquid components)	Part 1	_	10.32 lb/gal (1.2 kg/l)
ight		Part 2	_	8.54 lb/gal (1.0 kg/l)
We		Part 1	_	300 cps
		Part 2	_	280 cps
	Density - Free Rise		D-1622	3.2 lb/cf (0.05 g/cm)
gth	Compressive Strength - Parallel		D-1621	38 psi (0.26 MPa) @ 6% deflection
tren	Tensile Strength Water Absorption Closed Cell Content		D-1623	35 psi (0.26 MPa)
S			D-2843	5.1%
			D-2856	90% (min)

Codes and Approvals







Storage

Shelf Life	18 months from manufacture date
Storage Conditions	Clean, dry, well-ventilated indoor environment in an unopened container
Temperature Range	45°F to 95°F (7°C to 35°C) - Protect from freezing

Installation/Application





Bead

• Cartridges: Two grades available, applied at temperatures between: Winter grade: 0°F to 65°F (-18°C to 18.3°C)

 Boxes/Drums: Two grades available, applied at temperatures of: Regular grade: 40°F (4°C) and above Winter grade: 25°F to 65°F (-4°C to 18.3°C)

- Adhesive must be 72°F (22°C) before using in a pace cart.
- Refer to the application instructions guidelines for proper utilization of this product.

Packaging and Coverage

. uonuging and ooronge						
Container Type	Case	Box	Drum			
Items per Case/ Set	4 - cartridges/ case with 6 mixing tips	2 - boxes (parts)/ Set 5 gal (18.9 l) each	2 - drums (parts)/Set 15 gal (56.8 I) each			
Shipping Weight (approx.)	19 lb (8.6 kg)	Part 1 = 52 lb (23.6 kg) Part 2 = 43 lb (19.5 kg)	Part 1 = 160 lbs (72.6 kg) Part 2 = 135 lbs (61.2 kg)			
Pallet Quantity	40	32	9			
Coverage Rate*	400 ft ² to 600 ft ² (37.16 m ² to 55.74 m ²) per case	1200 ft ² to 2500 ft ² (111.5 m ² to 185.8 m ²) per set	3600 ft ² to 7500 ft ² (334.5 m ² to 696.8 m ²) per set			

⁺⁵⁰ gal size available as special order item.

^{*}Coverage, open and dry time rates can vary dramatically depending on the particular substrate and environmental conditions. Coverage rates stated herein are approximate only. If FM Global® or UL® approval is required, consult specific RoofNavSM or the UL Certifications Directory for specific application rates.



JM Two-Part Urethane Insulation Adhesive

Installation/Application Instructions

JM Two-Part UIA is dispensed in a semi-liquid bead that rises ¾" to 1" (19 mm to 25 mm) above the substrate. Beads are typically 12" (305 mm) on center. Within two minutes, the insulation board is placed into the adhesive and walked into place. Weigh the board stock down with readily available load on the rooftop; example pails of bonding adhesive, screw/plate buckets or other sources of weight (minimum 32 lbs) that will not damage the roof insulation. The adhesive cures completely in approximately 4 to 8 minutes after application, depending on temperature and weather conditions. Note: Board stock must be placed into the adhesive while it is still wet (before it reaches its tack-free state).

Ensure all insulation boards are 4' x 4' (1.22 m x 1.22 m) or smaller. Ensure all surfaces are dry and free of any debris, dirt, oil and grease before using JM Two-Part UIA.

Typical Application Rates

Insulation to:	sqs/gal pace cart	sqs/box of 4 cartridges
Concrete	up to 2.5	6
Insulation	up to 2.5	6
Smooth BUR	up to 1.7	5
Mod Bit	up to 1.7	5
Gypsum	up to 1.2	4
Lightweight Concrete	up to 1.7	4
Wood	up to 2.5	6
Tectum	up to 1.2	4
Steel	up to 1.4	4

Clean-Up and Disposal

Disposal

Neutralize and dispose of spilled material, unused contents and empty containers in accordance with local, state and federal regulations.

Environmental Hazard

PMDI in Part 1 component may cause pollution. Do not discharge into lakes, streams, ponds or public waters. For guidance, contact your regional office of the U.S. Environmental Protection Agency.

Precautions

First Aid — In case of contact with eyes, immediately flush eyes with running water for at least 15 minutes. Call a physician immediately. In case of contact with skin, wash affected area with soap and water. Remove all contaminated clothing and shoes. Wash clothing before reuse and discard contaminated shoes. If swallowed, drink large amounts of water to dilute. If vomiting occurs, drink more water and call a physician immediately.

Environmental Hazard — PMDI in Part 1 component may cause pollution. Do not discharge into lakes, streams, ponds or public waters. For guidance, contact your regional office of the U.S. Environmental Protection Agency.

Disposal — Neutralize and dispose of spilled material, unused contents and empty containers in accordance with local, state and federal regulations.

Safety — Wear proper clothing and safety equipment.

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at www.jm.com/roofing. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit www.jm.com/terms-conditions.