DAMPPROOFING

118 Black Asphaltum



Read Safety Data Sheet before using this product.

DESCRIPTION: 118 Black Asphaltum is a special formulated **QUICK-DRYING** general purpose black asphalt paint. It is prepared from a selected, high melting- point asphalt, carefully admixed with a pure hydrocarbon solvent to a paint consistency. It will withstand the rigors of hot summer temperatures without sagging or running. It provides excellent protection against weather and corrosion.

USES: 118 Black Asphaltum has wide use as a general purpose black asphalt coating on all surfaces. It provides excellent protection for aluminum window frames and other metals when placed in contact with masonry walls. It will also help prevent corrosion and decay on storage tanks, railings, pipe and exterior duct work.

SURFACE PREPARATIONS: All surfaces should be dry, clean and free from oil or grease, dust, dirt, loose paint or other foreign matter.

APPLICATION: Apply 118 Black Asphaltum by brush or spray equipment. Masonry and dried out built-up roof structures should be liberally coated to obtain the most penetration. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

COVERAGE RATE: Apply at the rate of 1 to 1.5 gallon per 100 sq. ft. depending upon the condition and porosity of the surface to be primed.

CAUTION: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying. Exterior use only.

PACKAGING: Available in 5-gallon pails and 55-gallon drums.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon: 7.34 lbs.

Solids by Weight: 52% Nominal

Solids by Volume: 46% Nominal

Color: Black

Application Temp.: 40°F to 120°F

Dry Time: 8 to 24 hours

Service Temp

(Cured Film): -40°F to 180°F

VOC Content: 430 g/L MAX

TT-C-494

FF-H-C-494

MIL-C-16173D



330 Central Ave. I Clark, NJ 07066 I 800.526.4236 I Fax 732.388.9422 | www.karnakcorp.com